

# **Apollo Scientific**

Part Number: BIM1008 Version No: 1.2 Safety Data Sheet

Chemwatch Hazard Alert Code: 2

Issue Date: 07/06/2023 Print Date: 07/06/2023 S.GHS.GB-NIR.EN

# SECTION 1 Identification of the substance / mixture and of the company / undertaking

#### **Product Identifier**

Product name	alpha-Methyl-D-mannopyranoside
Chemical Name	methyl-alpha-D-mannopyranoside
Synonyms	Not Available
Chemical formula	C7-H14-O6
Other means of identification	Not Available
CAS number	617-04-9*

# Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not /

Available

# Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road Not Available SK6 2QR United Kingdom (NI)
Telephone	01614060505	+44(0) 161 406 0505
Fax	0161 406 0506	Not Available
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk
Email	sales@apolloscientific.co.uk	sales@apolloscientific.co.uk

# **Emergency telephone number**

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

# **SECTION 2 Hazards identification**

# Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>	H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2
Legend:	1. Classified by Chernwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

# Label elements

Hazard pictogram(s)	
Signal word	Warning

# Hazard statement(s)

H335	May cause respiratory irritation.
H315	Causes skin irritation.
H319	Causes serious eye irritation.

# Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.
P261	Avoid breathing dust/fumes.
P280	Wear protective gloves, protective clothing, eye protection and face protection.
P264	Wash all exposed external body areas thoroughly after handling.

# Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P312	Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.
P337+P313	If eye irritation persists: Get medical advice/attention.
P302+P352	IF ON SKIN: Wash with plenty of water.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
P332+P313	If skin irritation occurs: Get medical advice/attention.
P362+P364	Take off contaminated clothing and wash it before reuse.

#### Precautionary statement(s) Storage

P405	Store locked up.
P403+P233	Store in a well-ventilated place. Keep container tightly closed.

#### Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

# **SECTION 3 Composition / information on ingredients**

#### Substances

CAS No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
Not Available	100	alpha-Methyl- D-mannopyranoside	Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3 , Skin Corrosion/Irritation Category 2, Serious Eye Damage/Eye Irritation Category 2; H335, H315, H319 <sup>[1]</sup>	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

# Mixtures

See section above for composition of Substances

# **SECTION 4 First aid measures**

#### Description of first aid measures

Eye Contact

If this product comes in contact with the eyes: • Wash out immediately with fresh running water.

	<ul> <li>Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids.</li> <li>Seek medical attention without delay; if pain persists or recurs seek medical attention.</li> <li>Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.</li> </ul>
Skin Contact	If skin or hair contact occurs: <ul> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

# Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

### **SECTION 5 Firefighting measures**

#### **Extinguishing media**

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

#### Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.

# Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> <li>May emit corrosive fumes.</li> </ul>

#### **SECTION 6 Accidental release measures**

# Personal precautions, protective equipment and emergency procedures

See section 8

#### **Environmental precautions**

See section 12

# Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid breathing dust and contact with skin and eyes.</li> <li>Wear protective clothing, gloves, safety glasses and dust respirator.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Sweep up, shovel up or</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	Moderate hazard. CAUTION: Advise personnel in area. Alert Emergency Services and tell them location and nature of hazard.

Control personal contact by wearing protective clothing.
Prevent, by any means available, spillage from entering drains or water courses.
<ul> <li>Recover product wherever possible.</li> </ul>
IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.
ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.
If contamination of drains or waterways occurs, advise Emergency Services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

# **SECTION 7 Handling and storage**

# Precautions for safe handling

Safe handling	<ul> <li>Avoid all personal contact, including inhalation.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Prevent concentration in hollows and sumps.</li> <li>DO NOT enter confined spaces until atmosphere has been checked.</li> <li>DO NOT allow material to contact humans, exposed food or food utensils.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately. Launder contaminated clothing before re-use.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

# Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	None known

# **SECTION 8 Exposure controls / personal protection**

# **Control parameters**

# Occupational Exposure Limits (OEL)

#### INGREDIENT DATA

Not Available

#### Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
alpha-Methyl- D-mannopyranoside	Not Available	Not Available	Not Available

Original IDLH

Ingredient	Original IDLH	Revised IDLH
alpha-Methyl- D-mannopyranoside	Not Available	Not Available
Exposure controls		
	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed	

Appropriate engineering controls	Engineering controls are used to remove a hazard or place engineering controls can be highly effective in protecting w provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job acti Enclosure and/or isolation of emission source which keeps that strategically "adds" and "removes" air in the work envir designed properly. The design of a ventilation system must Employers may need to use multiple types of controls to pr • Local exhaust ventilation is required where solids are h large, a certain proportion will be powdered by mutual f • If in spite of local exhaust an adverse concentration of t considered. Such protection might consist of: (a): particle dust respirators, if necessary, combined with an (b): filter respirators with absorption cartridge or canister of (c): fresh-air hoods or masks. Air contaminants generated in the workplace possess vary velocities" of fresh circulating air required to effectively rem Type of Contaminant: direct spray, spray painting in shallow booths, drum filling, discharge (active generation into zone of rapid air motion) grinding, abrasive blasting, tumbling, high speed wheel ge velocity into zone of very high rapid air motion). Within each range the appropriate value depends on: Lower end of the range 1: Room air currents minimal or favourable to capture 2: Contaminants of low toxicity or of nuisance value only. 3: Intermittent, low production. 4: Large hood or large air mass in motion Simple theory shows that air velocity falls rapidly with dista generally decreases with the square of distance from the e extraction point should be adjusted, accordingly, after refer extraction fan, for example, should be a minimum of 4-10 n distant from the extraction point. Other mechanical conside apparatus, make it essential that theoretical air velocities a installed or used.	orkers and will typically be independively or process is done to reduce the a selected hazard "physically" aware ronment. Ventilation can remove or the match the particular process and correvent employee overexposure. Handled as powders or crystals; evend friction. The substance in air could occur, results and the particular process and correvent employee overexposure. In absorption cartridge; If the right type; Ing "escape" velocities which, in turnove the contaminant. Conveyer loading, crusher dusts, go enerated dusts (released at high initial Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only nce away from the opening of a simple cases). The ence to distance from the contaminant (son-2000 f/min) for extraction corrections, producing performance definitions).	the termine the "capture Air Speed: as 1-2.5 m/s (200-500 f/min.) ial 2.5-10 m/s (500-2000 f/min.) apple extraction pipe. Velocity the termine the air speed at the ating source. The air velocity at the of crusher dusts generated 2 metres incits within the extraction	
Individual protection measures, such as personal protective equipment				
Eye and face protection	<ul> <li>Safety glasses with side shields.</li> <li>Chemical goggles.</li> <li>Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent]</li> </ul>			
Skin protection	See Hand protection below			

# otection See Hand protection below The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.

Hands/feet protection

The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be

Personal hygiene is a key element of effective hand care. Gloves must only be worm on class in the selection of gloves include:         Image: Statistic in the selection into account when considering gloves for long-term and the statustic gloves in any application, gloves are rated as:         Image: Statistic in the selection of the selection into account when considering gloves f		observed when making a final choice.
Suitability and durability of give type is dependent on usage. Important factors in the selection of gives include: <ul> <li>Generative and duration of contract.</li> <li>chemical resistance of give material,</li> <li>give thickness and</li> <li>destering:</li> <li>Select gives tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent).</li> <li>When prologend or frequently repeated contact may occur, a give with a protection class of 5 or higher (breakthrough time grater than 240 minutes according to EN 374, AS/N2S 2161.10 r national equivalent) is recommended.</li> <li>When only brief contact is expected.</li> <li>Some give polymer types are less affected by movement and this should be taken into account when considering gives for inorg-tem use.</li> <li>contaminate gip/ws should be repleced.</li> <li>As defined in ASTM F-739-96 in any application, gives are rated as:</li> <li>Excellent when breakthrough time &lt; 40 min</li> <li>For owhen give metrical digives with a thickness in price according to ever material digits.</li> <li>For owhen gives and discuss the repleced.</li> <li>Kadefined in ASTM F-739-96 in any application, gives are rated as:</li> <li>Excellent when breakthrough time &lt; 40 min</li> <li>For owhen gives and metrial digrads</li> <li>For general applications, gives with a thickness its price and and the socure commended.</li> <li>Fload be emphased that gives that always be taken into account to ever any appending on the activity is needed.</li> <li>For owhen gives and way depending on the activity inversed and the diverse gives and ways depending on the activity is needed.</li> <li>For owhen gives and ways depending on the activity inversed and would correlise and account to ever and the gives of varying thickness may abs required where there is a me</li></ul>		Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands
<ul> <li>Instance of glove material, or down material, or down material, or down material, or down thickness and ordered to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</li> <li>When protonged or frequently repeated contact may court, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0 or national equivalent).</li> <li>When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in AST NF739-68 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Fair whan breakthrough time &gt; 20 min</li> <li>Fair whan breakthrough time &gt; 20 min</li> <li>Fair whan breakthrough time &gt; 20 min</li> <li>For general applications, gloves material equivalent) is recommended.</li> <li>It should be emphasized that glove thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be amphasized that glove thickness typically greater than 0.35 mm, are recommended.</li> <li>Bodow thickness may also vary depending on the gloves on any time glove plow material. Therefore, glove selection also do be based on consideration of the task requirements and knowledge of prevention of the task. For example:</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of annual desterity is needed. However, these gloves are not pleve on the sakt courd by be washed and drive there is a barcsin or puncture potential.</li> <li>Thinker gloves (down to 0.1 mm or less) may be required where a high degree of annual desterity is i.e. where t</li></ul>		should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.
<ul> <li>- chemical resistance of glove material,         <ul> <li>- glove hickness and</li> <li>- destrify</li> </ul> </li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZ5 2161.1 or national equivalent).</li> <li>- When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 20 minutes according to EN 374, AS/NZ5 2161.10.1 or national equivalent) is recommended.</li> <li>- When only biel contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZ5 2161.10.1 or national equivalent) is recommended.</li> <li>- Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>- Contaminated gloves should be replaced.</li> <li>- Societ and the application, gloves are rated as:                 <ul> <li>- Fair when breakthrough time &gt; 20 min</li> <li>- Goor when glove material aglives in thickness typically greater than 0.35 mm, are recommended.</li> <li>- Thickness may also vary depending on the glove mainfacturer, the glove pand the glove model. Therefore, the annufacturers technical data should be appendient on the exact composition of the glove material. Therefore, glove a selection should also be taken into account and would also be taken into account and be into accound when a charge glove a neasuprice time. Hue data is a chareinal data ways to takein thre</li></ul></li></ul>		Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:
<ul> <li>- giove hickness and</li></ul>		frequency and duration of contact,
<ul> <li>. aximity</li> <li>. aximity</li> <li>Select glows is tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent).</li> <li>. When prolonged or frequently repeated contact may occur, a glow with a protaction class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N2S 2161.1 or national equivalent) is recommended.</li> <li>. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>. Contaminated gloves should be replaced.</li> <li>As defined in ASTM F739-96 in any application, gloves are rated as:         <ul> <li>. Excellent when breakthrough time &gt; 40 min</li> <li>. Poor when glove material degrades</li> <li>. For any more polication, gloves are rated as:                 <ul> <li>. Excellent when breakthrough time &gt; 40 min</li> <li>. Poor when glove material degrades</li> <li>. For general applications, gloves with a hickness typically greater than 0.35 mm, are recommended.</li> <li>. Stold be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the most appropriate glove to the task. Note: Depending on the activity being conducted, glows of varying thickness may be required where does and howidege of brankthrough time set as a chemical) is the set and the set and to any application, gloves are as mechanical (as well as a chemical) is the dependent on the exact composition of the ask complexity is needed.</li></ul></li></ul></li></ul>		chemical resistance of glove material,
Select gloves tested to a relevant standard (e.g. Europe EN 374, US F730, ASX25 2161.1 or national equivalent).         • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASX25 2161.10.1 or national equivalent) is recommended.         • When only bief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 50 minutes according to EN 374, ASX25 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-tem use.         • Contaminated gloves should be replaced.         As defined in ASTM F735.9961         • Bod when breakthrough time > 400 min         • Good when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         It should be based on consideration of the glove composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         It should be based on consideratin of the task req		· glove thickness and
<ul> <li>When inplonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.</li> <li>When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 40 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Pair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove restrations the should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the axity the glove state on the glove material depending on the axity their gloves are only likely to give should be requered.</li> <li>Thick gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these gloves are only likely to give should also a be accord on a clove hard and dive the resist and that a protection against undissolved, dry solids, where abravise particles are not present.</li> <li>Thick gloves (down to 0.1 mm or less) may be required where here is a mechanical (</li></ul></li></ul>		· dexterity
greater than 240 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended.         • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended.         • Gontaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 400 min         • Good when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a blow thackness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a blow thackness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a blow thackness may also vary depending on the glove manufacture; the glove specific tasks. For example:         • Thinner gloves (up to 1 mm or less) may be required where a hind glove type and the glove model. Therefore, the manufactures technical data should always be should hormally be igstored on should also be also on consideration of the task requirements on the exact composition of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may a chemical of the stars appropriate glove for the task. Note: Depending on the activity being co		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
• When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZ5 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       • Excellent when breakthrough time > 40 min         • Good when breakthrough time > 20 min       • Fair when breakthrough time > 20 min         • Por when glove material digorabes       For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to emparine difficustion, gloves ealerclon should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove mine enquired to reparcile tasks. For example:         • Thinkner gloves (Jown to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are not present.         • Thicker gloves (Jup to 3 mm or more) may be required where a high degree of annual dexterity is needed. However, these gloves are not present.         • Thinker gloves (Jup to 3 mm or more) may be required where a high degree of anauuld dexterity is needed. However, these gl		· When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time
according to EN 374, AS/NZS 2161.10.1 for national equivalent) is recommended.         - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         - Contaminated gloves should be replaced.         As defined in ASTM F.739-66 in any application, gloves are rated as:         - Excellent when breakthrough time > 400 min         - God when breakthrough time > 20 min         - Fair when breakthrough time > 20 min         - Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove material. Therefore, glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         - Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraching on protection and would normally be just for single use applications, then disposed of.         - Thinner gloves (down to 0.1 mm or neor) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraching on puncture potential         Gloves must only be worm on clean hands. After using gloves, hands should be vashed and dried thoroughly. A		greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       • Excellent when breakthrough time > 20 min         • Excellent when breakthrough time > 20 min       • Excellent when breakthrough time > 20 min         • Poor when glove material degrades       • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required there a high degree of manual dectarity is needed. However, these gloves are only likely to give short duration protection and would normaly be iguited for specific tasks. For example:         • Thinker gloves (duor too 1.1 mm or less) may be required where a high degree of manual dectarity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (duor too 1.1 mm or less) may be required where a high degree of manual dectarity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (duor too 1.1 mm or l		· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
Iong-term use:       - Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       - Excellent when breakthrough time > 480 min         - Good when breakthrough time > 20 min       - Fair when breakthrough time > 20 min         - Por when glove material degrades       For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturer technical data should always be taken into account to ensure selection of the most appropriate glove of the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to L) in mor (ress) way be required where high degree of manual deterting is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, gloves with a site is abrasion to on puncture potential         Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed motisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where a braisvie particles are not present. <ul> <li>polychythorporene.</li> <li>hintile</li></ul>		according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time < 20 min         • Fair when breakthrough time < 20 min         • For yeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may also care only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (ubor to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves mituned moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present.         • hotif thobber.       • hoty/choroprene.         • hutrie rubber.       • boly who do no elean hands. After us		· Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for
As defined in A <sup>5</sup> TM F-739-96 in any application, gloves are rated as:       Excellent when breakthrough time > 400 min         · Good when breakthrough time > 20 min       · Fair when breakthrough time > 20 min         · Poor when glove material degrades       For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most apporpriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (up to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only blew tors on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed molicules are not present.         • polychloroprene.       • hittire trabber.         • hould in the obser.       • butyl nubber.         • hittire tarbber.       • butyl nubber.         • butyl nubber.       • butyl nubber.         • hutrite rubber.       • butyl		long-term use.
<ul> <li>Excellent when breakthrough time &gt; 480 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>For yeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It is hould be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove maufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 0.1 mm or less) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves more on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraice particles are not present.</li> <li>polychioroprene.</li> <li>hittir tubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li> <li>butyf rubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li> <li>butyf ubber.</li></ul>		Contaminated gloves should be replaced.
<ul> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove milder.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to emsure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>Polychloroprene.</li> <li>hirtir tubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber</li></ul></li></ul>		As defined in ASTM F-739-96 in any application, gloves are rated as:
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the tagk movile do the on consideration of the tagk requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be prequired to specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychiloroprene. • nitrile rubber.</li> <li>butyl rubber.</li> <li>butyri rubhoride.</li></ul>		· Excellent when breakthrough time > 480 min
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 m, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinker gloves (up to 0.1 mm or less) may be required where a high degree of manual dexterily is needed. However, these gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where eatraive particles are not present polychoroprene initire rubber.</li> <li>butyl rubber.</li> <li>hittorcaautchouc polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> <li>Body protection</li> <li>See Other protection below</li> <li>Other protection</li> <li>Skin cleansing cream Skin cleansing cream Skin cleansing cream.</li> <li>Skin cleansing cream.</li> </ul>		· Good when breakthrough time > 20 min
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dextript is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dextript is needed. However, these gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. bylychloroprene. hittile rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber. bylychloroprene. bylychloroprene. bylychloroprene. bylychloroprene. bylychloroprene. bylychloroprene. bylychloropre		· Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required where a high degree of manual detrify is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraisnion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • hittile rubber. • hittile rubber. • hittile rubber. • polychloroprene. • hittile rubber. • fluorocaoutchouc. • polychloroprene. • hittile rubber. • fluorocaoutchouc. • polychloroprene. • hittile rubber. • fluorocaoutchouc. • polychloroprene. • hittile rubber. • fluorocaoutchouc. • polychloroprene. • hittile rubber. • Norealls. • P.VC apron. • See Other protectio		· Poor when glove material degrades
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove moutacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where a brasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>bouly lrubber.</li> <li>bouly lrubber.</li> <li>gloves shoul the examined for wear and/ or degradation constantly.</li> <li>Glove shoul the examined for wear and/ or degradation constantly.</li> <li>Other protection</li> <li>PAVC apron.</li> <li>barrier cream.</li> <li>Skin cleansing cream.</li> <li>Skin cleansing cream.</li> </ul>		
should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to 0.3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to 0.3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. butyl rubber. butyl rubber. ifuorocaoutchouc. polychiloroprene. ifuorocaoutchouc. butyl rubber. ifuorocaoutchouc. butyl rubber. ifuorocaoutchouc. butyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. botyl rubber. ifuorocaoutchouc. 		
Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: . Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. . Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present. bolychloroprene. hittile rubber. bolychloroprene. hittile rubber. bolychloroprene. hittile rubber. bolychloroprene. holychloroprene. hittile rubber. bolychloroprene. hittile rubber. <th></th> <th></th>		
manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. butyl rubber. butyl company and or degradation constantly. Body protection See Other protection below Other protection below butyle communication as a communication below butyle communication below butyle communication below butyle communication constantly.		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul><li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential              Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.              Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.              Polychloroprene.              hitrile rubber.              butyl rubber. </li></ul></li></ul>		
• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • hitrile rubber.         • butyl rubber.		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • budyl rubber.		
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polychloroprene.         • notriel rubber.         • butyl rubber.         • fluorocaoutchouc.         • polycharoprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polycharoprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polycharoprene.         • Noveralls.         • P.V.C apron.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • polychloroprene.       • initile rubber.       • butyl rubber.         • fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • P.V.C apron.         • Barrier cream.       • Skin cleansing cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. 		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • polychloroprene.       • nitrile rubber.         • butyl rubber.       • butyl rubber.         • fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.       • Skin cleansing cream.		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         fluorocaoutchouc.         polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below <ul> <li>Overalls.</li> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
i       polychloroprene.         i       nitrile rubber.         butyl rubber.       fluorocaoutchouc.         polycinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
<ul> <li>hitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection See Other protection below Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
Image: Protection of the protection		
Image: Polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Image: Body protection       See Other protection below         Image: Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> <li>Skin clean</li></ul>		▶ butyl rubber.
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> <li>Skin cleansing cream.</li> </ul>		▶ fluorocaoutchouc.
Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		polyvinyl chloride.
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		Gloves should be examined for wear and/ or degradation constantly.
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>	Body protection	See Other protection below
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		•
Other protection <ul> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
<ul> <li>Skin cleansing cream.</li> </ul>		
	Other protection	
r Eye wash unit.		ů – Elektrik
		r Eye wash unit.

#### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to

personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

#### **SECTION 9** Physical and chemical properties

#### Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	186-196	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

#### **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

# **SECTION 11 Toxicological information**

#### Information on toxicological effects

Inhaled

The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control

	measures be used in an occupational setting.
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	This material can cause eye irritation and damage in some persons.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

Legend:

1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	¥	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	*
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×

```
    Data available to make classification
```

# **SECTION 12 Ecological information**

#### Toxicity

Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity
	4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) -
	Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

# Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
	No Data available for all ingredients	No Data available for all ingredients

# **Bioaccumulative potential**

Ingredient	Bioaccumulation
	No Data available for all ingredients

# Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

# **SECTION 13 Disposal considerations**

Waste treatment methods	Vaste treatment methods	
Product / Packaging disposal	<ul> <li>Recycle wherever possible or consult manufacturer for recycling options.</li> <li>Consult State Land Waste Management Authority for disposal.</li> <li>Bury residue in an authorised landfill.</li> <li>Recycle containers if possible, or dispose of in an authorised landfill.</li> </ul>	

# **SECTION 14 Transport information**

#### Labels Required

Marine Pollutant NO

#### Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

#### Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
alpha-Methyl- D-mannopyranoside	Not Available

#### Transport in bulk in accordance with the IGC Code

Product name	Ship Type
alpha-Methyl- D-mannopyranoside	Not Available

#### **SECTION 15 Regulatory information**

# Safety, health and environmental regulations / legislation specific for the substance or mixture

#### **National Inventory Status**

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	No (alpha-Methyl-D-mannopyranoside)
Canada - DSL	No (alpha-Methyl-D-mannopyranoside)
Canada - NDSL	No (alpha-Methyl-D-mannopyranoside)
China - IECSC	Yes
Europe - EINEC / ELINCS / NLP	Yes
Japan - ENCS	No (alpha-Methyl-D-mannopyranoside)
Korea - KECI	No (alpha-Methyl-D-mannopyranoside)
New Zealand - NZIoC	Yes
Philippines - PICCS	No (alpha-Methyl-D-mannopyranoside)
USA - TSCA	No (alpha-Methyl-D-mannopyranoside)
Taiwan - TCSI	Yes
Mexico - INSQ	No (alpha-Methyl-D-mannopyranoside)
Vietnam - NCI	Yes
Russia - FBEPH	No (alpha-Methyl-D-mannopyranoside)
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

# **SECTION 16 Other information**

Revision Date	07/06/2023
Initial Date	07/06/2023

#### **SDS Version Summary**

Version Date of Update	Sections Updated
------------------------	------------------

#### Part Number: BIM1008 Version No: 1.2

#### alpha-Methyl-D-mannopyranoside

Version	Date of Update	Sections Updated
0.2	07/06/2023	Toxicological information - Acute Health (eye), Toxicological information - Acute Health (inhaled), Physical and chemical properties - Appearance, CAS Number, Toxicological information - Chronic Health, Hazards identification - Classification, Disposal considerations - Disposal, Exposure controls / personal protection - Exposure Standard, Firefighting measures - Fire Fighter (fire/explosion hazard), First Aid measures - First Aid (eye), Handling and storage - Handling Procedure, Composition / information on ingredients - Ingredients, Exposure controls / personal protection - Personal Protection (eye), Accidental release measures - Spills (major), Accidental release measures - Spills (minor), Handling and storage - Storage (storage incompatibility), Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms

#### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC - TWA: Permissible Concentration-Time Weighted Average

PC - STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit.

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

# Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Specific Target Organ Toxicity - Single Exposure	Expert judgement

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
(Respiratory Tract Irritation) Category 3 , H335	
Skin Corrosion/Irritation Category 2, H315	Expert judgement
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement

Powered by AuthorITe, from Chemwatch.