

Cerium, chips Apollo Scientific

Part Number: IN1399 Version No: 1.1 Safety Data Sheet (Conforms to Annex II of REACH (1907/2006) - Regulation 2020/878) Chemwatch Hazard Alert Code: 3

Issue Date: **16/09/2022** Print Date: **31/07/2023** S.REACH.GBR.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

1.1. Product Identifier

Product name	Cerium, chips
Chemical Name	cerium powder
Synonyms	Not Available
Proper shipping name	CERIUM, turnings or gritty powder
Chemical formula	Се
Other means of identification	Not Available
CAS number	7440-45-1
EC number	231-154-9

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
Uses advised against	No specific uses advised against are identified.

1.3. Details of the manufacturer or supplier of the safety data sheet

Registered company name	pollo Scientific		
Address	Whitefield Road, Bredbury SK62QR United Kingdom		
Telephone	01614060505		
Fax	0161 406 0506		
Website	http://www.apolloscientific.co.uk/		
Email	sales@apolloscientific.co.uk		

1.4. Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

SECTION 2 Hazards identification

2.1. Classification of the substance or mixture

Classification according to regulation (EC) No

H228 - Flammable Solids Category 1

Cerium, chips

1272/2008 [CLP] and amendments ^[1]	
Legend:	1. Classified by Chernwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

2.2. Label elements

Hazard pictogram(s)	
Signal word	Danger

Hazard statement(s)

H228 Flammable solid.

Supplementary statement(s)

Not Applicable

Precautionary statement(s) Prevention

P210	Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.		
P240	Ground and bond container and receiving equipment.		
P241	Use explosion-proof electrical/ventilating/lighting/intrinsically safe equipment.		
P280	Wear protective gloves and protective clothing.		

Precautionary statement(s) Response

P370+P378 In case of fire: Use alcohol resistant foam or normal protein foam to extinguish.
--

Precautionary statement(s) Storage

Not Applicable

Precautionary statement(s) Disposal

Not Applicable

2.3. Other hazards

REACH - Art.57-59: The mixture does not contain Substances of Very High Concern (SVHC) at the SDS print date.

SECTION 3 Composition / information on ingredients

3.1.Substances

1. CAS No 2.EC No 3.Index No 4.REACH No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor	Nanoform Particle Characteristics
Not Available	100	Cerium, chips	Not Applicable	Not Applicable	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

3.2.Mixtures

See 'Information on ingredients' in section 3.1

SECTION 4 First aid measures

4.1. Description of first aid measures

Eye Contact	If this product comes in contact with eyes: Wash out immediately with water. If irritation continues, seek medical attention.
	 Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.

Page 3 of 13 Cerium, chips

Skin Contact	 If skin or hair contact occurs: Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

4.2 Most important symptoms and effects, both acute and delayed

See Section 11

4.3. Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

5.1. Extinguishing media

DO NOT USE WATER, CO2 OR FOAM ON SUBSTANCE ITSELF

For SMALL FIRES:

Dry chemical, soda ash or lime.

For LARGE FIRES:

- DRY sand, dry chemical, soda ash;
- OR withdraw and allow fire to burn itself out.

5.2. Special hazards arising from the substrate or mixture

Fire Incompatibility Segregate from alcohol, water.

5.3. Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. May be violently or explosively reactive. Wear full protective clothing plus breathing apparatus. Prevent, by any means available, spillage from entering drains or water course. Consider evacuation (or protect in place) DO NOT use water on fires. CAUTION: If only water available, use flooding quantities of water or withdraw personnel. DO NOT allow water to enter containers. DO NOT approach containers suspected to be hot. Cool fire exposed containers with flooding quantities of water from a protected location until well after fire is out. If safe to do so, remove undamaged containers from path of fire. If fire gets out of control withdraw personnel and warn against entry. Equipment should be thoroughly decontaminated after use. Fight fire from a protected position or use unmanned hose holders or monitor nozzles. Withdraw immediately in case of rising sound from venting safety devices or discolouration of tanks. ALWAYS stay away from tank ends.
Fire/Explosion Hazard	 May ignite on contact with air, moist air or water. May react vigorously or explosively on contact with water. May decompose explosively when heated or involved in fire. May REIGNITE after fire is extinguished. Gases generated after contact with water or moist air may be poisonous, corrosive or irritating. Gases generated in fire may be poisonous, corrosive or irritating. Containers may explode on heating. Runoff may create multiple fire or explosion hazard.

SECTION 6 Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

See section 8

6.2. Environmental precautions

See section 12

6.3. Methods and material for containment and cleaning up

Minor Spills

IIs • Material from spill may be contaminated with water resulting in generation of gas which subsequently may pressure closed

Continued...

Cerium, chips

	 containers. Hold spill material in vented containers only and plan for prompt disposal Eliminate all ignition sources. Cover with DRY earth, sand or other non-combustible material. Then cover with plastic sheet to minimise spreading and to prevent exposure to rain or other sources of water. Use clean, non-sparking tools to collect absorbed material and place into loosely-covered metal or plastic containers ready for disposal.
Major Spills	 Wear gloves and safety glasses as appropriate. Clear area of personnel and move upwind. Alert Fire Brigade and tell them location and nature of hazard. Eliminate all ignition sources (no smoking, flares, sparks or flames) Stop leak if safe to do so; prevent entry into waterways, drains or confined spaces. May be violently or explosively reactive. DO NOT walk through spilled material. Wear gloves and year to be added to the space of the

6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

7.1. Precautions for safe handling

	-
	Avoid all personal contact, including inhalation.
	Wear protective clothing when risk of overexposure occurs.
	Use in a well-ventilated area.
	Avoid contact with moisture.
	Avoid smoking, naked lights or ignition sources.
	Avoid contact with incompatible materials.
	When handling, DO NOT eat, drink or smoke.
Safe handling	Keep containers securely sealed when not in use.
3	 Avoid physical damage to containers.
	 Always wash hands with soap and water after handling.
	 Work clothes should be laundered separately and before re-use
	 Use good occupational work practice.
	 Observe manufacturer's storage and handling recommendations contained within this SDS.
	 Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are
	maintained.
Fire and explosion	See section 5
protection	
	KEEP DRY! Packages must be protected from water ingress.
	FOR MINOR QUANTITIES:
	Store in an indoor fireproof cabinet or in a room of noncombustible construction and
	provide adequate portable fire-extinguishers in or near the storage area.
	FOR PACKAGE STORAGE
	Store in original containers in approved flame-proof area.
	No smoking, naked lights, heat or ignition sources.
	• DO NOT store in pits, depressions, basements or areas where vapours may be trapped.
Other information	Keep containers securely sealed.
	Store away from incompatible materials in a cool, dry well ventilated area.
	Protect containers against physical damage and check regularly for leaks.
	Protect containers from exposure to weather and from direct sunlight unless: (a) the packages are of metal or plastic
	construction; (b) the packages are securely closed are not opened for any purpose while in the area where they are stored;
	(c) adequate precautions are taken to ensure that rain water, which might become contaminated by the dangerous goods, is
	collected and disposed of safely.
	Ensure proper stock-control measures are maintained to prevent prolonged storage of dangerous goods.

t Number: IN1399	Page 5 of 13 Issue Date: 16/09
rsion No: 1.1	Cerium, chips Print Date: 31/07
	Automatic fire-sprinklers MUST NOT be installed in room or space.
	The room or space must be located at least five metres from the boundaries of the premises and from other buildings unless separated by a wall with a fire resistance of at least four hours.
	Observe manufacturer's storage and handling recommendations contained within this SDS.
	Storage containers must be hermetically sealed; the product must be stored under an inert, dry gas. For low viscosity materials and solids:
	storage, including any incompatibilities
	Drums and jerricans must be of the non-removable head type.
	Where a can is to be used as an inner package, the can must have a screwed enclosure.
	Even a starial and it was in a start based 00000 a OL (00 days, O)
	For materials with a viscosity of at least 2680 cSt. (23 deg. C):
Cuitable container	 For materials with a viscosity of at least 2680 cSt. (23 deg. C): Removable head packaging and
Suitable container	
Suitable container	Removable head packaging and
Suitable container	Removable head packaging and
Suitable container	 Removable head packaging and cans with friction closures may be used.
Suitable container	 Removable head packaging and cans with friction closures may be used. Where combination packages are used, there must be sufficient inert absorbent material to absorb completely any leakage that
Suitable container	 Removable head packaging and cans with friction closures may be used. Where combination packages are used, there must be sufficient inert absorbent material to absorb completely any leakage that may occur, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the
Suitable container	 Removable head packaging and cans with friction closures may be used. Where combination packages are used, there must be sufficient inert absorbent material to absorb completely any leakage that may occur, unless the outer packaging is a close fitting moulded plastic box and the substances are not incompatible with the plastic.

7.3. Specific end use(s)

Storage incompatibility

Hazard categories in accordance with

Regulation (EC) No 1272/2008

Qualifying quantity (tonnes) of dangerous substances as referred to

in Article 3(10) for the application of

See section 1.2

SECTION 8 Exposure controls / personal protection

Moisture sensitiveStore under argon

Not Available

Not Available

8.1. Control parameters

Ingredient	DNELs Exposure Pattern Worker	PNECs Compartment
Not Available	Dermal 5.07 mg/kg bw/day (Systemic, Chronic) Inhalation 8.13 mg/m ³ (Systemic, Chronic) Dermal 3.04 mg/kg bw/day (Systemic, Chronic) * Inhalation 4.8 mg/m ³ (Systemic, Chronic) * Oral 3.04 mg/kg bw/day (Systemic, Chronic) *	0.6 mg/L (Water (Fresh)) 60.9 μg/L (Water - Intermittent release) 60.9 mg/L (STP)

* Values for General Population

Occupational Exposure Limits (OEL)

INGREDIENT DATA

Source	Ingredient	Material name	TWA	STEL	Peak	Notes
Not Available						

Not Applicable

Emergency Limits

Ingredient	TEEL-1	TEEL-2		TEEL-3
Cerium, chips	Not Available	Not Available		Not Available
Ingredient	Original IDLH		Revised IDLH	
Cerium, chips	Not Available		Not Available	

8.2. Exposure controls

8.2.1. Appropriate	 Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation that strategically "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure. Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction. Exhaust ventilation should be designed to prevent accumulation and recirculation of particulates in the workplace. If in spite of local exhaust an adverse concentration of the substance in air could occur, respiratory protection should be considered. Such protection might consist of: (a): particle dust respirators, if necessary, combined with an absorption cartridge; (b): filter respirators with absorption cartridge or canister of the right type; (c): fresh-air hoods or masks Build-up of electrostatic charge on the dust particle, may be prevented by bonding and grounding. Powder handling equipment such as dust collectors, dryers and mills may require additional protection measures such as explosion venting. Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture vel				
engineering controls	Type of Contaminant:		Air Speed:		
	direct spray, spray painting in shallow booths, drum filling, discharge (active generation into zone of rapid air motion)		1-2.5 m/s (200-500 ft/min)		
	grinding, abrasive blasting, tumbling, high speed wheel ge velocity into zone of very high rapid air motion).	nerated dusts (released at high initial	2.5-10 m/s (500-2000 ft/min)		
	Within each range the appropriate value depends on:				
	Lower end of the range	Upper end of the range			
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents			
	2: Contaminants of low toxicity or of nuisance value only	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use	High production, heavy use		
	4: Large hood or large air mass in motion	4: Small hood-local control only	rol only		
	Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velo generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velo extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 ft/min) for extraction of crusher dusts generate metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the exapparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction system installed or used.				
8.2.2. Individual protection measures, such as personal protective equipment					
Eye and face protection	 Safety glasses with side shields Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent] Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59]. 				
Skin protection	See Hand protection below				
Hands/feet protection	Wear general protection observed Wear general protective gloves, eg. light weight rubber gloves. The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • frequency and duration of contact,				

- dexterity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. - Contaminated gloves should be replaced. As defined in ASTM F739-96 in any application, gloves are rated as: - Excellent when breakthrough time > 20 min - Good when breakthrough time > 20 min - Fair when breakthrough time > 20 min - Good when or protection of the glove will be dependent on the exact composition of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturer, the glove will also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vay depending on the glove manufacturer, the glove wore model. Therefore, the manufacturers technical data should always be taken into account to nearnus eslection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required. However, these gloves up to 3 m or more) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Rolove thitch coses. See Other prote		chemical resistance of glove material,
Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1.0 r national equivalent). · When prolonged to frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 200 minutes according to EN 374, AS/NZS 2161.1.0.1 or national equivalent) is recommended. · When only brief contact is expected, a glowe with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.1.0.1 or national equivalent) is recommended. · Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. · Contaminated gloves should be replaced. As defined in ASTM F-730-96 in any application, gloves are rated as: · Excellent when breakthrough time > 20 min · Bri when breakthrough time > 20 min · Fair when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily of the glove wilk a considered of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the glove moded. It should be to thickness in any occur, gloves of varying thickness may be caquiced. However, these gloves are only likely to give short duration protection and wo		glove thickness and
• When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • As defined in ASTM F.739-6in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • Feir when breakthrough time > 20 min • Por when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account or ensure selection of the most appropriate glove for the task. Note: Expending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where three is abrasion or puncture potential. </th <th></th> <th></th>		
greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • When only brief contact is expected, a glove with a protection diss of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 400 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. I should be emphasised that glove thickness is not necessarily agood predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Glove protection See Other protection below <t< th=""><th></th><th></th></t<>		
• When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161:10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • Foor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove and the glove through times. Glove thickness may also vary depending on the glove sort varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves m		
according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 400 min • Good when breakthrough time > 20 min • Por when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinker gloves (up to 3 mm o		
• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Containiated gloves should be replaced. • As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • For when glove material degrades • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mill be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended. Body protection See Other protection below <th></th> <th></th>		
Iong-term use. . Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: . Excellent when breakthrough time > 480 min . Good when breakthrough time > 20 min . Excellent when breakthrough time > 20 min . Fair when breakthrough time > 20 min . Excellent when breakthrough time > 20 min . Poor when glove material degrades . For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves or dyarying thickness may be required there seeded. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection		o
As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required tor specific tasks. For example: Thicker gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (Up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Verralls. <th></th> <th></th>		
 Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. 		Contaminated gloves should be replaced.
• Good when breakthrough time > 20 min • Fair when breakthrough time < 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (up to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed more moisturiser is recommended. Body protection See Other protection below • Overalls. • Eyewash unit. • Barrie		As defined in ASTM F-739-96 in any application, gloves are rated as:
 Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		 Excellent when breakthrough time > 480 min
 Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the ask requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:		 Good when breakthrough time > 20 min
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: 		-
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Skin cleansing cream. Skin cleansing cream. Skin cleansing cream. 		
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.Body protectionSee Other protection below• Overalls. • Skin cleansing cream. • Skin cleansing cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		
manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Eyewash unit. • Barrier cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		
• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.Body protectionSee Other protection below• Overalls. • Eyewash unit. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		
 Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Overalls. • Eyewash unit. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Body protection See Other protection below • Overalls. • Eyewash unit. • Barrier cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		· Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there
Image: Incomparison on perfumed moisturiser is recommended. Body protection See Other protection below Image: Im		is abrasion or puncture potential
Body protection See Other protection below Image: See Other protection below • Overalls. • Eyewash unit. • Eyewash unit. • Barrier cream. • Skin cleansing cream. • Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		
 Overalls. Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
 Eyewash unit. Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 	Body protection	See Other protection below
 Barrier cream. Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
 Skin cleansing cream. Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity. 		
Some plastic personal protective equipment (PPE) (e.g. gloves, aprons, overshoes) are not recommended as they may produce static electricity.		
produce static electricity.		
Uther protection r por large scale or continuous use wear tight-weave non-static clothing (no metallic fasteners, cutts or pockets).	Other protection	 For large scale or continuous use wear tight-weave non-static clothing (no metallic fasteners, cuffs or pockets).
Non sparking safety or conductive footwear should be considered. Conductive footwear describes a boot or shoe with a sole	• • • • •	
made from a conductive compound chemically bound to the bottom components, for permanent control to electrically ground		made from a conductive compound chemically bound to the bottom components, for permanent control to electrically ground
the foot an shall dissipate static electricity from the body to reduce the possibility of ignition of volatile compounds. Electrical		the foot an shall dissipate static electricity from the body to reduce the possibility of ignition of volatile compounds. Electrical
resistance must range between 0 to 500,000 ohms. Conductive shoes should be stored in lockers close to the room in which		resistance must range between 0 to 500,000 ohms. Conductive shoes should be stored in lockers close to the room in which
they are worn. Personnel who have been issued conductive footwear should not wear them from their place of work to their		
homes and return.		homes and return.

Respiratory protection

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*		PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

• Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

8.2.3. Environmental exposure controls

See section 12

SECTION 9 Physical and chemical properties

9.1. Information on basic physical and chemical properties

Appearance	Not Available		
·			
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	795	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	3468	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	6.67	VOC g/L	Not Available
Nanoform Solubility	Not Available	Nanoform Particle Characteristics	Not Available
Particle Size	Not Available		

9.2. Other information

Not Available

SECTION 10 Stability and reactivity

10.1.Reactivity	See section 7.2
10.2. Chemical stability	 May heat spontaneously Identify and remove sources of ignition and heating. Incompatible material, especially oxidisers, and/or other sources of oxygen may produce unstable product(s). Avoid sources of water contamination (e.g. rain water, moisture, high humidity). Avoid contact with oxygenated solvents/ reagents such as alcohols.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

SECTION 11 Toxicological information

11.1. Information on hazard classes as defined in Regulation (EC) No 1272/2008 Information on toxicological effects

Inhaled	The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.
Ingestion	The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	Although the material is not thought to be an irritant (as classified by EC Directives), direct contact with the eye may cause transient discomfort characterised by tearing or conjunctival redness (as with windburn). Slight abrasive damage may also result.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

	ΤΟΧΙΟΙΤΥ	IRRITATION
Cerium, chips	Inhalation(Rat) LC50: >5.05 mg/l4h ^[1]	Not Available
	Oral (Mouse) LD50; 400 mg/kg ^[1]	
Legend:	1. Value obtained from Europe ECHA Registered Substances - A Unless otherwise specified data extracted from RTECS - Regist	-

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
	Le	gend: 🗙 – Data either not ava	ailable or does not fill the criteria for classification

Data available to make classification

11.2 Information on other hazards

11.2.1. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

11.2.2. Other information

See Section 11.1

SECTION 12 Ecological information

12.1. Toxicity

	Endpoint	Test Duration (hr)	Species	Value	Source
Cerium, chips	Not Available	Not Available	Not Available	Not Available	Not Available
Legend:	4. US EPA, E	n 1. IUCLID Toxicity Data 2. Europe ECHA R cotox database - Aquatic Toxicity Data 5. EC ion Data 7. METI (Japan) - Bioconcentration	ETOC Aquatic Hazard Assessment Data 6. I		-

12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
	No Data available for all ingredients	No Data available for all ingredients

12.3. Bioaccumulative potential

Ingredient	Bioaccumulation
	No Data available for all ingredients

12.4. Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

12.5. Results of PBT and vPvB assessment

	Р	В	т
Relevant available data	Not Available	Not Available	Not Available
PBT	×	×	×
vPvB	×	×	×
PBT Criteria fulfilled?			No
vPvB			No

12.6. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

12.7. Other adverse effects

No evidence of ozone depleting properties were found in the current literature.

SECTION 13 Disposal considerations

13.1. Waste treatment methods

Product / Packaging disposal	 Recycle wherever possible. Consult manufacturer for recycling options or consult local or regional waste management authority for disposal if no suitable treatment or disposal facility can be identified. Dispose of by: burial in a land-fill specifically licensed to accept chemical and / or pharmaceutical wastes or Incineration in a licensed apparatus (after admixture with suitable combustible material) Decontaminate empty containers. Observe all label safeguards until containers are cleaned and destroyed.
Waste treatment options	Not Available
Sewage disposal options	Not Available

SECTION 14 Transport information

Labels Required

Marine Pollutant	NO
HAZCHEM	4W

Land transport (ADR-RID)

3078
CERIUM, turnings or gritty powder
Class4.3Subsidiary riskNot Applicable
I
Not Applicable
Hazard identification (Kemler)423Classification codeW2

	Cerium,	chips
--	---------	-------

Hazard Label	4.3
Special provisions	550
Limited quantity	500 g
Tunnel Restriction Code	2 (D/E)

Air transport (ICAO-IATA / DGR)

14.1. UN number	3078			
14.2. UN proper shipping name	Cerium turnings or gritty powder			
14.3. Transport hazard class(es)	ICAO/IATA Class	4.3		
	ICAO / IATA Subrisk	ICAO / IATA Subrisk Not Applicable		
	ERG Code 4W			
14.4. Packing group	П			
14.5. Environmental hazard	Not Applicable			
14.6. Special precautions for user	Special provisions		Not Applicable	
	Cargo Only Packing Instructions		490	
	Cargo Only Maximum Qty / Pack		50 kg	
	Passenger and Cargo Packing Instructions		484	
	Passenger and Cargo Maximum Qty / Pack		15 kg	
	Passenger and Cargo Limited Quantity Packing Instructions		Y475	
	Passenger and Cargo Limited Maximum Qty / Pack		5 kg	

Sea transport (IMDG-Code / GGVSee)

14.1. UN number	3078	
14.2. UN proper shipping name	CERIUM turnings or gritty powder	
14.3. Transport hazard class(es)	IMDG Class 4	4.3
	IMDG Subrisk	Not Applicable
14.4. Packing group	П	
14.5. Environmental hazard	Not Applicable	
	EMS Number	F-G, S-O
14.6. Special precautions for user	Special provisions	Not Applicable
	Limited Quantities	500 g

Inland waterways transport (ADN)

14.1. UN number	3078			
14.2. UN proper shipping name	CERIUM, turnings or gritty powder			
14.3. Transport hazard class(es)	4.3 Not Applicable			
14.4. Packing group	II			
14.5. Environmental hazard	Not Applicable			
14.6. Special precautions for user	Classification code	2		
	Special provisions	50		
	Limited quantity	00 g		
	Equipment required	P, EX, A		
	Fire cones number			

14.7. Maritime transport in bulk according to IMO instruments

14.7.1. Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

14.7.2. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

	Product name	Group
--	--------------	-------

14.7.3. Transport in bulk in accordance with the IGC Code

Product name	Ship Type

SECTION 15 Regulatory information

15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

This safety data sheet is in compliance with the following EU legislation and its adaptations - as far as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; Commission Regulation (EU) 2020/878; Regulation (EC) No 1272/2008 as updated through ATPs.

Information according to 2012/18/EU (Seveso III):

Seveso Category Not Available

15.2. Chemical safety assessment

For further information please look at the Chemical Safety Assessment and Exposure Scenarios prepared by your Supply Chain if available.

ECHA SUMMARY

Not Applicable

National Inventory Status

	-	
National Inventory	Status	
Australia - AIIC / Australia Non-Industrial Use	Not Available	
Canada - DSL	Not Available	
Canada - NDSL	Not Available	
China - IECSC	Not Available	
Europe - EINEC / ELINCS / NLP	Not Available	
Japan - ENCS	Not Available	
Korea - KECI	Not Available	
New Zealand - NZIoC	Not Available	
Philippines - PICCS	Not Available	
USA - TSCA	Not Available	
Taiwan - TCSI	Not Available	
Mexico - INSQ	Not Available	
Vietnam - NCI	Not Available	
Russia - FBEPH	Not Available	
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.	

SECTION 16 Other information

Revision Date	16/09/2022
Initial Date	16/09/2022

Full text Risk and Hazard codes

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch

Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

PC - TWA: Permissible Concentration-Time Weighted Average PC - STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit. IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value I OD. Limit Of Detection OTV: Odour Threshold Value **BCF: BioConcentration Factors** BEI: Biological Exposure Index AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Powered by AuthorITe, from Chemwatch.