

# Tetramethylsuccinic acid Apollo Scientific

Part Number: **OR0747** Version No: **1.2** Safety Data Sheet Chemwatch Hazard Alert Code: 3

Issue Date: **08/06/2023** Print Date: **08/06/2023** S.GHS.GB-NIR.EN

## SECTION 1 Identification of the substance / mixture and of the company / undertaking

#### **Product Identifier**

Product name	Tetramethylsuccinic acid	
Chemical Name	2,2,3,3-Tetramethylsuccinic acid	
Synonyms	ot Available	
Chemical formula	C8H14O4	
Other means of identification	Not Available	
CAS number	630-51-3*	

## Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not
Nelevant lucitineu uses	11017

s Not Available

## Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd	
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road Not Available SK6 2QR United Kingdom (NI)	
Telephone 01614060505		+44(0) 161 406 0505	
Fax 0161 406 0506		Not Available	
Website http://www.apolloscientific.co.uk/		apolloscientific.co.uk	
Email sales@apolloscientific.co.uk		sales@apolloscientific.co.uk	

## Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

## **SECTION 2 Hazards identification**

## Classification of the substance or mixture

Cla	assification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>	H318 - Serious Eye Damage/Eye Irritation Category 1, H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H315 - Skin Corrosion/Irritation Category 2
	Legend:	1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

## Label elements

Hazard pictogram(s)	
Signal word	Danger

## Hazard statement(s)

H318	Causes serious eye damage.	
H335	May cause respiratory irritation.	
H315	Causes skin irritation.	

## Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.	
P280	P280 Wear protective gloves, protective clothing, eye protection and face protection.	
P261	Avoid breathing dust/fumes.	
P264	Wash all exposed external body areas thoroughly after handling.	

## Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P310	Immediately call a POISON CENTER/doctor/physician/first aider.	
P302+P352	IF ON SKIN: Wash with plenty of water.	
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.	
P332+P313	If skin irritation occurs: Get medical advice/attention.	
P362+P364	Take off contaminated clothing and wash it before reuse.	

#### Precautionary statement(s) Storage

P405	Store locked up.	
P403+P233	Store in a well-ventilated place. Keep container tightly closed.	

#### Precautionary statement(s) Disposal

P501 Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

#### **SECTION 3 Composition / information on ingredients**

## Substances

CAS No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
630-51-3*	100	Tetramethylsuccinic acid	Serious Eye Damage/Eye Irritation Category 1, Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, Skin Corrosion/Irritation Category 2; H318, H335, H315 <sup>[1]</sup>	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

#### Mixtures

See section above for composition of Substances

## **SECTION 4 First aid measures**

## Description of first aid measures

Eye Contact

If this product comes in contact with eyes:

- Wash out immediately with water.
  - If irritation continues, seek medical attention.

Page 3 of 11

Tetramethylsuccinic acid

	Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	<ul> <li>If skin or hair contact occurs:</li> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

## Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

## **SECTION 5 Firefighting measures**

#### Extinguishing media

There is no restriction on the type of extinguisher which may be used.

• Use extinguishing media suitable for surrounding area.

#### Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.

## Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> </ul>

## **SECTION 6 Accidental release measures**

#### Personal precautions, protective equipment and emergency procedures

See section 8

#### **Environmental precautions**

See section 12

#### Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid contact with skin and eyes.</li> <li>Wear impervious gloves and safety glasses.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Do NOT use air hoses for cleaning</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	<ul> <li>Clear area of personnel and move upwind.</li> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Control personal contact with the substance, by using protective equipment and dust respirator.</li> <li>Prevent spillage from entering drains, sewers or water courses.</li> <li>Avoid generating dust.</li> <li>Sweep, shovel up. Recover product wherever possible.</li> </ul>

Put residues in labelled plastic bags or other containers for disposal.
If contamination of drains or waterways occurs, advise emergency services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

## **SECTION 7 Handling and storage**

## Precautions for safe handling

Safe handling	<ul> <li>Limit all unnecessary personal contact.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

## Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	Avoid contamination of water, foodstuffs, feed or seed. None known

#### **SECTION 8 Exposure controls / personal protection**

## **Control parameters**

## Occupational Exposure Limits (OEL)

#### INGREDIENT DATA

Not Available

## **Emergency Limits**

Ingredient	TEEL-1	TEEL-2		TEEL-3
Tetramethylsuccinic acid	Not Available	Not Available		Not Available
Ingredient	Original IDLH		Revised IDLH	
Tetramethylsuccinic acid	Not Available		Not Available	

#### Occupational Exposure Banding

Ingredient	Occupational Exposure Band Rating Occupational Exposure Band Limit	
Tetramethylsuccinic acid	E	≤ 0.01 mg/m³
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's	

Ingredient	Occupational Exposure Band Rating	Occupational Exposure Band	Limit		
	potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposur band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.				
xposure controls					
	Engineering controls are used to remove a hazard or place engineering controls can be highly effective in protecting w provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job acti Enclosure and/or isolation of emission source which keeps that strategically "adds" and "removes" air in the work envii designed properly. The design of a ventilation system must Employers may need to use multiple types of controls to pr Local exhaust ventilation is required where solids are h large, a certain proportion will be powdered by mutual f If in spite of local exhaust an adverse concentration of the considered. Such protection might consist of: (a): particle dust respirators, if necessary, combined with a (b): filter respirators with absorption cartridge or canister of (c): fresh-air hoods or masks. Air contaminants generated in the workplace possess vary velocities" of fresh circulating air required to effectively rem	rorkers and will typically be independent o ivity or process is done to reduce the risk. a selected hazard "physically" away from ronment. Ventilation can remove or dilute t match the particular process and chemic revent employee overexposure. handled as powders or crystals; even whe friction. the substance in air could occur, respirato n absorption cartridge; i the right type; ing "escape" velocities which, in turn, deter	f worker interactions to the worker and ventilation an air contaminant if cal or contaminant in use. In particulates are relatively bry protection should be		
Appropriate engineering	Type of Contaminant:		Air Speed:		
controls	direct spray, spray painting in shallow booths, drum filling, conveyer loading, crusher dusts, gas discharge (active generation into zone of rapid air motion)		1-2.5 m/s (200-500 f/min.)		
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial velocity into zone of very high rapid air motion).		2.5-10 m/s (500-2000 f/min.)		
	Within each range the appropriate value depends on:				
	Lower end of the range	Upper end of the range			
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents			
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion	4: Small hood-local control only			
	Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.				
Individual protection measures, such as personal protective equipment					
Eye and face protection	<ul> <li>Safety glasses with side shields</li> <li>Chemical goggles.</li> <li>Contact lenses may pose a special hazard; soft contact document, describing the wearing of lenses or restrictive include a review of lens absorption and adsorption for t Medical and first-aid personnel should be trained in the event of chemical exposure, begin eye irrigation immed be removed at the first signs of eye redness or irritation have washed hands thoroughly. [CDC NIOSH Current</li> </ul>	ons on use, should be created for each we the class of chemicals in use and an acco- ir removal and suitable equipment should diately and remove contact lens as soon a n - lens should be removed in a clean env	orkplace or task. This should unt of injury experience. I be readily available. In the as practicable. Lens should ironment only after workers		
Skin protection	See Hand protection below				
	The selection of suitable gloves does not only depend on the	he material, but also on further marks of c	quality which vary from		
Hands/feet protection	manufacturer to manufacturer. Where the chemical is a pre	eparation of several substances, the resist			

## Hands/feet protection

The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be

can not be calculated in advance and has therefore to be checked prior to the application.

should be wissled and dired thoroughly. Application of a non-perfumed moleculars is second and a second a second and a second and a second a		observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands
Subability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:         - referency and durability of glove material,         - obminal resistance of gloves material,         - down biochass and         - startify         Selecting of gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N25 2161.1 or national equivalent).         - When not biofic ordinal is expected a glove with a protection dass of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N25 2161.10.1 or national equivalent) is recommended.         - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       - Contaminate gloves should be replaced.         - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       - Contaminate gloves with a thickness typically greater than 0.35 mm, are recommended.         - To regrearia applications, gloves with a thickness typically greater than 0.35 mm, are recommended.       It should be emphasized that glove thickness is not necessarily a glove resistance to a specific chemical, as the germation of the construction of the glove with a should always be required where the site and through times.         - To when glove material digradas       - So minutes accound the exact composition of the glove model. Therefore, glove selection the activity be application of the exact approximated.         - It should be emphasized that glove thickness in on necessarily a glove tradeathrough tines.       - C		
<ul> <li>frequency and duration of contact.</li> <li>chemical resistance of glow material,</li> <li>glow thickness and</li> <li>diver thickness and</li> <li>diver thickness and</li> <li>diver thickness and</li> <li>diver thickness and</li> <li>with a protection class of 5 or higher (breakthrough time greater than 240 minuse according to EN 374, ASVES 2161.1 or national equivalent).</li> <li>When only bried contact is expected, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minuse according to EN 374, ASVES 2161.1 or national equivalent) is commended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>K defined in ASTM F739-68 minus applications, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>Is should be emphasized that glove thickness is not necessarily a good predictor of glove resistance. Boy estection should also be based on consideration of the task: requirements and knowledge of the packer digove should be regulated.</li> <li>Note: Depending on the activy boyes mark task above there is a glove model. Therefore, the manufacturers technical data should always be taken into account of the glove material. Therefore, the manufacturers technical data should always be taken into account and would normally be ignown contacted.</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of thereskthrough time site and the task requirements and knowledge o</li></ul>		
<ul> <li>- chemical resistance of glove material,         <ul> <li>- glove hickness and</li> <li>- desterity</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</li> <li>- When proleogid of frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0.1 or national equivalent) is recommended.</li> <li>- Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>- Contaminated gloves should be replaced.</li> <li>- Socie glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>- Contaminated gloves material acquisation (ploves are rated as:</li></ul></li></ul>		
<ul> <li>- glove thickness and</li></ul>		
<ul> <li>. dexiently</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNZS 2161.1 or national equivalent).</li> <li>When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F739-06 in any application, gloves are rated as:         <ul> <li>Scale glove matching time &gt; 420 min</li> <li>Good when breakthrough time &gt; 420 min</li> <li>Good when breakthrough time &gt; 420 min</li> <li>Fair when breakthrough time &gt; 420 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should alway be taken into account depending on the activity being conducted, glows of varying thickness may take dual ways be required that see and knowledge of treakthrough time set as a chemical of the ask. Note: Depending on the activity being conducted, gloves of varying thickness may be required that see and the order of the set as a chemical in sk. Note: Depending on the activity being conducted, gloves of varying thickness may be required that see and the order of the task. Note: Depending on the activity being conducted, gloves are and howledge of treakthrough time set as a chemical in sk. I. Where gloves (pu to 3 mm or more) may be required where there is a mech</li></ul></li></ul>		
<ul> <li>When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.</li> <li>When only brief contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.</li> <li>Some glow ophomer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 400 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Pior when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness to not necessarily a good predictor of glove restraint devices and the should also be based on consideration of the taks requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the exist glove material. Therefore, the manufacturers technical data should always be taken into account to ensure aslection of the glove model. Therefore, the Solve takeness may also vary depending on the activity in kiness may be required where ha high degrade of the most appropriate glove for the task.</li> <li>Note: Depending on the activity depending on the activity in kiness may be exacted for single us application, the glove material destark, for example:</li> <li>Thinter gloves (down to 0.1 mm or less) may be required where ha high degrade of the single dows gloves, hands should be washed and dried thoroughly. Application of a non-perfurned mobstruiser is arcon</li></ul></li></ul>		-
greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • When only brie contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F.739-06 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be be based on consideration of the task requirements and Knowledge of breakthrough times.         Glove thinkness may also vary depending on the glove mandicuture, the glove model. Therefore, glove as (Glove Thickness typically geneter than 0.35 mm, are recommended.         It should be based on consideration of the task requirements and Knowledge of breakthrough times.         Glove thinkness may also vary depending on the glove amolicator of glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove of or the task. Note: Depending on the activity being conducted, gioves of varying thickness way be required there they is a predict dwere were there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential </th <th></th> <th>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</th>		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
<ul> <li>When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 40 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>For when plove material digores is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to emust selection of the most appropriate glove for the task.</li> <li>Note: Depending on the activity being conducted, gloves of varying thickness may be required of vaperific tasks. For example:             <ul> <li>Thinker gloves (up to 3 mm or more) may be required where a high degree of manual deverify is needed. However, these gloves and publicely togies whole that furth protection and would be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual deverify is needed. However, these gloves are not present.</li> <li>byolythoroprene.</li> <li>third in oubber.</li> <li>byolythirdoride.</li> </ul> </li> <li>Body protecti</li></ul></li></ul>		
according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F.739-86 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Bord when breakthrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturer, the glove to the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to glove short duration protection and would normality be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abracion or proterop potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughy. Application of a non-perfumed moisturiser is recommended.         • built rubber.       • buil		
<ul> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Containinated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Ear when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may abse vary depending on the glove manufacture, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required there a high degree of manual destrictly is needd. However, these gloves use on on uncer and or more may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> </ul> </li> <li>Civices inductes that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         <ul> <li>polyhing chindie.</li> <li>Eloy protection</li> <li>See Other protection below</li> </ul> </li> <li>No spec</li></ul>		
Image: end of the second se		
• Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time < 20 min         • Far when breakthrough time < 20 min         • For when glove material degrades         For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted. gloves of varying thickness may be required where a high degree of manual dexterily is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then elsposed of.         • Thicker gloves (µbor to 0.1 nm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         • Obvier some only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommend		
As defined in ASTM F-739-96 in any application, gloves are rated as: <ul><li>Excellent when breakthrough time &gt; 400 min</li><li>Good when breakthrough time &gt; 20 min</li><li>Fair when breakthrough time &gt; 20 min</li><li>Poor when glove material degrades</li><li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.          It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the          permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection          should also be based on consideration of the task requirements and knowledge of breakthrough times.</br></li><li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove most appropriate glove for the task.          Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:          - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these          gloves are only likely to give short duration protection and would normally be use applications, then disposed of.          - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there          is abrasion or puncture potential          Gloves must only be wron on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a          non-perfumed molisturiser is recommended.Body protectionSee Other protection belowBody protectionSee Other protection belowOther protectionNo special equipment needed when handling small quantities.          • Overalls.          • Vorralls.          • Vorralls.          • Vorrall</li></ul>		-
<ul> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glow material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>I should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thinner gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended.</li> </ul> </li> <li>Experience indicates that the following goodymetate as glove materials for protection against undissolved, dry solids, where abrais particles are not present.         <ul> <li>polychloroprene.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.&lt;</li></ul></li></ul>		As defined in ASTM F-739-96 in any application, gloves are rated as:
<ul> <li>Fair when breakthrough time &lt; 20 min         <ul> <li>Poor when glove material degrades</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the tagk workedge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.</li> <li>Note: Depending on the activity being conducted, gloves of varying thickness may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polyviny chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> </li> <li>Body protection</li> <li>See Other protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>Other protection</li> <li>Nos special equipment needed w</li></ul>		Excellent when breakthrough time > 480 min
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the easily being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (duo to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a bracin or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>buyly rubber.</li> <li>buyly nubber.</li> <li>buyly n</li></ul>		<ul> <li>Good when breakthrough time &gt; 20 min</li> </ul>
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove start appropriate glove for the task. 		· Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the glove manufacturer, the glove through times.         Glove thickness may also vary depending on the glove manufacturer, the glove pand the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual daterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychioroprene.</li> <li>nitrile rubber.</li> <li>buyly rubber.</li> <li>fluorocaoutchouc.</li> <li>polychiory choride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> <li>Body protection</li> <li>See Other protection below</li> <li>No special equipment needed when handli</li>		Poor when glove material degrades
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove maturaturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (qom to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • hirtir trubber. • buyly lubber. • buyly cloride. Gloves should be examined for wear and/ or degradation constantly.Body protectionSee Other protection belowOther protectionNo special equipment needed when handling small quantities. OTHERWISE: • Doveralls. • Burrier cream.		For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.
should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glowe manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to 03 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrite rubber. • fluorocaoutchouc. • polycyhlorobrene. • fluorocaoutchouc. • polycyhloride. Gloves should be examined for wear and/ or degradation constantly.Body protectionSee Other protection belowOther protectionNo special equipment needed when handling small quantities. OTHERWISE: • Overalls. • Barrier cream.		
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: 		
Image: Second		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. · polychloroprene. · hitrile rubber. · butyl rubber. · butylense · butyle		
• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         Other protection         Other protection         • Daysell equipment needed when handling small quantities.         • Other states.         • Barrier cream.		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.         * nitrile rubber.         * buyly rubber.         * polychloroprene.         * nitrile rubber.         * buyly rubber.         * buyly rubber.         * buyly rubber.         * buyly rubber.         * polychloroprene.         * nitrile rubber.         * buyly rubber. <t< th=""><th></th><th></th></t<>		
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • nitrile rubber.       • liturocaoutchouc.       • polychloroprene.         • nitrile rubber.       • liturocaoutchouc.       • polychloroprene.         • nitrile rubber.       • liturocaoutchouc.       • polychloroprene.         • not perfumed moisturiser is recommended when handling small quantities.       See Other protection below         Body protection       See Other protection below       No special equipment needed when handling small quantities.         OTHERWISE:       • Overalls.       • Overalls.         • Data is a statistic cream.       • Diveralls.		
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • polychloroprene.       • intrile rubber.       • butyl rubber.         • fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:       • Overalls.         • Doter again.       • Barrier cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.         * nitrile rubber.         * butyl rubber.         * butyl rubber.         * fluorocaoutchouc.         * polychloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         * Overalls.         * Barrier cream.		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.• polychloroprene.• nitrile rubber.• butyl rubber.• fluorocaoutchouc.• polyvinyl chloride.Gloves should be examined for wear and/ or degradation constantly.Body protectionSee Other protection belowNo special equipment needed when handling small quantities.Other protection.• Overalls.• Barrier cream.		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         fluorocaoutchouc.         polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         Other protection         No special equipment needed when handling small quantities.         OTHERWISE:         Overalls.         Barrier cream.		
bit       polychloroprene.         nitrile rubber.       butyl rubber.         butyl rubber.       fluorocaoutchouc.         polycynyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       No special equipment needed when handling small quantities.         OTHERWISE:       • Overalls.         • Barrier cream.       • Barrier cream.		
butyl rubber.       + butyl rubber.       + fluorocaoutchouc.       + polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below       See Other protection below         Other protection       No special equipment needed when handling small quantities.         OTHERWISE:       + Overalls.       + Barrier cream.		
• fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       No special equipment needed when handling small quantities.         Other protection       • Overalls.         • Barrier cream.       • Barrier cream.		▶ nitrile rubber.
Image: Polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Image: Body protection       See Other protection below         Image: Dother protection       No special equipment needed when handling small quantities.         Other protection       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       No special equipment needed when handling small quantities.         Image: Polyvinyl chloride.       Polyvinyl chloride.         Image: Polyvinyl chloride. <td< th=""><th></th><th>▶ butyl rubber.</th></td<>		▶ butyl rubber.
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       No special equipment needed when handling small quantities.         Other protection       • Overalls.         • Barrier cream.       • Barrier cream.		Iluorocaoutchouc.
Body protection       See Other protection below         Other protection       No special equipment needed when handling small quantities.         Other protection       • Overalls.         • Barrier cream.       • Barrier cream.		
Other protection       No special equipment needed when handling small quantities.         OTHERWISE:       • Overalls.         • Barrier cream.		Gloves should be examined for wear and/ or degradation constantly.
Other protection       OTHERWISE:         • Overalls.       • Barrier cream.	Body protection	See Other protection below
Other protection       OTHERWISE:         • Overalls.       • Barrier cream.		No special equipment needed when handling small quantities.
► Barrier cream.		
	Other protection	► Overalls.
t Evowach unit		► Barrier cream.
		Eyewash unit.

#### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to

personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

#### **SECTION 9** Physical and chemical properties

#### Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	204-206	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

#### **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

## **SECTION 11 Toxicological information**

#### Information on toxicological effects

Inhaled

The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control

	measures be used in an occupational setting.	
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.	
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.	
Eye	Although the material is not thought to be an irritant (as classified by EC Directives), direct contact with the eye may cause transient discomfort characterised by tearing or conjunctival redness (as with windburn). Slight abrasive damage may also result.	
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.	

Legend: 1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

	Carcinogenicity	×
Skin Irritation/Corrosion	Reproductivity	×
Serious Eye Damage/Irritation	STOT - Single Exposure	×
Respiratory or Skin sensitisation	STOT - Repeated Exposure	×
Mutagenicity 🗙	Aspiration Hazard	×

Data entrier not available or does not nin the
 Data available to make classification

## **SECTION 12 Ecological information**

## Toxicity

Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity	
	4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) -	
	Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data	

## Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
Tetramethylsuccinic acid	LOW	LOW	

## **Bioaccumulative potential**

Ingredient	Bioaccumulation	
Tetramethylsuccinic acid	LOW (LogKOW = 0.9879)	

## Mobility in soil

Ingredient	Mobility	
Tetramethylsuccinic acid	LOW (KOC = 40.14)	

## **SECTION 13 Disposal considerations**

Waste treatment methods		
Product / Packaging disposa		

## **SECTION 14 Transport information**

## Labels Required

Marine Pollutant NO

## Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

#### Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

#### Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

#### Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

## Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

#### Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group	
Tetramethylsuccinic acid	Not Available	

#### Transport in bulk in accordance with the IGC Code

Product name	Ship Type
Tetramethylsuccinic acid	Not Available

#### **SECTION 15 Regulatory information**

#### Safety, health and environmental regulations / legislation specific for the substance or mixture

Tetramethylsuccinic acid is found on the following regulatory lists

Not Applicable

#### **National Inventory Status**

National Inventory	Status		
Australia - AIIC / Australia Non-Industrial Use	No (Tetramethylsuccinic acid)		
Canada - DSL	No (Tetramethylsuccinic acid)		
Canada - NDSL	No (Tetramethylsuccinic acid)		
China - IECSC	No (Tetramethylsuccinic acid)		
Europe - EINEC / ELINCS / NLP	No (Tetramethylsuccinic acid)		
Japan - ENCS	No (Tetramethylsuccinic acid)		
Korea - KECI	No (Tetramethylsuccinic acid)		
New Zealand - NZIoC	No (Tetramethylsuccinic acid)		
Philippines - PICCS	No (Tetramethylsuccinic acid)		
USA - TSCA	No (Tetramethylsuccinic acid)		
Taiwan - TCSI	No (Tetramethylsuccinic acid)		
Mexico - INSQ	No (Tetramethylsuccinic acid)		
Vietnam - NCI	No (Tetramethylsuccinic acid)		
Russia - FBEPH	No (Tetramethylsuccinic acid)		
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.		

#### **SECTION 16 Other information**

Revision Date	08/06/2023
Initial Date	09/06/2023

## **SDS Version Summary**

Version	Date of Update	Sections Updated
0.2	08/06/2023	Hazards identification - Classification, Composition / information on ingredients - Ingredients, Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms

## Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

- EN 13832 Footwear protecting against chemicals
- EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC - TWA: Permissible Concentration-Time Weighted Average PC - STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit。

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

#### Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Serious Eye Damage/Eye Irritation Category 1, H318	Expert judgement
Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H335	Expert judgement

Telescol	less la sea a		
Tetramet	nyisuco	cinic	acid

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Skin Corrosion/Irritation Category 2, H315	Expert judgement

Powered by AuthorITe, from Chemwatch.