

# **Apollo Scientific**

Part Number: **OR23083** Version No: **1.2** Safety Data Sheet Chemwatch Hazard Alert Code: 2

Issue Date: **26/05/2023** Print Date: **26/05/2023** S.GHS.GB-NIR.EN

### SECTION 1 Identification of the substance / mixture and of the company / undertaking

#### **Product Identifier**

Product name	2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole	
Chemical Name	2,4-Dimethylthiazol-5-yl)methanol	
Synonyms	Not Available	
Other means of identification	Not Available	
CAS number	50382-32-6*	

#### Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
--------------------------	---------------

### Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road Not Available SK6 2QR United Kingdom (NI)
Telephone	01614060505	+44(0) 161 406 0505
Fax	0161 406 0506	Not Available
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk
Email	sales@apolloscientific.co.uk	sales@apolloscientific.co.uk

#### **Emergency telephone number**

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

#### **SECTION 2 Hazards identification**

### Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>	H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2
Legend:	1. Classified by Chernwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

### Label elements

Hazard pictogram(s)	
Signal word	Warning

### Hazard statement(s)

H335	May cause respiratory irritation.	
H315	Causes skin irritation.	
H319	Causes serious eye irritation.	

### Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.
P261	Avoid breathing dust/fumes.
P280	Wear protective gloves, protective clothing, eye protection and face protection.
P264	Wash all exposed external body areas thoroughly after handling.

### Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P312	Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.	
P337+P313	If eye irritation persists: Get medical advice/attention.	
P302+P352	IF ON SKIN: Wash with plenty of water.	
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.	
P332+P313	If skin irritation occurs: Get medical advice/attention.	
P362+P364	Take off contaminated clothing and wash it before reuse.	

#### Precautionary statement(s) Storage

P405	Store locked up.
P403+P233	Store in a well-ventilated place. Keep container tightly closed.

#### Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

### **SECTION 3 Composition / information on ingredients**

### Substances

CAS No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
Not Available	100	2.4-Dimethyl- 5-(hydroxymethyl)- 1,3-thiazole	Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3 , Skin Corrosion/Irritation Category 2, Serious Eye Damage/Eye Irritation Category 2; H335, H315, H319 <sup>[1]</sup>	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

### Mixtures

See section above for composition of Substances

### **SECTION 4 First aid measures**

#### Description of first aid measures

Eye Contact

If this product comes in contact with the eyes: • Wash out immediately with fresh running water.

	<ul> <li>Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids.</li> <li>Seek medical attention without delay; if pain persists or recurs seek medical attention.</li> <li>Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.</li> </ul>
Skin Contact	If skin or hair contact occurs: <ul> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

### Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

#### **SECTION 5 Firefighting measures**

#### **Extinguishing media**

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

#### Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.

### Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> <li>May emit corrosive fumes.</li> </ul>

#### **SECTION 6 Accidental release measures**

### Personal precautions, protective equipment and emergency procedures

See section 8

### **Environmental precautions**

See section 12

### Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid breathing dust and contact with skin and eyes.</li> <li>Wear protective clothing, gloves, safety glasses and dust respirator.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Sweep up, shovel up or</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	Moderate hazard. <ul> <li>CAUTION: Advise personnel in area.</li> <li>Alert Emergency Services and tell them location and nature of hazard.</li> </ul>

<ul> <li>Control personal contact by wearing protective clothing.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Recover product wherever possible.</li> </ul>
<ul> <li>IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.</li> <li>ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.</li> <li>If contamination of drains or waterways occurs, advise Emergency Services.</li> </ul>

Personal Protective Equipment advice is contained in Section 8 of the SDS.

### **SECTION 7 Handling and storage**

### Precautions for safe handling

Safe handling	<ul> <li>Avoid all personal contact, including inhalation.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Prevent concentration in hollows and sumps.</li> <li>DO NOT enter confined spaces until atmosphere has been checked.</li> <li>DO NOT allow material to contact humans, exposed food or food utensils.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately. Launder contaminated clothing before re-use.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

### Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	None known

### **SECTION 8 Exposure controls / personal protection**

### **Control parameters**

### Occupational Exposure Limits (OEL)

### INGREDIENT DATA

Not Available

#### Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
2,4-Dimethyl- 5-(hydroxymethyl)- 1,3-thiazole	Not Available	Not Available	Not Available

2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole			Print Date: 26/05/2
Ingredient	Original IDLH	Revised IDLH	
2,4-Dimethyl- 5-(hydroxymethyl)- 1,3-thiazole	Not Available	Not Available	
Exposure controls			
	<ul> <li>engineering controls can be highly effective in p provide this high level of protection.</li> <li>The basic types of engineering controls are:</li> <li>Process controls which involve changing the water that strategically "adds" and "removes" air in the designed properly. The design of a ventilation strateging properly. The design of a ventilation strateging, a certain proportion will be powdered</li> <li>If in spite of local exhaust an adverse concerconsidered.</li> <li>Such protection might consist of:</li> <li>(a): particle dust respirators, if necessary, comb (b): filter respirators with absorption cartridge of (c): fresh-air hoods or masks.</li> </ul>	solids are handled as powders or crystals; even whe by mutual friction. entration of the substance in air could occur, respirato ined with an absorption cartridge; canister of the right type; bssess varying "escape" velocities which, in turn, det	f worker interactions to the worker and ventilation an air contaminant if cal or contaminant in use. n particulates are relatively ory protection should be
Appropriate engineerin	g Type of Contaminant:		Air Speed:
control	direct spray, spray painting in shallow booths, discharge (active generation into zone of rapid	drum filling, conveyer loading, crusher dusts, gas I air motion)	1-2.5 m/s (200-500 f/min.)
	grinding, abrasive blasting, tumbling, high spe velocity into zone of very high rapid air motion	ed wheel generated dusts (released at high initial	2.5-10 m/s (500-2000 f/min.)

Lower end of the range	Upper end of the range
1: Room air currents minimal or favourable to capture	1: Disturbing room air currents
2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity
3: Intermittent, low production.	3: High production, heavy use
4: Large hood or large air mass in motion	4: Small hood-local control only

Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.

Individual protection measures, such as personal protective equipment	
Eye and face protection	<ul> <li>Safety glasses with side shields.</li> <li>Chemical goggles.</li> <li>Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent]</li> </ul>
Skin protection	See Hand protection below
Hands/feet protection	The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.

In the back intrody in the 3 databances into the to be doubled into the introducture to the product goines goines and into the original set of the second		The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be
Presonal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. Marr using gloves, hands should be washed and dried throughly. Application of a non-perfurme metaturise ir recommended.         Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves induce: <ul> <li>dreguency and durability of glove type is dependent on usage. Important factors in the selection of gloves induce:             <li>dreguency and durability of glove type is dependent on usage. Important factors in the selection of gloves induce:             <li>dreguency and durability of glove type is dependent on usage. Important factors in the selection of gloves induce:             <li>dreguency and durability of gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNZS 2161.1 or national equivalent).</li> <li>When prolonged or frequently repeated contact may accur, a glove with a protection class of 5 or higher (breakthrough time greater than 20 minutes according to EN 374, ASNZS 2161.1.01 or national equivalent).</li> <li>When only bried contact is expected.</li> <li>Some glove polymer types are lease affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:                  <li>Excellant when breakthrough time &lt; 20 min</li> <li>Grow thore breakthrough time &lt; 20 min</li> <li>Grow thore breakthrough time &lt; 20 min</li> <li>Fair when threakthrough time &lt; 20 min</li> <li>Grow thore breakthrough time &lt; 20 min</li> <li>Grow thore breakthrough time &lt; 20 min</li> <li>Grow thore breakthrough time &lt; 20 min</li> <li>Foriw when preakending on the glove material degreades&lt;</li></li></li></li></li></ul>		
should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         subability and duration of contact.         - frequency and duration of contact.         - gives thickness and         - destrict resistance of give material,         - gives thickness and         - destrict resistance of fore material,         - gives thickness and         - destrict resistance of fore material,         - gives thickness and         - destrict resistance of fore material,         - gives thickness and         - destrict resistance of fore material,         - When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN22 S161:1.0 or national equivalent);         - When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time scording to EN 374, ASN22 S161:1.0 or national equivalent);         - Contaminated gloves should be replaced.         - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         - Contaminated gloves should be replaced.         - Contaminated gloves should be replaced.         - Contaminated gloves should be replaced.         - Far when preakthrough time < 20 min         - Good when breakthrough time < 20 min         - Far when preakthrough time < 20 min     <		
Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: <ul> <li>chemical resistance of glove material,</li> <li>glove thickness and</li> <li>doubtility</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</li> <li>When prolonged or frequenty repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0 or national equivalent).</li> <li>When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0 or national equivalent).</li> <li>When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for lang-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Eacelient when breakthrough time &lt; 20 min</li> <li>Fair when breakthrough time &lt; 20 min</li> <li>Food when gloves and on consideration of the task, represent than 0.35 m, are recommended.</li> <li>Food when glove and on consideration of the task (supplications glove for the task. Note: Depending on the activity baing conducted, gloves of varying thickness may abo varying thickness may abo varying thickness may be required when the resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the most appropriate glove for the task. Note: Depending on the achival baing conduc</li></ul></li></ul>		
<ul> <li>Inequency and duration of contact.</li> <li>Inequency and duration of contact.</li> <li>glove thickness and</li> <li>dwatchy</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</li> <li>When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZ 2161.1 or national equivalent) is recommended.</li> <li>When only brief contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZ 2161.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTH F733-96 in may application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 400 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the glove material. Breafore, glove selection should aloo be based on consideration of the task requirements and knowledge of breakthrough time.</li> <li>Thinker gloves (kom to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a schenical (as well as a chemical) risk i.e. where there is a schenical (as well as a chemical) risk i.e. where there is a schenical (as well as a chemical) risk i.e. where there is a schenical (as well as a chemical) risk i.e. where there is a schenical (as well as a</li></ul>		
<ul> <li>chemical resistance of glove material, - glove Thickness and - deaterity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASAZS 2161.1 or national equivalent), - When prolonged of frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent), When only bird contact is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for torg-term use. - Contaminated gloves should be replaced. As defined in ASTM F-739-6in any application, gloves are rated as: - Streellent when breakthrough time &gt; 20 min - Fair when breakthrough time &gt; 20 min - Thicker glo</li></ul>		
<ul> <li>glove hickness and 'edentify' Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASAZS 2161.1 or national equivalent).</li> <li>When protonged or frequently repeated contact may occur, a glove with a protection class of S or higher (breakthrough time greater than 240 innues according to EN 374, ASAZS 2161.1 or national equivalent) is recommended.</li> <li>When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 innues according to EN 374, ASNZS 2161.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>For when glove material degrades</li> <li>For yeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor by glove and the glove glove glove extention.</li> <li>Glove thickness may also vary depending on the faxe requirements and knowledge of breakthrough times, glove shot duration or the xaxt composition of the glove material. Therefore, the manufactures relevanical distaves be taken into account when cosplicit catakes, For example: Thinner gloves (to to 3 mm or relevant) being conducted, gloves of varying thickness must also the task. Note: Depending on the activity being conducted, gloves and nativity being degraded when breakthrough time glove the task. Note: Sepending on the activity being conducted, gloves and nativity being degraded by movement and knowledge of breakthrough time, second gloves are analy likely to glove shord duration protection and would normality be just doct duratit</li></ul>		
<ul> <li>- desterity</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F738, ASAZS 2161.1 or national equivalent).</li> <li>- Vhen protoingd or frequently repeated contact may occur, a glove with a protection class of \$ or higher (breakthrough time greater than 240 minutes according to EN 374, ASAZS 2161.10.1 or national equivalent) is recommended.</li> <li>- Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>- Contaminated gloves should be replaced.</li> <li>- Scellent when breakthrough time &gt; 20 min</li> <li>- Fair when breakthrough time &lt; 20 min</li> <li>- Sore glove polyce will be dependent on the exac composition of the glove matchall. Therefore, glove selection should also be based on consideration on the tax caccord or barse stepsized of specific chemical, as the manufacturers technical data should always be taken into account to ensure selection of the mask should be washed and the spore the task. Note: Depending on the gloveos of vanjing thickness may be required for specific tasks. Fo</li></ul>		-
Select gives tested to a relevant standard (e.g. Europe EN 374, US F730, ASN25 2161.1 or rational equivalent).         • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10.1 or rational equivalent) is recommended.         • When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN25 2161.10.1 or rational equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm use.         • Contaminated gloves should be replaced.         As defined in ASTM F739.99 elitations, gloves are rated as:         • Excellent when breakthrough time > 400 min         • Good when breakthrough time > 20 min         • For oreneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove with a dipoteness in on necessarily a good predictor of glove resistance to a specific chemical, as the manufacturers technical data should always be taken into account or ensure selection of the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required where here is a mechanical (as well as a chemical) risk i.e. where there is a fore analyzer with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         It should be abased on c		
• When in prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.         • When only brief contact is supected, a glow with a protection class of 5 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended.         • Some glow polymor types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated glowes should be replaced.         As defined in ASTM F730-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 400 min         • Good when breakthrough time > 400 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Foor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove for the task.         Note: Depending on the activity being conducter gloves are only likely to give soft the glove series and the manufacturer, the glove for the task.         Note: Depending on the activity depending on the activity give short the glove material activity is needed. However, these gloves are only likely to give short duaration protection and would normally be just		
greater than 240 minutes according to EN 374, ASIN2S 2161.10.1 or national equivalent) is recommended.         • When only brie contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASIN2S 2161.10.1 or national equivalent) is recommended.         • Seme glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Gord when breakthrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a bould alveys be taken into account to ensure healthrough time.         Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should alveys be taken into account to ensure selection of the most appropriate glove to the take.         • Other protection       0.4 mm resets that differe alve quirements and knowledge of branule desterity is needed. However, these gloves must only likely to give should normally be just for single use appropriate glove the take. Note: Depending on the activity being conducted, gloves of varying thickness may also vary depending on the activity demend and diverter heart estametand account th		
<ul> <li>When only brief contact is expected, a glove with a protection class of 20 rhigher (treakthrough time greater than 60 minutes according to EN 374, ASNIZS 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 40 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>For when gloves stored grades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove multi be dependent on the exact composition of the glove motel. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensus eslection of the most appropriate glove for the task.</li> <li>Note: Depending on the active being on the glove where a high degree of manual dexterity is needed. However, these gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves for during or placetter of polymers rae suitable as glove materials for protection against undissolved, dry solids, where abrais or puncture potential</li> <li>Gloves mixer on clean hands. After using gloves, hands should be washed and ried thoroughly. Application of a non-perfurmed moisturiser is recommended.</li> <li>Experience indicates that t</li></ul>		
according to EN 374, ASINZS 2161.10. or national equivalent) is recommended.         Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         Excellent when breakthrough time > 20 min         Fair when breakthrough time > 20 min         Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove typical the activity being conduced, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, glove the task. Note: Depending on the activity being conduced, gloves, hands should a brea should always there there is a mechanical (as well as a chemical) risk i.e. where there is abarision or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moistu		greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       • Contaminated gloves should be replaced.         • As defined in ASTM F-739-96 in any application, gloves are rated as:       • Excellent when breakthrough time > 20 min         • Good when breakthrough time > 20 min       • Excellent when breakthrough time > 20 min         • Poor when glove material degrades       • Poor when glove material degrades         • Poor when glove material degrades       • Gootaminated gloves should be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove bye and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required tor specific tasks. For example:         • Thinker gloves (down to 1.1 mm or less) may be required where a high degree of manual detartify is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, the discound movel on the requirementer is a demical) risk i.e. where there is abrasion or puncture potential         Glove stucknow       • Thinker gloves (down to 1.1 mm or less) may be required where a high degree of manual detartify is needed. However, these gloves end the gloves is a chemical) risk i.e. where there is abrasion or puncture potential <td< th=""><th></th><th>· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes</th></td<>		· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
Iong-term use.       Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       Excellent when breakthrough time > 400 min         Good when breakthrough time > 20 min       Fair when breakthrough time > 20 min         Poor when glove material degrades       For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove should a the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufactures technical data should always be taken into account to ensure selection of the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required there should also required where there is a mechanical (as well as a chemical) fisk i.e. where there is abrasion or puncture potential         Glove serue only likely to give short duration protection and would normally be just for single use applications, the disposed of.         Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) fisk i.e. where there is abrasion or puncture potential         Glove struct only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.		according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time < 20 min         • Good when breakthrough time < 20 min         • Fair When breakthrough time < 20 min         • Bood when breakthrough time < 20 min         • Fair When breakthrough time < 20 min         • Bood when breakthrough time < 100 min the casts composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most tappropriate glove for the task. Tor example:         • Thinker gloves (dow to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential.         Gloves must only be worn on cleen hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed motis		· Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for
As defined in ASTM F-739-96 in any application, gloves are rated as:       Excellent when breakthrough time > 400 min         Good when breakthrough time > 20 min       - Fair when breakthrough time > 20 min         - Poor when glove material degrades       For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mile dependent on the exact composition of the glove maderial. Therefore, the manufactures technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasion or pulce the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.       * initie rubber.       * polychloroprene.         * hurdies are ont present.       * polychloroprene.       * initie rubber.         * polychloroprene.       * hurdies are not present.       * polychloroprene.         * hurdies are not present.       * polychloroprene.       * hurdies are not or degradation constantly.         Body protection       See Other protection below       * Overalls.         * polychloroprene.       * hurdies are not present.		long-term use.
<ul> <li>Excellent when breakthrough time &gt; 480 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove or manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the gloves of varying thickness may be required to respective there is a mechanical (as well as a chemical) risk i.e. where there is a breasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should alw and should always be taken under shiph degree of manufacturer, the manufacturer is the there is a breasion or puncture potential.</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychoroprene.</li> <li>hintir turber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychoroprene.</li> <li>hintir turber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl ru</li></ul>		Contaminated gloves should be replaced.
<ul> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required of the spectre will be dependent on and would normally be just for single use applications, then disposed of.</li> <li>Thinker gloves (Jup to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (Up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>Polychloroprene.</li> <li>Hirting tubber.</li> <li>Hitting tubber.</li> <li>Horigr tubber.</li> <li>Horigr t</li></ul>		As defined in ASTM F-739-96 in any application, gloves are rated as:
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thickner gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. + polychioroprene. + hitrie rubber.</li> <li>buyly rubber.</li> <li< th=""><th></th><th>Excellent when breakthrough time &gt; 480 min</th></li<></ul>		Excellent when breakthrough time > 480 min
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove of the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:</li></ul>		Good when breakthrough time > 20 min
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required to respecific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         • Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • hitrile rubber.       • buty rubber.       • buty rubber.         • buty rubber.       • buty rubber.       • buty rubber.         • looveralls.		Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the task requirements and knowledge of breakthrough times. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraion or puncture potential Gloves sure only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves use to 10 be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present. > polychloroprene. > hittile tubber. > holy rubber. > holy		Poor when glove material degrades
Permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves guo to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiers is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychiloroprene. • jolychiloroprene. • jolychiloroprene. 		For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.
should also be based on consideration of the task requirements and knowledge of breakthrough times.       Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • buly rubber.       • buly rubber.         • buly rubber.       • fluorocaoutchouc.         • polychloroprene.       • fluorocaoutchouc.         • buly rubber.       • fluorocaoutchouc.         • buly rubber.       • fluorocaoutchouc.         • polychloroprene.       • fluorocaoutchouc.         • polychloroprene.       • fluorocaoutchouc.         • buly rubber.       • fluorocaoutchouc. <t< th=""><th></th><th>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the</th></t<>		It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. bolychloroprene. intrile rubber. buly rubber. 		permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. bolychloroprene. intrile rubber. buly rubber. 		
Imanufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. 		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>&gt; polychloroprene.</li> <li>&gt; hitrile rubber.</li> <li>&gt; buty! rubber.</li> <li>&gt; buty: rubber.</li> <li>&gt; buty: rubber.</li></ul>		manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.
<ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection See Other protection below Other protection Cher protection Skin cleansing cream. Skin cleansing cream.		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • bolyvinyl choride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.       • Skin cleansing cream.		
<ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychloroprene.</li> <li>fluorocaoutchouc.</li> <li>polychloroprene.</li> <li>See Other protection below</li> </ul>		
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • nitrile rubber.       • butyl rubber.       • fluorocaoutchouc.         • polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • P.V.C apron.         • Barrier cream.       • Skin cleansing cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. 		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         fluorocaoutchouc.         polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below            • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
• polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
• nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
• butyl rubber.       • fluorocaoutchouc.       • polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       • Overalls.       • P.V.C apron.         • Barrier cream.       • Skin cleansing cream.		
Image:		
• polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection.       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>Overalls.</li> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> <li>Skin cleansing cream.</li> </ul>		
Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		
Other protection <ul> <li>Overalls.</li> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>	Body protection	See Other protection below
Other protection       • Barrier cream.         • Skin cleansing cream.		► Overalls.
► Skin cleansing cream.		► P.V.C apron.
	Other protection	► Barrier cream.
		Skin cleansing cream.
		► Eye wash unit.
		•

#### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

. The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data,

Part Number: OR23083 Version No: 1.2

#### 2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole

and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

• Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

• Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

 $\cdot$  Try to avoid creating dust conditions.

#### **SECTION 9 Physical and chemical properties**

#### Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	56-57	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

#### **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

### **SECTION 11 Toxicological information**

#### Information on toxicological effects

Inhaled The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives

	using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.	
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.	
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.	
Eye	This material can cause eye irritation and damage in some persons.	
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.	

 
 Legend:
 1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	✓	STOT - Single Exposure	✓
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
	Le	gend: 🗙 – Data either not ava	ailable or does not fill the criteria for classification

Data entrier not available of does not init the cr
 — Data available to make classification

### **SECTION 12 Ecological information**

### Toxicity

Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity
	4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) -
	Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

### Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
	No Data available for all ingredients	No Data available for all ingredients	

### **Bioaccumulative potential**

Ingredient	Bioaccumulation
	No Data available for all ingredients

### Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

#### **SECTION 13 Disposal considerations**

Waste treatment methods		
Product / Packagin dispos		

### **SECTION 14 Transport information**

### Labels Required

Marine Pollutant NO

### Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

#### Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
2,4-Dimethyl- 5-(hydroxymethyl)- 1,3-thiazole	Not Available

#### Transport in bulk in accordance with the IGC Code

Product name	Ship Type
2,4-Dimethyl- 5-(hydroxymethyl)- 1,3-thiazole	Not Available

#### **SECTION 15 Regulatory information**

### Safety, health and environmental regulations / legislation specific for the substance or mixture

#### **National Inventory Status**

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Canada - DSL	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Canada - NDSL	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
China - IECSC	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Europe - EINEC / ELINCS / NLP	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Japan - ENCS	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Korea - KECI	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
New Zealand - NZIoC	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Philippines - PICCS	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
USA - TSCA	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Taiwan - TCSI	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Mexico - INSQ	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Vietnam - NCI	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Russia - FBEPH	No (2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole)
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

#### **SECTION 16 Other information**

Revision Date	26/05/2023
Initial Date	26/05/2023

### **SDS Version Summary**

Version	Date of Update	Sections Updated
0.2	26/05/2023	Physical and chemical properties - Appearance, Hazards identification - Classification, Composition / information on ingredients - Ingredients, Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms

### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

- EN 13832 Footwear protecting against chemicals
- EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC-TWA: Permissible Concentration-Time Weighted Average PC-STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit<sub>o</sub> IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

#### Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H335	Expert judgement
Skin Corrosion/Irritation Category 2, H315	Expert judgement

### Issue Date: 26/05/2023 Print Date: 26/05/2023

# 2,4-Dimethyl-5-(hydroxymethyl)-1,3-thiazole

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement

Powered by AuthorITe, from Chemwatch.