

4-Bromonicotinaldehyde Apollo Scientific

Part Number: **OR3273** Version No: **2.2** Safety Data Sheet Chemwatch Hazard Alert Code: 0

Issue Date: **07/07/2023** Print Date: **07/07/2023** S.GHS.GB-NIR.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

Product Identifier

Product name	4-Bromonicotinaldehyde
Chemical Name	4-bromopyridine-3-carbaldehyde
Synonyms	Not Available
Other means of identification	Not Available
CAS number	154105-64-3*

Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
Relevant identified uses	Not Available

Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road, Bredbury Cheshire SK6 2QR United Kingdom (NI)
Telephone	01614060505	+44(0) 161 406 0505
Fax	0161 406 0506	Not Available
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk
Email	sales@apolloscientific.co.uk	sales@apolloscientific.co.uk

Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

SECTION 2 Hazards identification

Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments ^[1]

Not Applicable

Label elements

Hazard pictogram(s)	Not Applicable
Signal word	Not Applicable

Hazard statement(s)

Not Applicable

Precautionary statement(s) Prevention

Not Applicable

Precautionary statement(s) Response

Not Applicable

Precautionary statement(s) Storage

Not Applicable

Precautionary statement(s) Disposal

Not Applicable

SECTION 3 Composition / information on ingredients

Substances

CAS No		%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
Legend:	Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties				L; * EU IOELVs

Mixtures

See section above for composition of Substances

SECTION 4 First aid measures

Description of first aid measures

Eye Contact	 If this product comes in contact with eyes: Wash out immediately with water. If irritation continues, seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	 If skin or hair contact occurs: Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.
----------------------	-------------

Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves in the event of a fire. Prevent, by any means available, spillage from entering drains or water courses. Use fire fighting procedures suitable for surrounding area. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 Non combustible. Not considered a significant fire risk, however containers may burn.

SECTION 6 Accidental release measures

Personal precautions, protective equipment and emergency procedures

See section 8

Environmental precautions

See section 12

Methods and material for containment and cleaning up

Minor Spills	 Clean up all spills immediately. Avoid contact with skin and eyes. Wear impervious gloves and safety glasses. Use dry clean up procedures and avoid generating dust. Vacuum up (consider explosion-proof machines designed to be grounded during storage and use). Do NOT use air hoses for cleaning Place spilled material in clean, dry, sealable, labelled container.
Major Spills	 Clear area of personnel and move upwind. Alert Fire Brigade and tell them location and nature of hazard. Control personal contact with the substance, by using protective equipment and dust respirator. Prevent spillage from entering drains, sewers or water courses. Avoid generating dust. Sweep, shovel up. Recover product wherever possible. Put residues in labelled plastic bags or other containers for disposal. If contamination of drains or waterways occurs, advise emergency services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

Precautions for safe handling

Safe handling	 Limit all unnecessary personal contact. Wear protective clothing when risk of exposure occurs. Use in a well-ventilated area. Avoid contact with incompatible materials. When handling, DO NOT eat, drink or smoke. Keep containers securely sealed when not in use. Avoid physical damage to containers. Always wash hands with soap and water after handling. Work clothes should be laundered separately. Use good occupational work practice. Observe manufacturer's storage and handling recommendations contained within this SDS. Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.
Other information	 Store in original containers. Keep containers securely sealed. Store in a cool, dry area protected from environmental extremes. Store away from incompatible materials and foodstuff containers.

 Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS. For major quantities: Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams). Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may reconsultation with local authorities. 	equire
---	--------

Conditions for safe storage, including any incompatibilities

Suitable container	 Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	Avoid contamination of water, foodstuffs, feed or seed. None known ▶ Store at 2-8°C

SECTION 8 Exposure controls / personal protection

Control parameters

Occupational Exposure Limits (OEL)

INGREDIENT DATA

Not Available

Emergency Limits

Ingredient	TEEL-1	TEEL-2		TEEL-3
4-Bromonicotinaldehyde	Not Available	Not Available		Not Available
Ingredient	Original IDLH		Revised IDLH	
4-Bromonicotinaldehyde	Not Available		Not Available	

Exposure controls

	Engineering controls are used to remove a hazard of				
	engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection.				
	The basic types of engineering controls are:				
	Process controls which involve changing the way a	job activity or process is done to reduce the risk.			
	Enclosure and/or isolation of emission source which				
	that strategically "adds" and "removes" air in the wo				
	designed properly. The design of a ventilation syste Employers may need to use multiple types of contro		al or contaminant in use.		
	Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction.				
	If in spite of local exhaust an adverse concentration of the substance in air could occur, respiratory protection should be considered.				
Appropriate engineering	Such protection might consist of:				
controls	(a): particle dust respirators, if necessary, combined with an absorption cartridge;				
	(b): filter respirators with absorption cartridge or canister of the right type;				
	(c): fresh-air hoods or masks. Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture				
	velocities" of fresh circulating air required to effectively remove the contaminant.				
	Type of Contaminant:		Air Speed:		
	direct spray, spray painting in shallow booths, drur discharge (active generation into zone of rapid air	1-2.5 m/s (200-500 f/min.)			
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial velocity into zone of very high rapid air motion).		2.5-10 m/s (500-2000 f/min.)		
	Within each range the appropriate value depends on:				
	Lower end of the range Upper end of the range				

	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents			
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity			
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion	4: Small hood-local control only			
	Simple theory shows that air velocity falls rapidly with dista				
	generally decreases with the square of distance from the e extraction point should be adjusted, accordingly, after refer		-		
	extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velo extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated				
	distant from the extraction point. Other mechanical conside				
	apparatus, make it essential that theoretical air velocities a installed or used.	ire multiplied by factors of 10 or m	ore when extraction systems are		
Individual protection measures, such as					
personal protective equipment					
	Safety glasses with side shields				
	 Chemical goggles. [AS/NZS 1337.1, EN166 or national 	l equivalent]			
	Contact lenses may pose a special hazard; soft contact	t lenses may absorb and concentr	ate irritants. A written policy		
Fire and free masterian	document, describing the wearing of lenses or restriction		•		
Eye and face protection	include a review of lens absorption and adsorption for the Medical and first-aid personnel should be trained in the				
	event of chemical exposure, begin eye irrigation immed		-		
	be removed at the first signs of eye redness or irritation		an environment only after workers		
	have washed hands thoroughly. [CDC NIOSH Current	Intelligence Bulletin 59].			
Skin protection	See Hand protection below				
	The selection of suitable gloves does not only depend on t	he material, but also on further ma	irks of quality which vary from		
	The selection of suitable gloves does not only depend on t manufacturer to manufacturer. Where the chemical is a pre-				
	manufacturer to manufacturer. Where the chemical is a pre can not be calculated in advance and has therefore to be o	eparation of several substances, th checked prior to the application.	e resistance of the glove material		
	manufacturer to manufacturer. Where the chemical is a pre can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obt	eparation of several substances, th checked prior to the application.	e resistance of the glove material		
	manufacturer to manufacturer. Where the chemical is a pre- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obto observed when making a final choice.	eparation of several substances, the checked prior to the application. cained from the manufacturer of the checked prior the manufacturer of the checked prior the manufacturer of the checked prior the checked	e resistance of the glove material		
	manufacturer to manufacturer. Where the chemical is a pre can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obt	eparation of several substances, the checked prior to the application. ained from the manufacturer of the Gloves must only be worn on clean	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands		
	manufacturer to manufacturer. Where the chemical is a pre- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obto observed when making a final choice. Personal hygiene is a key element of effective hand care. should be washed and dried thoroughly. Application of a ne Suitability and durability of glove type is dependent on usa	eparation of several substances, the checked prior to the application. ained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomm	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended.		
	manufacturer to manufacturer. Where the chemical is a pre- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obto observed when making a final choice. Personal hygiene is a key element of effective hand care. Is should be washed and dried thoroughly. Application of a ne Suitability and durability of glove type is dependent on usa • frequency and duration of contact,	eparation of several substances, the checked prior to the application. ained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomm	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended.		
	manufacturer to manufacturer. Where the chemical is a pre- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obto observed when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a ne Suitability and durability of glove type is dependent on usa • frequency and duration of contact, • chemical resistance of glove material,	eparation of several substances, the checked prior to the application. ained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomm	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended.		
	manufacturer to manufacturer. Where the chemical is a pre- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be obto observed when making a final choice. Personal hygiene is a key element of effective hand care. Is should be washed and dried thoroughly. Application of a ne Suitability and durability of glove type is dependent on usa • frequency and duration of contact,	eparation of several substances, the checked prior to the application. ained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomm	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended.		
	manufacturer to manufacturer. Where the chemical is a pro- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be oblo- observed when making a final choice. Personal hygiene is a key element of effective hand care. Is should be washed and dried thoroughly. Application of a no Suitability and durability of glove type is dependent on usa · frequency and duration of contact, · chemical resistance of glove material, · glove thickness and · dexterity Select gloves tested to a relevant standard (e.g. Europe E	eparation of several substances, the checked prior to the application. aned from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomr ge. Important factors in the selection N 374, US F739, AS/NZS 2161.1 of	ne resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands mended. on of gloves include:		
	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtoobserved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a model of the substance of glove type is dependent on usa frequency and durability of glove type is dependent on usa frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Element of the substance of the substance	eparation of several substances, the checked prior to the application. cained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection N 374, US F739, AS/NZS 2161.1 of ur, a glove with a protection class of	the resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands mended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time		
	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtoobserved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a nuscliability and durability of glove type is dependent on usa frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Element on the prolonged or frequently repeated contact may occur greater than 240 minutes according to EN 374, AS/NZS 24 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection N 374, US F739, AS/NZS 2161.1 of ur, a glove with a protection class of 161.10.1 or national equivalent) is	the resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands mended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended.		
	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtoobserved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a model of the substance of glove type is dependent on usa frequency and durability of glove type is dependent on usa frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Element of the substance of the substance	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr	the resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands mended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended.		
	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtored when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a nustrability and durability of glove type is dependent on usa frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Element on usa care than 240 minutes according to EN 374, AS/NZS 216.1.10.1 or national equival. Some glove polymer types are less affected by movement of the standard by move	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended.	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
	manufacturer to manufacturer. Where the chemical is a pro- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be oblo- observed when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a no- Suitability and durability of glove type is dependent on usa · frequency and duration of contact, · chemical resistance of glove material, · glove thickness and · dexterity Select gloves tested to a relevant standard (e.g. Europe El · When prolonged or frequently repeated contact may occu greater than 240 minutes according to EN 374, AS/NZS 21 · When only brief contact is expected, a glove with a protect according to EN 374, AS/NZS 2161.10.1 or national equiva · Some glove polymer types are less affected by movemer long-term use.	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended.	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtored when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a nust stability and durability of glove type is dependent on usa frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Elevant than 240 minutes according to EN 374, AS/NZS 21 When only brief contact is expected, a glove with a protect according to EN 374, AS/NZS 2161.10.1 or national equival. Some glove polymer types are less affected by movemer long-term use. Contaminated gloves should be replaced. 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into acc	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
Hands/feet protection	manufacturer to manufacturer. Where the chemical is a pro- can not be calculated in advance and has therefore to be of The exact break through time for substances has to be oblo- observed when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a no- Suitability and durability of glove type is dependent on usa · frequency and duration of contact, · chemical resistance of glove material, · glove thickness and · dexterity Select gloves tested to a relevant standard (e.g. Europe El · When prolonged or frequently repeated contact may occu greater than 240 minutes according to EN 374, AS/NZS 21 · When only brief contact is expected, a glove with a protect according to EN 374, AS/NZS 2161.10.1 or national equiva · Some glove polymer types are less affected by movemer long-term use.	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into acc	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
Hands/feet protection	 manufacturer to manufacturer. Where the chemical is a process of the calculated in advance and has therefore to be of the exact break through time for substances has to be obtored when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a new suitability and durability of glove type is dependent on usa if frequency and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Element on usa care than 240 minutes according to EN 374, AS/NZS 21 When only brief contact is expected, a glove with a protect according to EN 374, AS/NZS 2161.10.1 or national equivale. Some glove polymer types are less affected by movement long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves and 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into acc	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
Hands/feet protection	 manufacturer to manufacturer. Where the chemical is a process of the exact break through time for substances has to be obterved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Effection of the prolonged or frequently repeated contact may occur greater than 240 minutes according to EN 374, AS/NZS 216.1.10.1 or national equivaleties of the prolonget or types are less affected by movemer long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are is Excellent when breakthrough time > 20 min Fair when breakthrough time < 20 min 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the selection ge. Important factors in the selection ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into acc	e resistance of the glove material e protective gloves and has to be n hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes		
Hands/feet protection	 manufacturer to manufacturer. Where the chemical is a process of the exact break through time for substances has to be obterved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Effection of the prolonged or frequently repeated contact may occur greater than 240 minutes according to EN 374, AS/NZS 216.1.10.1 or national equivaleties of the prolonged or types are less affected by movemer long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are is Excellent when breakthrough time > 480 min Good when breakthrough time < 20 min Fair when breakthrough time < 20 min Poor when glove material degrades 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the select and a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into acc e rated as:	he resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands mended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes count when considering gloves for		
Hands/feet protection	 manufacturer to manufacturer. Where the chemical is a process of the exact break through time for substances has to be obterved when making a final choice. Personal hygiene is a key element of effective hand care. If should be washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and dried thoroughly. Application of a model of the washed and duration of contact, chemical resistance of glove material, glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe Effection of the prolonged or frequently repeated contact may occur greater than 240 minutes according to EN 374, AS/NZS 216.1.10.1 or national equivaleties of the prolonget or types are less affected by movemer long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are is Excellent when breakthrough time > 20 min Fair when breakthrough time < 20 min 	eparation of several substances, the checked prior to the application. trained from the manufacturer of the Gloves must only be worn on clear on-perfumed moisturiser is recomminge. Important factors in the select N 374, US F739, AS/NZS 2161.1 of ur, a glove with a protection class of 161.10.1 or national equivalent) is ction class of 3 or higher (breakthr alent) is recommended. Int and this should be taken into accur e rated as:	ne resistance of the glove material e protective gloves and has to be in hands. After using gloves, hands nended. on of gloves include: or national equivalent). of 5 or higher (breakthrough time recommended. ough time greater than 60 minutes count when considering gloves for		

permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.

Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there

is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a

non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.

polychloroprene.

nitrile rubber.

	 butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly.
Body protection	See Other protection below
Other protection	No special equipment needed when handling small quantities. OTHERWISE: • Overalls. • Barrier cream. • Eyewash unit.

Respiratory protection

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

• Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

• Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

SECTION 9 Physical and chemical properties

Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available

Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

SECTION 10 Stability and reactivity

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

SECTION 11 Toxicological information

Information on toxicological effects

Inhaled	The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.
Ingestion	The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	Although the material is not thought to be an irritant (as classified by EC Directives), direct contact with the eye may cause transient discomfort characterised by tearing or conjunctival redness (as with windburn). Slight abrasive damage may also result.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

4 Dremenia etinel de hude	ΤΟΧΙΟΙΤΥ	IRRITATION	
4-Bromonicotinaldehyde	Not Available	Not Available	
Legend:	 Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances 		

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
Legend: 🛛 🗙 – Data either not available or does not fill the criteria for classification			

Data available to make classification

Toxicity

	Endpoint	Test Duration (hr)	Species	Value	Source
4-Bromonicotinaldehyde	Not Available	Not Available	Not Available	Not Available	Not Available
Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data				

Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air		
	No Data available for all ingredients	No Data available for all ingredients		

Bioaccumulative potential

Ingredient	Bioaccumulation	
	No Data available for all ingredients	

Mobility in soil

Ingredient	Mobility	
	No Data available for all ingredients	

SECTION 13 Disposal considerations

Waste treatment methods

Product / Packaging disposal Recycle wherever possible or consult manufacturer for recycling options. Consult State Land Waste Management Authority for disposal. Bury residue in an authorised landfill. Recycle containers if possible, or dispose of in an authorised landfill.

SECTION 14 Transport information

Labels Required

Marine Pollutant NO

Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name Group

Transport in bulk in accordance with the IGC Code

Product name Ship Type

SECTION 15 Regulatory information

Safety, health and environmental regulations / legislation specific for the substance or mixture

National Inventory Status

National Inventory	Status	
Australia - AIIC / Australia Non-Industrial Use	Not Available	
Canada - DSL	Not Available	
Canada - NDSL	Not Available	
China - IECSC	Not Available	
Europe - EINEC / ELINCS / NLP	Not Available	
Japan - ENCS	Not Available	
Korea - KECI	Not Available	
New Zealand - NZIoC	Not Available	
Philippines - PICCS	Not Available	
USA - TSCA	Not Available	
Taiwan - TCSI	Not Available	
Mexico - INSQ	Not Available	
Vietnam - NCI	Not Available	
Russia - FBEPH	Not Available	
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.	

SECTION 16 Other information

Revision Date	07/07/2023
Initial Date	07/07/2023

SDS Version Summary

Version	Date of Update	Sections Updated	
1.2	07/07/2023	CAS Number, Hazards identification - Classification, Composition / information on ingredients - Ingredients, Korean MSDS Number, Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms	

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

- EN 374 Protective gloves against chemicals and micro-organisms
- EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

- PC TWA: Permissible Concentration-Time Weighted Average
- PC STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

- STEL: Short Term Exposure Limit
- TEEL: Temporary Emergency Exposure Limit,

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

- NOAEL :No Observed Adverse Effect Level
- LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors BEI: Biological Exposure Index AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Powered by AuthorITe, from Chemwatch.