

# **Apollo Scientific**

Part Number: **OR4829** Version No: **1.1** Safety Data Sheet (Conforms to Annex II of REACH (1907/2006) - Regulation 2020/878) Chemwatch Hazard Alert Code: 0

Issue Date: **16/09/2022** Print Date: **03/08/2023** S.REACH.GBR.EN

### SECTION 1 Identification of the substance / mixture and of the company / undertaking

#### **1.1. Product Identifier**

Product name	3,4-Dihydroquinolin-2(1H)-one
Chemical Name	hydrocarbostyril
Synonyms	Not Available
Chemical formula	С9Н9NO
Other means of identification	Not Available
CAS number	553-03-7

#### 1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
Uses advised against	No specific uses advised against are identified.

#### 1.3. Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific
Address	Whitefield Road, Bredbury SK62QR United Kingdom
Telephone	01614060505
Fax	0161 406 0506
Website	http://www.apolloscientific.co.uk/
Email	sales@apolloscientific.co.uk

### 1.4. Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

# **SECTION 2 Hazards identification**

# 2.1. Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>

Not Applicable

#### 2.2. Label elements

Hazard pictogram(s)	Not Applicable
Signal word	Not Applicable

#### Hazard statement(s)

Not Applicable

#### Supplementary statement(s)

Not Applicable

### Precautionary statement(s) Prevention

Not Applicable

### Precautionary statement(s) Response

Not Applicable

#### Precautionary statement(s) Storage

Not Applicable

#### Precautionary statement(s) Disposal

Not Applicable

# 2.3. Other hazards

REACH - Art.57-59: The mixture does not contain Substances of Very High Concern (SVHC) at the SDS print date.

### **SECTION 3 Composition / information on ingredients**

#### 3.1.Substances

1. CAS No 2.EC No 3.Index No 4.REACH No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor	Nanoform Particle Characteristics
Not Available	100	3,4-Dihydroquinolin- 2(1H)-one	Not Applicable	Not Applicable	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

### 3.2.Mixtures

See 'Information on ingredients' in section 3.1

### **SECTION 4 First aid measures**

#### 4.1. Description of first aid measures

Eye Contact	<ul> <li>If this product comes in contact with eyes:</li> <li>Wash out immediately with water.</li> <li>If irritation continues, seek medical attention.</li> <li>Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.</li> </ul>
Skin Contact	<ul> <li>If skin or hair contact occurs:</li> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

# 4.2 Most important symptoms and effects, both acute and delayed

See Section 11

### 4.3. Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

### **SECTION 5 Firefighting measures**

### 5.1. Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

#### 5.2. Special hazards arising from the substrate or mixture

Fire incompatibility None known.
----------------------------------

#### 5.3. Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> </ul>

### **SECTION 6 Accidental release measures**

#### 6.1. Personal precautions, protective equipment and emergency procedures

See section 8

#### 6.2. Environmental precautions

See section 12

### 6.3. Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid contact with skin and eyes.</li> <li>Wear impervious gloves and safety glasses.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Do NOT use air hoses for cleaning</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	<ul> <li>Clear area of personnel and move upwind.</li> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Control personal contact with the substance, by using protective equipment and dust respirator.</li> <li>Prevent spillage from entering drains, sewers or water courses.</li> <li>Avoid generating dust.</li> <li>Sweep, shovel up. Recover product wherever possible.</li> <li>Put residues in labelled plastic bags or other containers for disposal.</li> <li>If contamination of drains or waterways occurs, advise emergency services.</li> </ul>

### 6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

### **SECTION 7 Handling and storage**

#### 7.1. Precautions for safe handling

Safe handling	<ul> <li>Limit all unnecessary personal contact.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> </ul>
---------------	---

#### Issue Date: 16/09/2022 Print Date: 03/08/2023

3,4-Dihydroquinolin-2(1H)-one
-------------------------------

	<ul> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Fire and explosion protection	See section 5
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

# 7.2. Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	Avoid contamination of water, foodstuffs, feed or seed. None known
Hazard categories in accordance with Regulation (EC) No 1272/2008	Not Available
Qualifying quantity (tonnes) of dangerous substances as referred to in Article 3(10) for the application of	Not Available

# 7.3. Specific end use(s)

See section 1.2

# **SECTION 8 Exposure controls / personal protection**

### 8.1. Control parameters

Ingredient	DNELs Exposure Pattern Worker	PNECs Compartment
Not Available	Not Available	Not Available

\* Values for General Population

### Occupational Exposure Limits (OEL)

# INGREDIENT DATA

Source	Ingredient	Material name	TWA	STEL	Peak	Notes
Not Available						

Not Applicable

### Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
3,4-Dihydroquinolin- 2(1H)-one	Not Available	Not Available	Not Available

Skin protection

See Hand protection below

### 3,4-Dihydroquinolin-2(1H)-one

Ingredient	Original IDLH	Revised IDLH	
3,4-Dihydroquinolin- 2(1H)-one	Not Available	Not Available	
2. Exposure controls			
8.2.1. Appropriat engineering control	<ul> <li>s direct spray, spray painting in shallow booths, drum filling, discharge (active generation into zone of rapid air motion) grinding, abrasive blasting, tumbling, high speed wheel gen velocity into zone of very high rapid air motion).</li> <li>Within each range the appropriate value depends on: Lower end of the range</li> <li>1: Room air currents minimal or favourable to capture</li> <li>2: Contaminants of low toxicity or of nuisance value only.</li> <li>3: Intermittent, low production.</li> <li>4: Large hood or large air mass in motion</li> <li>Simple theory shows that air velocity falls rapidly with distant generally decreases with the square of distance from the extraction point should be adjusted, accordingly, after referer extraction fan, for example, should be a minimum of 4-10 m/distant from the extraction point. Other mechanical considera apparatus, make it essential that theoretical air velocities are installed or used.</li> </ul>	tkers and will typically be independent of w         ty or process is done to reduce the risk.         selected hazard "physically" away from the nment. Ventilation can remove or dilute ar natch the particular process and chemical went employee overexposure.         Inded as powders or crystals; even when particol.         e substance in air could occur, respiratory         absorption cartridge;         ne right type;         g "escape" velocities which, in turn, deterrive the contaminant.         conveyer loading, crusher dusts, gas         nerated dusts (released at high initial         Upper end of the range         1: Disturbing room air currents         2: Contaminants of high toxicity         3: High production, heavy use         4: Small hood-local control only         ce away from the opening of a simple extra raction point (in simple cases). Therefore the to distance from the contaminating sorts is (800-2000 f/min) for extraction of crushe ations, producing performance deficits with	Air Speed: 1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
8.2.2. Individual protectio measures, such a personal protectiv equipmer			
Eye and face protectio	<ul> <li>Safety glasses with side shields</li> <li>Chemical goggles. [AS/NZS 1337.1, EN166 or national e</li> <li>Contact lenses may pose a special hazard; soft contact l document, describing the wearing of lenses or restriction include a review of lens absorption and adsorption for the Medical and first-aid personnel should be trained in their event of chemical exposure, begin eye irrigation immedia</li> </ul>	enses may absorb and concentrate irritan s on use, should be created for each work e class of chemicals in use and an accoun removal and suitable equipment should b	place or task. This should t of injury experience. e readily available. In the

be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59].

Hands/feet protectionThe selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from<br/>manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material<br/>can not be calculated in advance and has therefore to be checked prior to the application.<br/>The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be<br/>observed when making a final choice.<br/>Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands

should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.

<ul> <li>Instance of give material, - down in thickness and - down in the protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended. - When noty bitel contact is expected, a givew with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended. - When noty bitel contact is expected, a givew with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 17-739-68 may application, gives are rated as: - Excellent when breakthrough time - 240 min - Gord when breakthrough time - 20 min - Fair when breakthrough time - 20 min - For when gives ond the adve and divide we madacture, thegive breakthrough time</li></ul>		Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:
<ul> <li>- glova thickness and</li></ul>		· frequency and duration of contact,
<ul> <li>. distarily</li> <li>. distarily</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/A25 2161.1 or national equivalent).</li> <li>. When nybiologid or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/A25 2161.10.1 or national equivalent) is recommended.</li> <li>. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm use.</li> <li>. Contaminated gloves should be replaced.</li> <li>As defined in ASTM F739-86 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>For when glove material digrades</li> <li>For ownen glove material digrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>Ishould be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a glove thickness in the accound of the glove model. Therefore, glove selection should also based on considerition of the task.</li> <li>Net: Depending on the activity being conducted, gloves of unormally be used for considering of the task.</li> <li>Net: Depending on the activity being conducted, gloves of unormality is needed. Horever, these gloves (down to 0.1 mm or nes) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is a basel and considering on the activity being conducted, gloves of protection adjound normally be use splications, then disposed of a "Thicker gloves (up to 0.1 mm or nes) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abrasino reputcher potential</li></ul></li></ul>		· chemical resistance of glove material,
Select gioves tested to a relevant standard (e.g. Europe EN 374, US F733, ASXS 2161.1 or national equivalent).         • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNS2 2161.10.1 or national equivalent) is recommended.         • When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNS2 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 400 min         • Good when breakthrough time > 20 min         • Foir when figure shathrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a trictness typically greater than 0.35 mm, are recommended.         It should be omphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data taken into account during theres are only likely to glove should havasy be tendine during the most symptomical dostrop is needed. However, these gloves are only likely to give short duration protection and would normally be use applications, then disposed of, • Thiker gloves (up to 3 mm or more) may be required		· glove thickness and
• When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended.           • Some glow oplymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.           • Sode glow oplymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.           • Sode when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min           • Poor when glow material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           • Bor when glow material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           • Bor when glow material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           • Thinker gloves (see on consideration of the task requirements and knowledge of breakthrough times.         • Or when glow will be degrades           • Or when glow will be degrades         For general applications, doves will be diver antivature, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure solection of the specific tasks. For example:           • Thinker gloves (up to 3 mm or more) may be requir		· dexterity
greater than 240 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended.         • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Orntaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetion efficiency of the glove willto adherous the activation protection and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove or varying thickness may abe required where there is in deformed in annual detactify its needed. However, these gloves are only likely to give short dation protection and would normally be just for single use applications, glove, item dation an on-perfume discuss event.         • Thinker gloves (down to 1.1 mm or less) may be r		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
<ul> <li>When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZ5 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove oplymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 400 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>For when glove material digraves is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, flow markedial gloves is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, fle manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varing thickness may be required on the equive material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varing there is a mechanical (as well as a chemical) risk i.e. where there is abrais on ry uncluve potential</li> <li>Gloves must use potencial data. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed molisturier is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraise partice and not present.</li> <li>Polychirooprene.</li> <li>Notire protection below&lt;</li></ul>		
according to EN 374, AS/NZS 2161.0.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F.739-86 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based no consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove maintfacturer, the glove tipote model. Therefore, the manufacturer, the glove tipote and the glove model. Therefore, gloves so of using the gene of manual destority is needed. However, these gloves are on puncture potential         Other protection of the ollowing potential destination protection and would hore single applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical), risk i.e. where there is abraision or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and fried thoroughly. Application of a non-perfumed mistur		greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
<ul> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 420 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the take requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.</li> <li>Thinker gloves (up to 3 mm or more) may be required drug be enguired thyse for sanghle:             <ul> <li>Thinker gloves (up to 3 mm or more) may be required where a neuros estimation a comperture potential</li> <li>Glove thickness are not play by gloves, hands should be washed and dried thoroughly. Application of a non-perfumed mosturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>budy in ubber.</li> <li>budy in ubber.</li> <li>budy in ubber.</li></ul></li></ul></li></ul>		· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
Image term use.       • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       • Excellent when breakthrough time > 480 min         • Good whom breakthrough time > 20 min       • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min       • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min       • Fair when breakthrough time > 20 min         • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.       It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove multiple typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove multiple typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove model. Therefore, glove selection the manufactures technical data should always be taken in tha account to ensure selection of the most appropring glove for the task. Note: Depending on the activity being conducted, gloves of varing thickness may be required where a high degree of manual deterity is needed. However, these gloves are only likely to glove short duration protection and would normally be just for single use applications, then disposed of.         • Thinner gloves (down to 0.1 mm or more) may be required where there is		
• Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time < 400 min         • Good when breakthrough time < 20 min         • Fair when breakthrough time < 20 min         • For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove maturacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity ping conducted, gloves of varying thickness may also explicit tasks. For example:         • Thinker gloves (dow not 0.1 mm or less) may be required where a high degree of manual destrem; is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (dow not 0.1 mm or less) may be required where is a mechanical (as well as a chemical) risk i.e. where there is a bronce there is a breaktine where braineal is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraisive particles are not present.         • polybrity/chloroprene.       • hittile rubber.         • hit		
As defined in ASTM F-739-96 in any application, gloves are rated as:         · Excellent when breakthrough time > 400 min         · Good When breakthrough time < 20 min         · Fair when breakthrough time < 20 min         · Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacture, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required where here is abrasion or puncture potential         Gloves site on to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be wom on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraisve particles are not present.         • polychioroprene.       • hirtlie		
<ul> <li>Excellent when breakthrough time &gt; 480 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove maufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (gut to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturistic is recommended.</li> </ul> </li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         <ul> <li>polychloroprene.</li> <li>hithir tubber.</li> <li>butly rubbe</li></ul></li></ul>		
• Good when breakthrough time > 20 min         • Pair when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove matural advarys be taken into account to ensure selection of the most appropriate gloves for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high dependent or single use applications, the disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where a brash departices are not present.</li> <li>polychloroprene.</li> <li>nitrie rubber.</li> <li>polychloroprene.</li> <li>nitrie rubber.</li> <li>byly hubber.</li> <li>byly hubber.</li> <li>byly hubber.</li> <li>byly hubber.</li> <li>byly hubber.</li> <li>byly hubber.</li> <li>byloychloroprene.</li> <li>polychlo</li></ul>		
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the eaxet composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required to specific tasks. For example:         <ul> <li>Thicner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there gloves ser a only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experime indicativer is that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychioroprene.</li> <li>hybly chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> </li> <li>Body protection</li> <li>See Other protection below</li></ul>		
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required to reseific tasks. For example:         <ul> <li>Thinker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is aloreasin or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyf rubber.</li> <li>butyf rubber.</li> <li>butyf rubber.</li> <li>floroceatutchouc.</li> <li>polychloroprene.</li> <li>floroceatutchouc.</li> <li>p</li></ul></li></ul>		
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychiloroprene.       • polychiloroprene.         • hittile rubber.       • butyl rubber.         • butyl rubber. <th></th> <th></th>		
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextrity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>hotychloroprene.</li> <li>hittile rubber.</li> <li>bolychloroprene.</li> <li>nitrile rubber.</li> <li>b</li></ul>		
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychioroprene.</li> <li>hitrile rubber.</li> <li>bustf rubber.</li> <li>polychioroprene.</li> <li>hitrile rubber.</li> <li>gloves should be examined for wear and/ or degradation constantly.</li> <li>Body protection</li> <li>See Other protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>Orther protection</li> <li>Barrier cream.</li> <li>overalls.</li> <li></li></ul>		
should also be based on consideration of the task requirements and knowledge of breakthrough times.       Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required to respecific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>buty rubber.</li> <li>futorocaoutchouc.</li> <li>polyvinyl chioride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection     See Other protection below           No special equipment needed when handling small quantities.           Other protection         No special equipment needed when handling small quantities.		
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> </ul> <li>Gloves should be examined for wear and/ or degradation constantly.</li> <li>Body protection</li> <li>See Other protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>Other protection</li>		
manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychiordie.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> <li>See Other protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>OTHERWISE:</li> <li>Overalls.</li> <li>Borrier cream.</li> <li>Burrier cream.</li> <li>Vertional data should and the should and the section of the most appropriate glove for the task.</li> <li>No special equipment needed when handling small quantities.</li> <li>Other protection</li> <li>Vertionals.</li> <li>Barrier cream.</li> <li>Sectional data should be as the protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>Other protection<!--</th--><th></th><th></th></li></ul>		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>intrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>fluorocaoutchouc.</li> <li>gloves should be examined for wear and/ or degradation constantly.</li> </ul> <li>Body protection         <ul> <li>See Other protection below</li> <li>No special equipment needed when handling small quantities.</li> <li>OTHERWISE:                 <ul> <li>Overalls.</li> <li>Barrier cream.</li> </ul> </li> </ul></li>		
<ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hittle rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection See Other protection below No special equipment needed when handling small quantities. Other protection Other protection Barrier cream.		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polychloroprene.         • nitrile rubber.         • fluorocaoutchouc.         • polychloroprene.         • nitrile rubber.         • fluorocaoutchouc.         • polychloroprene.         • nitrile rubber.         • fluorocaoutchouc.         • polychul be examined for wear and/ or degradation constantly.         Gloves should be examined for wear and/ or degradation constantly.         Other protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polycyinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.         * nitrile rubber.         * butyl rubber.         * butyl rubber.         * fluorocaoutchouc.         * polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         * Overalls.         * Barrier cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. <ul> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection         See Other protection below           No special equipment needed when handling small quantities.         OTHERWISE: <ul> <li>Overalls.</li> <li>Barrier cream.</li> </ul>		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         butyl rubber.         fluorocaoutchouc.         polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
• polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
<ul> <li>hitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection           See Other protection below           No special equipment needed when handling small quantities.           OTHERWISE:           • Overalls.           • Barrier cream.		
• butyl rubber.       • fluorocaoutchouc.         • polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         No special equipment needed when handling small quantities.       OTHERWISE:         • Overalls.       • Deveralls.         • Barrier cream.       • Barrier cream.		
• fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         No special equipment needed when handling small quantities.         OTHERWISE:         • Overalls.         • Barrier cream.		
Image: Polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Image: Body protection       See Other protection below         Image: Dother protection       No special equipment needed when handling small quantities.         Image: Other protection       OTHERWISE:         Image: Polycing Content of Polycing		
Body protection         See Other protection below           Other protection         No special equipment needed when handling small quantities.           OTHERWISE:         Overalls.           Barrier cream.         Barrier cream.		
Other protection       No special equipment needed when handling small quantities.         OTHERWISE:       • Overalls.         • Barrier cream.       • Barrier cream.		Gloves should be examined for wear and/ or degradation constantly.
Other protection       OTHERWISE:         • Overalls.       • Barrier cream.	Body protection	See Other protection below
Other protection       OTHERWISE:         • Overalls.       • Barrier cream.		No special equipment needed when handling small quantities.
► Barrier cream.		
	Other protection	▶ Overalls.
► Evewash unit.		▶ Barrier cream.
		► Eyewash unit.

#### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

• Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

 $\cdot$  Use approved positive flow mask if significant quantities of dust becomes airborne.

 $\cdot$  Try to avoid creating dust conditions.

#### 8.2.3. Environmental exposure controls

See section 12

#### **SECTION 9** Physical and chemical properties

#### 9.1. Information on basic physical and chemical properties

Appearance	Not Available		
			1
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	165-167	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available
Nanoform Solubility	Not Available	Nanoform Particle Characteristics	Not Available
Particle Size	Not Available		

#### 9.2. Other information

Not Available

### **SECTION 10 Stability and reactivity**

10.1.Reactivity	See section 7.2
10.2. Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

### **SECTION 11 Toxicological information**

11.1. Information on hazard classes as defined in Regulation (EC) No 1272/2008 Information on toxicological effects

Inhaled	The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	Although the material is not thought to be an irritant (as classified by EC Directives), direct contact with the eye may cause transient discomfort characterised by tearing or conjunctival redness (as with windburn). Slight abrasive damage may also result.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

3,4-Dihydroquinolin-	тохісіту	IRRITATION	
2(1H)-one	Not Available	Not Available	
Legend:	1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances		

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
	Le	gend: 🗙 – Data either not ava	ailable or does not fill the criteria for classificatior

Data available to make classification

### 11.2 Information on other hazards

### 11.2.1. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

#### 11.2.2. Other information

See Section 11.1

# **SECTION 12 Ecological information**

#### 12.1. Toxicity

	Endpoint	Test Duration (hr)	Species	Value	Source
3,4-Dihydroquinolin- 2(1H)-one	Not Available	Not Available	Not Available	Not Available	Not Available
Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data				

### 12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
	No Data available for all ingredients	No Data available for all ingredients	

# 12.3. Bioaccumulative potential

Ingredient	Bioaccumulation	
	No Data available for all ingredients	

### 12.4. Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

### 12.5. Results of PBT and vPvB assessment

	P	В	т
Relevant available data	Not Available	Not Available	Not Available
PBT	×	×	×
vPvB	×	×	×
PBT Criteria fulfilled?			
vPvB	No		

### 12.6. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

### 12.7. Other adverse effects

No evidence of ozone depleting properties were found in the current literature.

### **SECTION 13 Disposal considerations**

### 13.1. Waste treatment methods

Product / Packaging disposal	<ul> <li>Recycle wherever possible or consult manufacturer for recycling options.</li> <li>Consult State Land Waste Management Authority for disposal.</li> <li>Bury residue in an authorised landfill.</li> <li>Recycle containers if possible, or dispose of in an authorised landfill.</li> </ul>
Waste treatment options	Not Available
Sewage disposal options	Not Available

### **SECTION 14 Transport information**

### Labels Required

Marine Pollutant	NO
HAZCHEM	Not Applicable

### Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number or ID number	Not Applicable					
14.2. UN proper shipping name	Not Applicable					
14.3. Transport hazard	Class	Not Applicab	le			
class(es)	Subsidiary risk	Subsidiary risk Not Applicable				
14.4. Packing group	Not Applicable					
14.5. Environmental hazard	Not Applicable					
	Hazard identifica	ation (Kemler)	Not Applicable			
	Classification code		Not Applicable			
14.6. Special precautions	Hazard Label		Not Applicable			
for user	user Special provisions		Not Applicable			
	Limited quantity		Not Applicable			
	Tunnel Restriction	on Code	Not Applicable			

14.1. UN number	Not Applicable				
14.2. UN proper shipping name	Not Applicable				
	ICAO/IATA Class Not Applicable				
14.3. Transport hazard class(es)	ICAO / IATA Subrisk Not Applicable				
class(es)	ERG Code Not Applicable				
14.4. Packing group	Not Applicable				
14.5. Environmental hazard	Not Applicable				
	Special provisions		Not Applicable		
	Cargo Only Packing Instructions		Not Applicable		
	Cargo Only Maximum Qty / Pack		Not Applicable		
14.6. Special precautions for user	Passenger and Cargo Packing Instructions		Not Applicable		
	Passenger and Cargo Maximum Qty / Pack		Not Applicable		
	Passenger and Cargo	Limited Quantity Packing Instructions	Not Applicable		
	Passenger and Cargo Limited Maximum Qty / Pack		Not Applicable		

### Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable		
14.2. UN proper shipping name	Not Applicable		
14.3. Transport hazard	IMDG Class Not Applicable		
class(es)	IMDG Subrisk	Not Applicable	
14.4. Packing group	Not Applicable		
14.5. Environmental hazard	Not Applicable		
	EMS Number	Not Applicable	
14.6. Special precautions for user	Special provisions	Not Applicable	
	Limited Quantities	Not Applicable	

# Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable		
14.2. UN proper shipping name	Not Applicable		
14.3. Transport hazard class(es)	Not Applicable Not Applicable		
14.4. Packing group	Not Applicable		
14.5. Environmental hazard	Not Applicable		
14.6. Special precautions for user	Classification code	Not Applicable	
	Special provisions	Not Applicable	
	Limited quantity	Not Applicable	
	Equipment required	Not Applicable	
	Fire cones number	Not Applicable	

### 14.7. Maritime transport in bulk according to IMO instruments

### 14.7.1. Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

# 14.7.2. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

# 14.7.3. Transport in bulk in accordance with the IGC Code

Product name Ship Type

# **SECTION 15 Regulatory information**

## 15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

This safety data sheet is in compliance with the following EU legislation and its adaptations - as far as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; Commission Regulation (EU) 2020/878; Regulation (EC) No 1272/2008 as updated through ATPs.

# Information according to 2012/18/EU (Seveso III):

Seveso Category	Not Available

#### 15.2. Chemical safety assessment

For further information please look at the Chemical Safety Assessment and Exposure Scenarios prepared by your Supply Chain if available.

#### ECHA SUMMARY

Not Applicable

#### **National Inventory Status**

National Inventory	Status	
Australia - AIIC / Australia Non-Industrial Use	Not Available	
Canada - DSL	Not Available	
Canada - NDSL	Not Available	
China - IECSC	Not Available	
Europe - EINEC / ELINCS / NLP	Not Available	
Japan - ENCS	Not Available	
Korea - KECI	Not Available	
New Zealand - NZIoC	Not Available	
Philippines - PICCS	Not Available	
USA - TSCA	Not Available	
Taiwan - TCSI	Not Available	
Mexico - INSQ	Not Available	
Vietnam - NCI	Not Available	
Russia - FBEPH	Not Available	
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.	

#### **SECTION 16 Other information**

Revision Date	16/09/2022
Initial Date	16/09/2022

#### Full text Risk and Hazard codes

#### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

- EN 166 Personal eye-protection EN 340 Protective clothing
- EN 374 Protective gloves against chemicals and micro-organisms
- EN 13832 Footwear protecting against chemicals
- EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC - TWA: Permissible Concentration-Time Weighted Average PC - STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit. IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value I OD. Limit Of Detection OTV: Odour Threshold Value **BCF: BioConcentration Factors BEI: Biological Exposure Index** AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Powered by AuthorITe, from Chemwatch.

