

# **Apollo Scientific**

Part Number: **OR907361** Version No: **1.1** Safety Data Sheet Chemwatch Hazard Alert Code: 2

Issue Date: **08/09/2023** Print Date: **08/09/2023** S.GHS.GB-NIR.EN

# SECTION 1 Identification of the substance / mixture and of the company / undertaking

### **Product Identifier**

Product name	3-(1-Cyanocyclopropyl)phenylboronic acid
Chemical Name	(2-(1-氰基环丙基)苯基)硼酸
Synonyms	Not Available
Other means of identification	Not Available
CAS number	2096339-75-0*

### Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	lot Available
--------------------------	---------------

### Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road, Bredbury SK6 2QR Northern Ireland (UK)
Telephone	01614060505	+44(0) 161 406 0505
Fax	0161 406 0506	Not Available
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk
Email	sales@apolloscientific.co.uk	sales@apolloscientific.co.uk

### **Emergency telephone number**

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

### **SECTION 2 Hazards identification**

# Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>	H302 - Acute Toxicity (Oral) Category 4, H312 - Acute Toxicity (Dermal) Category 4, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2, H332 - Acute Toxicity (Inhalation) Category 4
Legend:	1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

## Label elements

Hazard pictogram(s)	
Signal word	Warning

### Hazard statement(s)

H302	Harmful if swallowed.
H312	Harmful in contact with skin.
H315	Causes skin irritation.
H319	Causes serious eye irritation.
H332	Harmful if inhaled.

### Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.
P261	Avoid breathing dust/fumes.
P264	Wash all exposed external body areas thoroughly after handling.
P270	Do not eat, drink or smoke when using this product.
P280	Wear protective gloves, protective clothing, eye protection and face protection.

### Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P337+P313	If eye irritation persists: Get medical advice/attention.
P301+P312	IF SWALLOWED: Call a POISON CENTER/doctor/physician/first aider if you feel unwell.
P302+P352	IF ON SKIN: Wash with plenty of water.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
P330	Rinse mouth.
P332+P313	If skin irritation occurs: Get medical advice/attention.
P362+P364	Take off contaminated clothing and wash it before reuse.

# Precautionary statement(s) Storage

## Not Applicable

# Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or	pecial waste collection point in accordance with any local regulation

### **SECTION 3 Composition / information on ingredients**

### Substances

CAS No %[weight] Name Classification according to regulation (EC) No 1272/2008 [CLP] and SCL / M-Factor
---

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

### Mixtures

See section above for composition of Substances

# **SECTION 4 First aid measures**

### Description of first aid measures

Eye Contact

- If this product comes in contact with the eyes: • Wash out immediately with fresh running water.
- Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally

	<ul> <li>lifting the upper and lower lids.</li> <li>Seek medical attention without delay; if pain persists or recurs seek medical attention.</li> <li>Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.</li> </ul>
Skin Contact	<ul> <li>If skin or hair contact occurs:</li> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

# Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

# **SECTION 5 Firefighting measures**

### Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

# Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.
----------------------	-------------

### Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> <li>May emit corrosive fumes.</li> </ul>

# **SECTION 6 Accidental release measures**

### Personal precautions, protective equipment and emergency procedures

See section 8

# **Environmental precautions**

See section 12

# Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid breathing dust and contact with skin and eyes.</li> <li>Wear protective clothing, gloves, safety glasses and dust respirator.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Sweep up, shovel up or</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	Moderate hazard. <ul> <li>CAUTION: Advise personnel in area.</li> <li>Alert Emergency Services and tell them location and nature of hazard.</li> <li>Control personal contact by wearing protective clothing.</li> </ul>

Prevent, by any means available, spillage from entering drains or water courses.
▶ Recover product wherever possible.
• IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or oth
containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.
ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.
If contamination of drains or waterways occurs, advise Emergency Services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

# **SECTION 7 Handling and storage**

# Precautions for safe handling

Safe handling	<ul> <li>Avoid all personal contact, including inhalation.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Prevent concentration in hollows and sumps.</li> <li>DO NOT enter confined spaces until atmosphere has been checked.</li> <li>DO NOT allow material to contact humans, exposed food or food utensils.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately. Launder contaminated clothing before re-use.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

# Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	None known

# **SECTION 8 Exposure controls / personal protection**

## **Control parameters**

### Occupational Exposure Limits (OEL)

# INGREDIENT DATA

Not Available

#### Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
3-(1-Cyanocyclopropyl)phenylboronic acid	Not Available	Not Available	Not Available

Ingredient	Original IDLH	Revised IDLH
3-(1-Cyanocyclopropyl)phenylboronic acid	Not Available	Not Available

# Exposure controls

Exposure controls				
Appropriate engineering controls	Engineering controls are used to remove a hazard or place engineering controls can be highly effective in protecting we provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job acti Enclosure and/or isolation of emission source which keeps that strategically "adds" and "removes" air in the work envir designed properly. The design of a ventilation system must Employers may need to use multiple types of controls to pr • Local exhaust ventilation is required where solids are h large, a certain proportion will be powdered by mutual f • If in spite of local exhaust an adverse concentration of t considered. Such protection might consist of: (a): particle dust respirators, if necessary, combined with ar (b): filter respirators with absorption cartridge or canister of (c): fresh-air hoods or masks. Air contaminants generated in the workplace possess varyi velocities" of fresh circulating air required to effectively rem Type of Contaminant: direct spray, spray painting in shallow booths, drum filling, discharge (active generation into zone of rapid air motion) grinding, abrasive blasting, tumbling, high speed wheel ge velocity into zone of very high rapid air motion). Within each range the appropriate value depends on: Lower end of the range 1: Room air currents minimal or favourable to capture 2: Contaminants of low toxicity or of nuisance value only. 3: Intermittent, low production. 4: Large hood or large air mass in motion Simple theory shows that air velocity falls rapidly with distant generally decreases with the square of distance from the ex- extraction point should be adjusted, accordingly, after refer- extraction point should be adjusted, accordingly, after refer- extraction point, should be a minimum of 4-10 n distant from the extraction point. Other mechanical conside apparatus, make it essential that theoretical air velocities ar installed or used.	orkers and will typically be independ vity or process is done to reduce the a selected hazard "physically" away ronment. Ventilation can remove or match the particular process and cl event employee overexposure. andled as powders or crystals; ever riction. the substance in air could occur, res n absorption cartridge; the right type; ing "escape" velocities which, in turr ove the contaminant. conveyer loading, crusher dusts, ga enerated dusts (released at high initi Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only nce away from the opening of a sim xtraction point (in simple cases). Th ence to distance from the contaminan of (800-2000 f/min) for extraction o rations, producing performance def	te risk. y from the worker and ventilation dilute an air contaminant if hemical or contaminant in use. h when particulates are relatively spiratory protection should be h, determine the "capture Air Speed: as 1-2.5 m/s (200-500 f/min.) ial 2.5-10 m/s (500-2000 f/min.) ple extraction pipe. Velocity rerefore the air speed at the ating source. The air velocity at the of crusher dusts generated 2 metres icits within the extraction	
Individual protection measures, such as personal protective equipment				
Eye and face protection	<ul> <li>Safety glasses with side shields.</li> <li>Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent]</li> <li>Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59].</li> </ul>			
Skin protection	See Hand protection below			
Hands/feet protection	The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be			

Approval hygine is a lay element of affective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dred thoroughly. Application of a non-perturned misturies in the selection of gloves include: <ul> <li>trequency and duration of contact,</li> <li>thermical resistance of glove material,</li> <li>glove hickness and</li> <li>destrint?</li> </ul> <li>Subability and duration of contact,</li> <li>thermical resistance of glove material,</li> <li>glove hickness and</li> <li>destrint?</li> <li>Belet gloves tested to a netwarn standard (e.g. Europe EN 374, US F739, AS/N25 2161.10 r national equivalent).</li> <li>When noty hold for forequerity repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N25 2161.10.1 r national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for lang-term use.</li> <ul> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F739-96 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time 2 00 min</li> <li>Foor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.55 mm, are recommended.</li> <li>Isolud be emphasized nat glove with a thickness typically greater than 0.56 mm, are recommended.</li> <li>Isolud be applied to on the sixet quore associated as:</li> <ul> <li>Excellent when breakthrough time 2 00 min</li> <li>For greenal applications, gloves with a thickness typically greater than 0.55 mm, are recommended.</li> <li>It s</li></ul></ul>		channed when making a final shains
should be washed and dired thoroughly. Application of a non-perfurmed moisturiser is recommended.       Section of source is dependent on usage. Important factors in the selection of gloves include: <ul> <li>requency and duration of contact.</li> <li>chemical resistance of glove material.</li> <li>glove thickness and</li> <li>setterity</li> </ul> Sected gloves tested to a relevant standard (a.g. Europe EN 374. US F739, AS/NZS 2161.1 or national equivalent).         · When only brief contact may occur. a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.1 or national equivalent) is economended.           · When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.1 or national equivalent) is economicated.         · When only brief contact may optication, gloves are rated as:           · Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         · Contaminated gloves should be replaced.           A defined in ATM F73996 (in any application, gloves are rated as:         · Screelen when breakthrough time < 20 min           · Good when breakthrough time < 20 min         · Good when treated gloves down in take equivalents and knowledge of breakthrough time.           · Store glove polymer types are less and discrete to a glove manufacturer. He glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection the most appropriate glove fore transate streater and in the clave and maind would fo		observed when making a final choice. Bereasel hydrage is a key element of effective hand ears. Cleves must only be were an elegen hands. After using gleves, hands
Suitability and durability of glove type is dispondent on usage. Important factors in the selection of gloves include: <ul> <li>requency and duration of contact.</li> <li>elemical resistance of glove material,</li> <li>glove thickness and</li> <li>devetrity</li> </ul> Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).           'When prolonged of frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.01 or national equivalent).           'When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.01 or national equivalent) is recommended.           'Some glove op/our types are less affected by movement and this should be taken into account when considering gloves for long-term use.         'Contaminate gloves: should be replaced.           'So defined in ASTM F-739-96 in any opplication, gloves are rated as:         'Escellent when breakthrough time > 400 min           'Foor when glove material diggreads         'For general applications, gloves with a trickness typically greater than 0.35 mm, are recommended.           'Isolud be omphased that glove thickness in the account to ensure selection of the most papprinte glove for the task.           'Dor when glove material diggread on anotaction of the task regularity metal.           'Isolud be applications, gloves away dippending on the glove material lopscellcaton. the discover dives gloves for the task. <th></th> <th></th>		
<ul> <li>intequency and duration of contact.</li> <li>intervention of contact.</li> <li>When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 40 minutes according to EN 374, ASNZS 2161.10 or national equivalent).</li> <li>When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 40 minutes according to EN 374, ASNZS 2161.10 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in AST H-739.46 minutes according to EN 374, ASNZS 2011.01 or national equivalent); second model.</li> <li>For general applications, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 40 minutes</li> <li>Good whan breakthrough time &gt; 20 min</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are racommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove restarts. For example:</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of parametizations of the sakes. For example:</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these gloves are not approximately be indicates that the following polymer are suitable as glove material (as well as a chemical) fisk i.e. where there is a breakting the regioned on a the gloves of a manual desterity is needed. However, these gloves are not pres</li></ul>		
<ul> <li>chemical resistance of glove material,         <ul> <li>glove thickness and</li> <li>destrift</li> </ul> </li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASAZS 2161.1 or national equivalent),             <ul> <li>When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves ahould be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:                 <ul> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Flar when breakthrough time &gt; 20 min</li> <li>Flor when glove material gloves thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the parmeation efficiency of the glove multical dependent on the exact composition of the glove material.</li> <li>Glove thickness are vary depending on the glove material diverse based on consideration of the task.</li> <li>Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:</li></ul></li></ul></li></ul>		
<ul> <li>gives thickness and</li></ul>		
<ul> <li>. disterily</li> <li>. disterily</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNZS 2161.1 or national equivalent).</li> <li>. When optionged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.</li> <li>. When only helf contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.</li> <li>. Some glove oplomer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>. Contaminated gloves should be replaced.</li> <li>Ra defined in ASTM F739-96 in any application, gloves are rated as:</li> <li>. Excellent when breakthrough time &gt; 40 min</li> <li>. Fair when breakthrough time &gt; 20 min</li> <li>. Fair when breakthrough time &gt; 20 min</li> <li>. For when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be based on consideration of the take requirements and knowledge of breakthrough times.</li> <li>. Glove thickness may also vary depending on the glove manufacturer, the glove tope and the glove model. Therefore, the manufacturer scherical data stere requirements and knowledge of the stakthrough time set operated.</li> <li>. Thinter gloves (opt to 0.1 mm or less) may be required where a high degree of manual detaterity is needed. However, these gloves such to 0.1 mm or less) may be required where a high degree of manual detaterity is needed. However, these gloves such to 0.1 mm or less in mays be required where a high degree of manual detaterity is needed. However, these gloves are only likely to 9 mm or more in may be required where a high degree of manual detate</li></ul>		
Select gives tested to a relevant standard (e.g. Europe EN 374, US F738, ASX25 2161.1 or national equivalent).         When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended.         When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended.         Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 480 min         • Good when breakthrough time > 20 min         • For or when glove milted idegrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove with a dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the tak requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove material dependent, the axis to the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required tor specific chemical, as the gloves are only likely to give short duration protection advould normaly be glove maderi. Therefore, g		•
• When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • When only birle contact is expected, a glow with a protection class of 5 or higher (breakthrough time greater than 00 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • Some glow ophware types are less affected by movement and this should be taken into account when considering gloves for long-term use.           • Contaminated gloves should be replaced.           As defined in ASTM F-739-96 in any application, gloves are rated as:           • Excellent when breakthrough time > 20 min           • Fair when breakthrough time > 20 min           • Foor when glowe material degrades           For greeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           It should be emphasized that glove thickness is not necessarily agood predictor of glove resistance to a specific chemical, as the permeation afficiency of the glove material. Therefore, glove salection should also be based on consideration of the task requirements and knowledge of breakthrough times.           Glove thickness may also vary depending on the activity being conductary, the glove material class. For example:           • Thicker gloves (down to 0.1 mm or less) may be required where a high degree of manual dextinity is needed. However, these gloves side to 10 yeine should buse that duration protection and would normally be give to a specific chemical, as the tremanufacturery tepatifial           • Thi		•
greater than 240 minutes according to EN 374, ASNX52 2161.10.1 or national equivalent) is recommended.         • When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNX52 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Good when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove material activation of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturer is technical data should always be taken into account to ensure selection of the most apportie glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abreadin or posteric to adveort these gloves are not preserve.         • Thicker gloves (up to 3 mm or more) may be required where a high d		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
according to EN 374, AS/N2S 2161.10.1 or national equivalent) is recommended.         Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         Contaminated gloves should be replaced.         As defined in ASTM 7-739-bit in any application, gloves are rated as:         Excellent when breakthrough time > 20 min         Fair when breakthrough time > 20 min         Foor when glove material degrades         For ogeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove thickness technical data should always be taken into account to ensure selection of the most supportinte glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraicin discusters is the following polymers are suitable as glove materials for protection against undissolved, dry solids, where a braix partices are not present.         Thinner gloves should be examined for wear and/ or degradation constantly.         Body protec		
according to EN 374, ASINZS 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTIN F-739-bit any application, gloves are rated as:         • Sociellent when breakthrough time > 400 min         • Good when breakthrough time > 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection a should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove material. Therefore, glove selection a should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove step and the glove material. Therefore, the manufacturer schnical data should always be taken into account to ensure selection of the maxe papropriate glove for the task. Note: Depending on the alcivity being conducted, gloves of varying thichenses may be required where a high degree of manual destretily is needed. However, these gloves sere only likely to give short duration protection and would normally be guist or single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a breaktin out on the maxe		When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
<ul> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-6in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Poor when glove material degrades</li> </ul> </li> <li>For opencing gloves and degrades</li> <li>Glove thickness may also vary depending on the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove would. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thicness may also that on the more diverse manufacturer, is a plove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thicness may also complexities is an end to be selection on the diver and where there is a brain or proprive (up to at mor more) may be required where a high degree of manual detactivity is needed. However, these gloves use on y likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to at mor more) may be required where a high degree of manual detactivity is needed.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection again</li></ul>		
Important       Important         Contaminated gloves should be replaced.       As defined in ASTM F-739-96 in any application, gloves are rated as:         Excellent when breakthrough time > 480 min       Good when breakthrough time > 20 min         Fair when breakthrough time > 20 min       For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove material. Therefore, the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer schnical data should always be taken into account to ensure selection of the manufacturer is schnadion or puncture potential         Glove thickness may also vary depending on the glove madel. Therefore, the manufacturer schnical data should always be taken into account to ensure selection of the moutes appropriate gloves (awn to 1.1 mor or less) may be required where a high degree of manufacturer, these gloves are only likely to give short duration protection and would normality be just for single use applications, then disposed of.		<b>o</b>
• Contaminated gloves should be replaced.         As defined in ASTM F-739-68 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time < 20 min         • For when glove material degrades         For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove material egloves type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the glove material applications, then disposed of.         • Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worm on clean hands. After using gloves, hands should be washed and d		
As defined in ASTM F-739-96 in any application, gloves are rated as: <ul><li>Excellent when breakthrough time &gt; 480 min</li><li>Good when breakthrough time &gt; 20 min</li><li>Fair when breakthrough time &gt; 20 min</li><li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li><li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove mudei. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li><li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: </li></ul>		-
• Excellent when breakthrough time > 480 min         • Good when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a tickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove manufacturer, the glove thickness may also vary depending on the gloves of varying thickness may be required to specific tasks. For example:         • Other protection       Glove thickness may also vary depending on the gloves of varying thickness may be required to specific tasks. For example:         • Thiner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasive particles are not protection and would normally be just for single use application of a non-perfurmed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.       • highly rubber.         • highly rubber.       • bylyly rubbr.         • bylyly rubber.       • by		
• Good when breakthrough time > 20 min         • Fair when breakthrough time < 20 min         • Poir when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily agod predictor of glove restatence to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of vanying thickness may be required of respecific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves sure only likely to give short duration protection and would normally be just for single use applications, then disposed of .         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsive particles are not present.         • polychioroprene.       • polychioroprene.         • hit in rubber.       • butyl rubber.         • butyl rubber.       • butyl rubber.         • hit orceaautchouce.       • polychioroprene.         • hitoric authoduce.       Gloves should		
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the tags.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.</li> <li>Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required on super propriet gloves for when gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thinner gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychioroprene.</li> <li>hitrile rubber.</li> <li>butyl rubber.</li></ul></li></ul>		
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thiner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves smust only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> </ul> </li> </ul>		-
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove metrial. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normality be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrais perfue there is and the distentin the distore dora dined thoroughly. Application of a non-perfume</li></ul>		
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the glove manufacturer, the glove the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinker gloves (down to 0.1 mu or less) may be required where a high degree of manual destript is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hittile rubber.</li> <li>buyly lubber.</li> <li>fluorecaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Glove should be examined for wear and/ or degradation constantly.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> <li>Overalls.</li> <li>P.V.C apron.</li> <li>P.V.C apron.</li> <li>P.V.C apron.</li> <li>Skin cleansing cream.</li> <li>Skin cleansing cream.</li> </ul>		
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: 		
should also be based on consideration of the task requirements and knowledge of breakthrough times.       Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hittile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychloroprene.</li> <li>hittile rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection     See Other protection below		
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>butyl</li></ul>		
Imanufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul><li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li><li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.          Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.          Polychloroprene.          Initile rubber.          butyl rubber. </li></ul></li></ul>		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         . Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         . Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasino or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl. Capron.         • Barrier		
<ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         <ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.             <ul></ul></li></ul></li></ul>		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.         * nitrile rubber.         * buyl rubber.         * polychloroprene.         * nitrile rubber.         * buyl rubber.         * buyl rubber.         * buyl rubber.         * buyl rubber.         * polychloroprene.         * nitrile rubber.         * buyl rubbr.         * buyl rubbr.         * Determi		
<ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>&gt; polychloroprene.</li> <li>&gt; nitrile rubber.</li> <li>&gt; butyl rubber.</li> <li>&gt; fluorocaoutchouc.</li> <li>&gt; polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul>		
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • polychloroparene.         • nitrile rubber.         • butyl rubber.         • polychlorocautchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.         * nitrile rubber.         * butyl rubber.         * fluorocaoutchouc.         * polychloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         * Overalls.         * P.V.C apron.         * Barrier cream.         * Skin cleansing cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. <ul> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection         See Other protection below               Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         fluorocaoutchouc.         polycyinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
• polychloroprene.       • nitrile rubber.         • butyl rubber.       • butyl rubber.         • fluorocaoutchouc.       • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		
• nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         Other protection         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Image: Protection of the protection		
• fluorocaoutchouc.       • polyvinyl chloride.         · polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		
Image: Polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly.         Image: Body protection       See Other protection below         Image: Other protection       • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li></ul>		
Body protection       See Other protection below         Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.		
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		Gloves should be examined for wear and/ or degradation constantly.
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>	Body protection	See Other protection below
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		▶ Overalls.
Other protection <ul> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
► Skin cleansing cream.	Other protection	

### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to

personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

#### **SECTION 9** Physical and chemical properties

#### Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

### **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

# **SECTION 11 Toxicological information**

#### Information on toxicological effects

Inhaled

The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control

	measures be used in an occupational setting.
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	This material can cause eye irritation and damage in some persons.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

3-(1-Cyanocyclopropyl)phenylboronic acid		ΤΟΧΙCITY	IRRITATION
		Not Available	Not Available
Legend: 1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances			

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	×	Reproductivity	×
Serious Eye Damage/Irritation	*	STOT - Single Exposure	×
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
	Le	gend: X – Data either not avail ✓ – Data available to ma	able or does not fill the criteria for classification ke classification

# **SECTION 12 Ecological information**

# Toxicity

3-(1-Cyanocyclopropyl)phenylboronic acid		Endpoint	Test Duration (hr)	Species	Value	Source
		Not Available	Not Available	Not Available	Not Available	Not Available
Legend: Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data						

# Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
	No Data available for all ingredients	No Data available for all ingredients

# **Bioaccumulative potential**

Ingredient	Bioaccumulation
	No Data available for all ingredients

# Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

# **SECTION 13 Disposal considerations**

Product / Packaging disposal		
---------------------------------	--	--

# **SECTION 14 Transport information**

La	abels Required	
	Marine Pollutant	NO

# Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

# 14.7.1. Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

### 14.7.2. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group

# 14.7.3. Transport in bulk in accordance with the IGC Code

Product name Ship Type

## **SECTION 15 Regulatory information**

# Safety, health and environmental regulations / legislation specific for the substance or mixture

### **National Inventory Status**

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	Not Available
Canada - DSL	Not Available
Canada - NDSL	Not Available
China - IECSC	Not Available
Europe - EINEC / ELINCS / NLP	Not Available
Japan - ENCS	Not Available
Korea - KECI	Not Available
New Zealand - NZIoC	Not Available
Philippines - PICCS	Not Available
USA - TSCA	Not Available
Taiwan - TCSI	Not Available
Mexico - INSQ	Not Available
Vietnam - NCI	Not Available
Russia - FBEPH	Not Available
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

### **SECTION 16 Other information**

Revision Date	08/09/2023
Initial Date	08/09/2023

### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC-TWA: Permissible Concentration-Time Weighted Average PC-STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit。 IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value LOD: Limit Of Detection OTV: Odour Threshold Value **BCF: BioConcentration Factors BEI: Biological Exposure Index** AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

### Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Acute Toxicity (Oral) Category 4, H302	Expert judgement
Acute Toxicity (Dermal) Category 4, H312	Expert judgement
Skin Corrosion/Irritation Category 2, H315	Expert judgement
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement
Acute Toxicity (Inhalation) Category 4, H332	Expert judgement

Powered by AuthorITe, from Chemwatch.