

## **Apollo Scientific**

Part Number: OR914205 Version No: 2.2 Safety Data Sheet

Chemwatch Hazard Alert Code: 2

Issue Date: 05/07/2023 Print Date: 05/07/2023 S.GHS.GB-NIR.EN

#### SECTION 1 Identification of the substance / mixture and of the company / undertaking

#### **Product Identifier**

Product name	6-Dimethyl-5,7-dioxaspiro[2.5]octane-4,8-dione			
Chemical Name	-dimethyl-5,7-dioxaspiro[2,5]octane-4,8-dione			
Synonyms	Not Available			
Chemical formula	C8-H10-O4			
Other means of identification	Not Available			
CAS number	5617-70-9*			

#### Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not A

Available

#### Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd	
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road, Bredbury Cheshire SK6 2QR United Kingdom (NI)	
Telephone	01614060505	+44(0) 161 406 0505	
Fax	0161 406 0506	Not Available	
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk	
Email	sales@apolloscientific.co.uk		

#### **Emergency telephone number**

Association / Organisation Not Available	
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

#### **SECTION 2 Hazards identification**

#### Classification of the substance or mixture

**Classification according to** regulation (EC) No 1272/2008 [CLP] and amendments [1]

H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

## Label elements

Hazard pictogram(s)		
Signal word	Warning	

#### Hazard statement(s)

H335	May cause respiratory irritation.	
H315	Causes skin irritation.	
H319	Causes serious eye irritation.	

#### Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.
P261 Avoid breathing dust/fumes.	
P280 Wear protective gloves, protective clothing, eye protection and face protection.	
P264 Wash all exposed external body areas thoroughly after handling.	

## Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing		
P312	Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.		
P337+P313	If eye irritation persists: Get medical advice/attention.		
P302+P352	IF ON SKIN: Wash with plenty of water.		
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.		
P332+P313	If skin irritation occurs: Get medical advice/attention.		
P362+P364	P362+P364         Take off contaminated clothing and wash it before reuse.		

#### Precautionary statement(s) Storage

P405	Store locked up.	
P403+P233	+P233 Store in a well-ventilated place. Keep container tightly closed.	

#### Precautionary statement(s) Disposal

P501 Dispose of contents/container to authorised hazardous or special waste collection point	n accordance with any local regulation.
--	---

#### **SECTION 3 Composition / information on ingredients**

#### Substances

	CAS No		%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn		L; * EU IOELVs				

available; [e] Substance identified as having endocrine disrupting properties

## Mixtures

See section above for composition of Substances

#### **SECTION 4 First aid measures**

#### Description of first aid measures

Eye Contact

If this product comes in contact with the eyes:

- Wash out immediately with fresh running water.
- + Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally

	<ul> <li>lifting the upper and lower lids.</li> <li>Seek medical attention without delay; if pain persists or recurs seek medical attention.</li> <li>Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.</li> </ul>
Skin Contact	If skin or hair contact occurs: <ul> <li>Flush skin and hair with running water (and soap if available).</li> <li>Seek medical attention in event of irritation.</li> </ul>
Inhalation	<ul> <li>If fumes, aerosols or combustion products are inhaled remove from contaminated area.</li> <li>Other measures are usually unnecessary.</li> </ul>
Ingestion	<ul> <li>Immediately give a glass of water.</li> <li>First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.</li> </ul>

## Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

#### **SECTION 5 Firefighting measures**

#### Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

#### Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.
----------------------	-------------

#### Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> <li>May emit corrosive fumes.</li> </ul>

## **SECTION 6 Accidental release measures**

#### Personal precautions, protective equipment and emergency procedures

See section 8

#### **Environmental precautions**

See section 12

#### Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Clean up all spills immediately.</li> <li>Avoid breathing dust and contact with skin and eyes.</li> <li>Wear protective clothing, gloves, safety glasses and dust respirator.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Sweep up, shovel up or</li> <li>Vacuum up (consider explosion-proof machines designed to be grounded during storage and use).</li> <li>Place spilled material in clean, dry, sealable, labelled container.</li> </ul>
Major Spills	Moderate hazard.  CAUTION: Advise personnel in area.  Alert Emergency Services and tell them location and nature of hazard.  Control personal contact by wearing protective clothing.

Prevent, by any means available, spillage from entering drains or water courses.
Recover product wherever possible.
• IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or othe
containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.
ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.
If contamination of drains or waterways occurs, advise Emergency Services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

## **SECTION 7 Handling and storage**

## Precautions for safe handling

Safe handling	<ul> <li>Avoid all personal contact, including inhalation.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> <li>Prevent concentration in hollows and sumps.</li> <li>DO NOT enter confined spaces until atmosphere has been checked.</li> <li>DO NOT allow material to contact humans, exposed food or food utensils.</li> <li>Avoid contact with incompatible materials.</li> <li>When handling, DO NOT eat, drink or smoke.</li> <li>Keep containers securely sealed when not in use.</li> <li>Avoid physical damage to containers.</li> <li>Always wash hands with soap and water after handling.</li> <li>Work clothes should be laundered separately. Launder contaminated clothing before re-use.</li> <li>Use good occupational work practice.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.</li> </ul>
Other information	<ul> <li>Store in original containers.</li> <li>Keep containers securely sealed.</li> <li>Store in a cool, dry area protected from environmental extremes.</li> <li>Store away from incompatible materials and foodstuff containers.</li> <li>Protect containers against physical damage and check regularly for leaks.</li> <li>Observe manufacturer's storage and handling recommendations contained within this SDS.</li> <li>For major quantities:</li> <li>Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams).</li> <li>Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.</li> </ul>

## Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Lined metal can, lined metal pail/ can.</li> <li>Plastic pail.</li> <li>Polyliner drum.</li> <li>Packing as recommended by manufacturer.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	None known

## **SECTION 8 Exposure controls / personal protection**

#### **Control parameters**

#### Occupational Exposure Limits (OEL)

## INGREDIENT DATA

Not Available

#### Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
6,6-Dimethyl- 5,7-dioxaspiro[2.5]octane- 4,8-dione	Not Available	Not Available	Not Available

Ingredient

**Original IDLH** 

Issue Date: 05/07/2023 Print Date: 05/07/2023

#### 6,6-Dimethyl-5,7-dioxaspiro[2.5]octane-4,8-dione

Ingredient	Original IDLH	Revised IDLH
6,6-Dimethyl- 5,7-dioxaspiro[2.5]octane- 4,8-dione	Not Available	Not Available
Exposure controls		
	Engineering controls are used to remove a hazard or place a bar engineering controls can be highly effective in protecting workers provide this high level of protection.	

The basic types of engineering controls are:

Process controls which involve changing the way a job activity or process is done to reduce the risk.

Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation that strategically "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure.

- Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction.
- If in spite of local exhaust an adverse concentration of the substance in air could occur, respiratory protection should be considered.

Such protection might consist of:

(a): particle dust respirators, if necessary, combined with an absorption cartridge;

- (b): filter respirators with absorption cartridge or canister of the right type;
- (c): fresh-air hoods or masks.

Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture velocities" of fresh circulating air required to effectively remove the contaminant.

Appropriate engineering	Type of Contaminant:	Air Speed:
controls	direct spray, spray painting in shallow booths, drum filling, conveyer loading, crusher dusts, gas discharge (active generation into zone of rapid air motion)	1-2.5 m/s (200-500 f/min.)
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial velocity into zone of very high rapid air motion).	2.5-10 m/s (500-2000 f/min.)

Within each range the appropriate value depends on:

Lower end of the range	Upper end of the range
1: Room air currents minimal or favourable to capture	1: Disturbing room air currents
2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity
3: Intermittent, low production.	3: High production, heavy use
4: Large hood or large air mass in motion	4: Small hood-local control only

Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.

Individual protection measures, such as personal protective equipment	
Eye and face protection	<ul> <li>Safety glasses with side shields.</li> <li>Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent]</li> <li>Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59].</li> </ul>
Skin protection	See Hand protection below
Hands/feet protection	The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.

The exact break through time for substances has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has to be obtained from the manufacture of the protective gloves and has the has a defected by movement and this should be take inthe account when considering gloves for functin		
Personal hygione is a key element of effective hand care. Gloves must only be worn oclean hands. After using gloves, hands should be watched and died thoroughly. Application of a non-perfurme modulus is a recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: <ul> <li>requency and duration of context.</li> <li>channel resistance of glove material,</li> <li>idport hickness and</li> <li>destinity</li> </ul> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNZS 2161.1 or national equivalent).</li> <li>'When only brief contact is espectrade. a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent).</li> <li>'When only brief contact is espectrade. a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent).</li> <li>'When only brief contact is espectrade. a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent).</li> <li>'When only brief protes are is affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>'Contaminated gloves should be replaced.</li> <li>As defined in ASTM F.73.996 in any application, gloves with a protection class of a one performance.</li> <li>For when glove material dogrados</li> <li>'Por when glove material dogrados</li> <li>'Dore minutes according the selection account to the according to glove resistance to a specific chemical, as the permeation afficients, and thickness typically greater than 0.35 mm, are recommended.</li> <li>How tho breaktrough time &lt; 20 min</li> <li>Glove thickness may alav vary dpecandi</li>		The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be
should be vashed and dired thoroughly. Application of a non-perfumed moisturiser is recommended.         visitability and duration of context.         - hermical resistance of glove material,         - prove flickness and         - settarity         Bedet gloves lested to a relevant standard (a.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent).         - When protonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 200 minutes according to EN 374, ASN2S 2161.1 or national equivalent).         - When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 200 minutes according to EN 374, ASN2S 2161.1 or national equivalent).         - When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 20 minutes according to EN 374, ASN2S 2161.1 or national equivalent).         - When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time scatchrough time		observed when making a final choice.
Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:         • represers and duration of contact.         • destriction         • glove thickness and         • glove thickness and         • When prolonged of frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent).         • When prolonged of frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contraministed gloves should be replaced.         • Social when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Foor when glove buickness is not accessarily a good predictor of glove medical. Therefore, glove selection about das to be based on consideration of the tax (uncommended.         • Ishould be emphased of the glove will be dependent on the exact composition of the most appropriate glove for the tax.         • Doro when glove buickness may abs vary depending on the glove manufacturer. He glove made.         • Sourd when threadstrough time < 20 min         • Fair when break		Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands
<ul> <li>- frequency and duration of contact.</li> <li>- demical resistance of glove material,</li> <li>- glove thickness and</li> <li>- dotstrifty</li> <li>Solicet gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent).</li> <li>- When prolonged or frequently ropeated contact may occur, a glove with a protection class of 5 or higher (treakthrough time greater than 40 minutes according to EN 374, ANDS 2161.1.0 to rational equivalent) is recommended.</li> <li>- When only brief contact is expected. a glove with a protection class of 3 or higher (treakthrough time greater than 40 minutes according to EN 374, ASIN2S 2161.1.0 to rational equivalent) is recommended.</li> <li>- Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>- Contaminated gloves should be replaced.</li> <li>As defined in ASTA ASIN2S 2161.1.01 or national equivalent) is recommended.</li> <li>- Gord when breakthrough time &gt; 400 min</li> <li>- Fair when breakthrough time &gt; 20 min</li> <li>- Fair when breakthrough time &gt; 400 min</li> <li>- Good when breakthrough time &gt; 400 minutes</li> <li>- For general applications, gloves when a thickneses typically</li></ul>		should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.
<ul> <li>- chemical resistance of glove material, - glove thickness and - distrity: Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). - When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (treakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent); - When only bried contact is expected, a glove with a protection class of 5 or higher (treakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.</li> <li>- Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. - Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: - Excellent when breakthrough time &gt; 20 min - Good when breakthrough time &gt; 20 min - Fair when breakthrough time &gt; 20 min - Glove time glove on clean</li></ul>		Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:
<ul> <li>glove thickness and</li> <li>glove thickness and</li> <li>glove thickness and</li> <li>glove thickness and</li> <li>when prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (treakthrough time greater than 40 dimutes according to EN 374, ASN25 2161.10 or national equivalent);</li> <li>When only bried contact is expected, a glove with a protection class of 3 or higher (treakthrough time greater than 40 dimutes according to EN 374, ASN25 2161.10 or national equivalent); is recommended.</li> <li>When only bried contact is expected, a glove with a protection class of 3 or higher (treakthrough time greater than 40 dimutes according to EN 374, ASN25 2161.10 or national equivalent); is recommended.</li> <li>Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm use.</li> <li>Contaminated gloves should be replaced.</li> <li>As defined in ASTM F-739-96 in any application, gloves are rated as:</li> <li>Excellent when breakthrough time &gt; 20 min</li> <li>Foor when glove material degrades</li> <li>For owhen glove material degrades</li> <li>For owhen glove diverses typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove motel. Therefore, the generation glove (for use and the orgeneration of the task. Therefore, glove selection should always be taken into account to the expect doctex the permeation efficiency of the glove thickness is not necessarily a good predictor by glove dischripting on the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:</li> <li>Thinker gloves (top to 3m or nor roles) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abre</li></ul>		frequency and duration of contact,
<ul> <li>. deteriny</li> <li>. deteriny</li> <li>Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).</li> <li>. When onplotinged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.</li> <li>. Some glove opymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.</li> <li>. Contaminated gloves should be replaced.</li> <li>Ras defined in ASTM F739-96 in any application, gloves are rated as:</li> <li>. Excellent when breakthrough time &gt; 480 min</li> <li>. 6 codd when breakthorough time &gt; 620 min</li> <li>. Fair when breakthorough time &gt; 420 min</li> <li>. Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be based on consistering on the exact composition of the glove material. Therefore, glove selection should always be trade trade in any application of the stark trough times.</li> <li>Clove thickness may also vary depending on the glove maturaturer, the glove type and the glove model. Therefore, the manufacture: technical datas should always be trade into account of the most apportate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required through time.</li> <li>Clove since only likely to glove should be required where a high degree of manual destript is a chemical, as there gloves must not not 0.1 mm or less) may be required where a high degree of manual destript is needed. However, these gloves are only likely to give should always be required where a high degree of manual destript is accomplete.</li> <li>Thinner gloves (glova 0.1 mm or less) may be required where a high degree of manual destretily is need</li></ul>		chemical resistance of glove material,
Select ploves tested to a relevant standard (e.g. Europe EN 374, US F739, ASN25 2161.1 or national equivalent).         When prolonge of requently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended.         • When only bief contact is expected, glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN25 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 480 min         • Good whan breakthrough time > 20 min         • For owhen glove mile digorades         For general applications, glove with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the tax requirements and knowledged or breakthrough times.         Glove thickness may also vary depending on the glove manual charger is medded.         It should be emphasised that glove thickness that in concount to ensure selection of the most appropriate glove for the task.         Note:       Depending on the activity being conducted, gloves of varying thickness may be required thore specific thesed. However,		· glove thickness and
• When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • When only brief contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • Some glow ophymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.           • Contaminated gloves should be replaced.           As defined in ASTM F-739-96 in any application, gloves are rated as:           • Excellent when breakthrough time > 20 min           • Fair when breakthrough time > 20 min           • Fair when breakthrough time > 20 min           • Hore when gloves should be replaced.           Kost ophymer types are degrades           For greeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           It should be emphasised their glove will be dependent on the exact composition of the glove material degrades           For greeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           It should be seased on consideration of the task requirements and knowledge of breakthrough times.           Glove thickness may also vary depending on the activity depending on the activity dependent on the exact composition of the glove for the task.           Note: Depending on the activity depending on the activit		· dexterity
• When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • When only brief contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.           • Some glow ophymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.           • Contaminated gloves should be replaced.           As defined in ASTM F-739-96 in any application, gloves are rated as:           • Excellent when breakthrough time > 20 min           • Fair when breakthrough time > 20 min           • Fair when breakthrough time > 20 min           • Hore when gloves should be replaced.           Kost ophymer types are degrades           For greeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           It should be emphasised their glove will be dependent on the exact composition of the glove material degrades           For greeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.           It should be seased on consideration of the task requirements and knowledge of breakthrough times.           Glove thickness may also vary depending on the activity depending on the activity dependent on the exact composition of the glove for the task.           Note: Depending on the activity depending on the activit		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Por own glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mite abstrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove product of or the task.         Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         • Thinker gloves (dow to 0.1 mm or less) may be required where a high degree of manual detectry is needed. However, these gloves are not practice paternal.         • Stoke must only be worn on clean hands. After using gloves, hands should hove should normally be just for single use applications, the disposed of a non-perfurmed molituriser is recommended.         •		
• When only birle contact is expected, a glove with a protection class of a higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 21611.0.1 or national equivalent) is recommended.         • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         • Contaminated gloves should be replaced.         As defined in ASTM 7-739-96 in any application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Poor when glove material gloves is not necessarily a good predictor of glove resistance to a specific chemical, as the premeation efficiency of the glove mit a discretistic digreds         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove takichness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mills degreades         Glove thickness may also vary depending on the glove multicuturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account on most progenitic glove tor the task. Note: Depending on the active bord und normally be just for single use applications, the discrete day movement and three is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Glove thickness may also could normally be just for single use applications, the discrete day move due normally be just for single use applications, the discrete day mover a materials for protection against undissolved, day solids, wh		
according to EN 374, ASN/2S 2161.10.1 or national equivalent) is recommended.         Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         Contaminated gloves should be replaced.         As defined in ASTM 7-739-96 in any application, gloves are rated as:         Excellent when breakthrough time > 20 min         Fair when breakthrough time > 20 min         Foor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the take requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove thick tasks. For example:         Thinner gloves (by to 10.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of a non-perfutued during the should hore is a perfective a second the constant as the requirements.         Thinner gloves (by to 3 mm or nes) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give should hore polymers are suitable as glove materials for protection against undissolved, dry solids, where a brassive particles are not present.		
• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.       • Contaminated gloves should be replaced.         • As defined in ASTM F-739-06 in any application, gloves are rated as:       • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min       • Fair when breakthrough time > 20 min         • Poor when glove matchild degrades       • For orgeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Clove thickness may also vary depending on the glove manufacturer, the glove byee and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.         Note: Depending on the activity being conducted, gloves of varying thickness may also vary depending loves are not ylikely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (down to 1.1 mm or less) may be required where a high degree of manual detxetty is needed.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • bidy/nit/ ubbritit		
Important       Important         Body protection       See Other protection below         Important       See Other protection below		
• Contaminated gloves should be replaced.         As defined in ASTM F-739-96 is may application, gloves are rated as:         • Excellent when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the solve duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential.         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfunded missuriser is recommended.         • Thicker gloves (up to 3 mm or more) may be required where there is a diventials for protection against undissolved, dry solids, where abraive particles are not present.         • Thinker gloves (up to 1 mor clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfunded m		
As defined in ASTM F-739-96 in any application, gloves are rated as: <ul><li>Excellent when breakthrough time &gt; 480 min</li><li>Good when breakthrough time &gt; 20 min</li><li>Fair when breakthrough time &gt; 20 min</li><li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li><li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model.</li><li>Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li><li>Glove thickness may also vary depending on the glove manufacturer, the glove bye and the glove model.</li><li>Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:  <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves so or on chean hands. After using gloves, hands should be washed and dried thoroughly. Application of a          non-perfumed moisturiser is recommended.</li><li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids,          where abrasive particles are not present.</li><li> polychloroprene.          huiry rubber.          built rubb</li></ul></li></ul>		
<ul> <li>Excellent when breakthrough time &gt; 480 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>Por when glove material degrades</li> <li>For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exat composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the glove model casks. For example:</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brais on or pucture potential</li> <li>Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrais apply up to indice.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> <li>Body protection</li> <li>See Other protection below</li> <li>Other protection</li> <li>Baring cream.</li> <li>Skin cleansing cream.</li> </ul>		•
• Good when breakthrough time > 20 min         • Fair when breakthrough time < 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily agood predictor of glove material. Therefore, glove selection should also be based on consideration of the ask requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most apporting topice for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required on specific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsoin or puncture potential.         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present.         • polychloroprene.       • bityly rubber.         • hight roubber.       • butyly rub		
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mile be dependent on the exact composition of the task.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.</li> <li>Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:</li> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>butyl rubber.</li></ul>		
<ul> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.</li> <li>It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.</li> <li>Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves smust only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> </ul> </li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         <ul> <li>polychiloroprene.</li> <li>hittir tubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li> <li>buyl rubber.</li></ul></li></ul>		-
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to .1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterit, is needed. However, these gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>buty furbher.</li> <li>b</li></ul>		Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on considering of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: •Thinner gloves (down to 0.1 mor of less) may be required where a high degree of manual destript is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. •Thicker gloves (pu to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential.         Glove thickness       Glove thickness is not necessarily a glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • hittile rubber. • looking under the event composition of the event composition of the glove should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below       • Overalls. • P.V/C apron. • P.V/C apron. • P.V/C apron. • P.V/C apron. • Skin cleansing cream. • Skin cleansing cream.		Poor when glove material degrades
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextretly is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • buly rubber. • buly cloride. Gloves should be examined for wear and/ or degradation constantly.Body protectionSee Other protection belowCher protection· Overalls. · Parrier. · buly rubber. · buly cloride. · Doveralls. · Polycal parrier. · buly cloride. · Barrier cream. · Skin cleansing cream.		For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.
should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a              non-perfumed moisturiser is recommended.              Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids,              where abrasive particles are not present.              byly/nbloride.              Gloves should be examined for wear and/ or degradation constantly.           Body protection         See Other protection below           Other protection         Barrier cream              Skin cleansing cream.</li></ul></li></ul>		It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsion or puncture potential</li> <li>Gloves must only be wom on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>butyl</li></ul>		permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection
Imanufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul><li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li><li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li><li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li><li>butyl rubber.</li><li>butyl ruber.</li><li>butyl ruber.</li><li>butyl ruber.</li><li>butyl ruber.</li><li>butyl rubber.</li><li>butyl ruber.</li><li>butyl ru</li></ul></li></ul>		should also be based on consideration of the task requirements and knowledge of breakthrough times.
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>butyl ru</li></ul>		Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the
<ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         <ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.             <ul> <li>polychloroprene.</li> <li>hittile rubber.</li> <li>butyf rubber.</li> <li>butyf rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> </li> <li>Body protection         <ul> <li>See Other protection below</li> <li>Other protection</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul> </li> </ul></li></ul>		manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubbr.         • butyl rubbr.		Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • polychloroprene.       • nitrile rubber.         • butyl rubber.       • fluorocaoutchouc.         • polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • P.V.C apron.         • Barrier cream.       • Skin cleansing cream.		
where abrasive particles are not present.         polychloroprene.         nitrile rubber.         butyl rubber.         fluorocaoutchouc.         polycyinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below            • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
i       polychloroprene.         nitrile rubber.       butyl rubber.         butyl rubber.       fluorocaoutchouc.         polycinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>Overalls.</li> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
• nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing cream.		
Image: butyl rubber.       Huorocaoutchouc.		
Image: Polyvinyl chloride.       Polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection          • Overalls.         • P.V.C apron.         • Barrier cream.         • Skin cleansing		
Image: Polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Image: Body protection       See Other protection below         Image: Other protection       • Overalls.         • P.V.C apron.       • Barrier cream.         • Skin cleansing cream.       • Skin cleansing cream.		
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Other protection <ul> <li>Overalls.</li> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
Body protection       See Other protection below         Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>	Body protection	See Other protection below
Other protection <ul> <li>P.V.C apron.</li> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		▶ Overalls.
Other protection <ul> <li>Barrier cream.</li> <li>Skin cleansing cream.</li> </ul>		
<ul> <li>Skin cleansing cream.</li> </ul>	Other protection	·
		5
		-,

#### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(AII classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

. The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data,

Part Number: **OR914205** Version No: **2.2** 

#### 6,6-Dimethyl-5,7-dioxaspiro[2.5]octane-4,8-dione

and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

• Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

• Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

 $\cdot$  Use approved positive flow mask if significant quantities of dust becomes airborne.

 $\cdot$  Try to avoid creating dust conditions.

## **SECTION 9** Physical and chemical properties

## Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	69-73	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

#### **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

#### **SECTION 11 Toxicological information**

#### Information on toxicological effects

Inhaled The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives

Issue Date: 05/07/2023 Print Date: 05/07/2023

#### 6,6-Dimethyl-5,7-dioxaspiro[2.5]octane-4,8-dione

	using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.
Ingestion	The material has <b>NOT</b> been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	This material can cause eye irritation and damage in some persons.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

6,6-Dimethyl- 5,7-dioxaspiro[2.5]octane- 4,8-dione	TOXICITY Not Available	IRRITATION Not Available
Legend:	1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances	

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	¥	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	*
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
Legend: 🔀 – Data either not available or does not fill the criteria for classification			

Data available to make classification

## **SECTION 12 Ecological information**

Toxicity

6,6-Dimethyl-	Endpoint	Test Duration (hr)	Species	Value	Source
5,7-dioxaspiro[2.5]octane- 4,8-dione	Not Available	Not Available	Not Available	Not Available	Not Available
Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data				

## Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
	No Data available for all ingredients	No Data available for all ingredients	

#### **Bioaccumulative potential**

Ingredient	Bioaccumulation	
	No Data available for all ingredients	

## Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

#### **SECTION 13 Disposal considerations**

	Recycle wherever possible or consult manufacturer for recycling options.
Product / Packaging	<ul> <li>Consult State Land Waste Management Authority for disposal.</li> </ul>
disposal	<ul> <li>Bury residue in an authorised landfill.</li> </ul>
	Recycle containers if possible, or dispose of in an authorised landfill.

#### **SECTION 14 Transport information**

Labels Required			
Marine Pollutant	NO		
Land transport (ADR): NO	OT REGULATED FOR TRANSPORT OF DANGEROUS GOODS		
Air transport (ICAO-IATA	/ DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS		
Sea transport (IMDG-Cod	Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS		
Inland waterways transpo	ort (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS		
Transport in bulk according to Annex II of MARPOL and the IBC code Not Applicable			
Transport in bulk in acco	Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code		
Product name	Group		
Transport in bulk in accordance with the IGC Code			
Product name	Ship Type		
SECTION 15 Regulatory information			

## Safety, health and environmental regulations / legislation specific for the substance or mixture

## **National Inventory Status**

National Inventory	Status	
Australia - AIIC / Australia Non-Industrial Use	Not Available	
Canada - DSL	Not Available	
Canada - NDSL	Not Available	
China - IECSC	Not Available	
Europe - EINEC / ELINCS / NLP	Not Available	
Japan - ENCS	Not Available	
Korea - KECI	Not Available	
New Zealand - NZIoC	Not Available	
Philippines - PICCS	Not Available	
USA - TSCA	Not Available	
Taiwan - TCSI	Not Available	
Mexico - INSQ	Not Available	
Vietnam - NCI	Not Available	
Russia - FBEPH	Not Available	
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.	

#### **SECTION 16 Other information**

Revision Date	05/07/2023
Initial Date	05/07/2023

#### **SDS Version Summary**

Version	Date of Update	Sections Updated
1.2	05/07/2023	Toxicological information - Acute Health (eye), Physical and chemical properties - Appearance, CAS Number, Hazards identification - Classification, Exposure controls / personal protection - Exposure Standard, Firefighting measures - Fire Fighter (fire/explosion hazard), First Aid measures - First Aid (eye), Handling and storage - Handling Procedure, Composition / information on ingredients - Ingredients, Korean MSDS Number, Exposure controls / personal protection - Personal Protection (other), Exposure controls / personal protection - Personal Protection (eye), Accidental release measures - Spills (major), Accidental release measures - Spills (minor), Handling and storage - Storage (storage incompatibility), Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms

#### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

#### **Definitions and abbreviations**

PC - TWA: Permissible Concentration-Time Weighted Average

PC - STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit.

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

#### Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Specific Target Organ	Expert judgement

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure	
Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3 , H335		
Skin Corrosion/Irritation Category 2, H315	Expert judgement	
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement	

Powered by AuthorITe, from Chemwatch.