

Apollo Scientific

Part Number: **PC450274** Version No: **1.1** Safety Data Sheet (Conforms to Annex II of REACH (1907/2006) - Regulation 2020/878) Chemwatch Hazard Alert Code: 2 Issue Date: 18/06/2024 Print Date: 18/06/2024 S.REACH.GB-NIR.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

1.1. Product Identifier

Product name	1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid		
Synonyms	Not Available		
Chemical formula	C15-H17-F-N4-O3		
Other means of identification	Not Available		
CAS number	74011-58-8*		
EC number	961-175-5*		

1.2. Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Use according to manufacturer's directions.	
Uses advised against	No specific uses advised against are identified.	

1.3. Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific		
Address	Whitefield Road, Bredbury SK62QR United Kingdom		
Telephone	01614060505		
Fax	0161 406 0506		
Website	http://www.apolloscientific.co.uk/		
Email	sales@apolloscientific.co.uk		

1.4. Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

SECTION 2 Hazards identification

2.1. Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments ^[1]	H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2, H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3
Legend:	1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

2.2. Label elements

Hazard pictogram(s)



1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid

Signal word Warning

Hazard statement(s)	
H315	Causes skin irritation.
H319	Causes serious eye irritation.
H335	May cause respiratory irritation.

Supplementary statement(s)

Not Applicable

Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.	
P261 Avoid breathing dust/fumes.		
P280	Wear protective gloves, protective clothing, eye protection and face protection.	
P264	Wash all exposed external body areas thoroughly after handling.	

Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.			
P312	Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.			
P337+P313	If eye irritation persists: Get medical advice/attention.			
P302+P352	IF ON SKIN: Wash with plenty of water.			
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.			
P332+P313	If skin irritation occurs: Get medical advice/attention.			
P362+P364	Take off contaminated clothing and wash it before reuse.			

Precautionary statement(s) Storage

P405	Store locked up.
P403+P233	Store in a well-ventilated place. Keep container tightly closed.

Precautionary statement(s) Disposal

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

Material contains 1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid.

2.3. Other hazards

REACH - Art.57-59: The mixture does not contain Substances of Very High Concern (SVHC) at the SDS print date.

SECTION 3 Composition / information on ingredients

P501

3.1.Substances					
1. CAS No 2.EC No 3.Index No 4.REACH No	% [weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M- Factor	Nanoform Particle Characteristics
1. 74011-58-8* 2.961-175-5* 3.Not Available 4.Not Available	100	<u>1-Ethyl-6-fluoro-1,4-dihydro-</u> <u>4-oxo-7-(1-piperazinyl)-1,8-</u> naphthyridine-3-carboxylic acid	Skin Corrosion/Irritation Category 2, Serious Eye Damage/Eye Irritation Category 2, Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3; H315, H319, H335 ^[1]	Not Available Acute M factor: Not Available Chronic M factor: Not Available	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

3.2.Mixtures

See 'Information on ingredients' in section 3.1

SECTION 4 First aid measures

4.1. Description of first aid measures

Eye Contact

- If this product comes in contact with the eyes: • Wash out immediately with fresh running water.
 - Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids.

	 Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel. 	
Skin Contact	If skin contact occurs: Immediately remove all contaminated clothing, including footwear. Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation. 	
Inhalation	 If fumes or combustion products are inhaled remove from contaminated area. Lay patient down. Keep warm and rested. Prostheses such as false teeth, which may block airway, should be removed, where possible, prior to initiating first aid procedures. Apply artificial respiration if not breathing, preferably with a demand valve resuscitator, bag-valve mask device, or pocket mask as trained. Perform CPR if necessary. Transport to hospital, or doctor, without delay. 	
Ingestion	 Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor. 	
4.2 Most important symptoms and effects, both acute and delayed		

See Section 11

4.3. Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

5.1. Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
 Use extinguishing media suitable for surrounding area.

5.2. Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.

5.3. Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves in the event of a fire. Prevent, by any means available, spillage from entering drains or water courses. Use fire fighting procedures suitable for surrounding area. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 Non combustible. Not considered a significant fire risk, however containers may burn. May emit poisonous fumes. May emit corrosive fumes.

SECTION 6 Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures See section 8

6.2. Environmental precautions

See section 12

6.3. Methods and material for containment and cleaning up

Minor Spills	 Clean up all spills immediately. Avoid breathing dust and contact with skin and eyes. Wear protective clothing, gloves, safety glasses and dust respirator. Use dry clean up procedures and avoid generating dust. Sweep up, shovel up or Vacuum up (consider explosion-proof machines designed to be grounded during storage and use). Place spilled material in clean, dry, sealable, labelled container.
Major Spills	 Moderate hazard. CAUTION: Advise personnel in area. Alert Emergency Services and tell them location and nature of hazard. Control personal contact by wearing protective clothing. Prevent, by any means available, spillage from entering drains or water courses. Recover product wherever possible. IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal. ALWAYS: Wash area down with large amounts of water and prevent runoff into drains. If contamination of drains or waterways occurs, advise Emergency Services.
	Continued

1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid

6.4. Reference to other sections

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

7.1. Precautions for safe hand	ing
Safe handling	 Avoid all personal contact, including inhalation. Wear protective clothing when risk of exposure occurs. Use in a well-ventilated area. Prevent concentration in hollows and sumps. DO NOT enter confined spaces until atmosphere has been checked. DO NOT allow material to contact humans, exposed food or food utensils. Avoid contact with incompatible materials. When handling, DO NOT eat, drink or smoke. Keep containers securely sealed when not in use. Avoid physical damage to containers. Always wash hands with scap and water after handling. Work clothes should be laundered separately. Launder contaminated clothing before re-use. Use good occupational work practice. Observe manufacturer's storage and handling recommendations contained within this SDS. Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.
Fire and explosion protection	See section 5
Other information	 Store in original containers. Keep containers securely sealed. Store in a cool, dry area protected from environmental extremes. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS. For major quantities: Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams). Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.

7.2. Conditions for safe storage, including any incompatibilities

Suitable container	 Polyethylene or polypropylene container. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	None known
Hazard categories in accordance with Regulation (EC) No 2012/18/EU (Seveso III)	Not Available
Qualifying quantity (tonnes) of dangerous substances as referred to in Article 3(10) for the application of	Not Available

7.3. Specific end use(s)

See section 1.2

SECTION 8 Exposure controls / personal protection

8.1. Control parameters

Ingredient	DNELs Exposure Pattern Worker	PNECs Compartment
Not Available	Not Available	Not Available

* Values for General Population

Occupational Exposure Limits (OEL)

INGREDIENT DATA

Source	Ingredient	Material name	TWA	STEL	Peak	Notes
Not Available						

Not Applicable

Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
1-Ethyl-6-fluoro-1,4-dihydro-4- oxo-7-(1-piperazinyl)-1,8- naphthyridine-3-carboxylic acid	Not Available	Not Available	Not Available

 $1- Ethyl-6-fluoro-1, 4-dihydro-4-oxo-7-(1-piperazinyl)-1, 8-naphthyridine-3-carboxylic\ acid$

Ingredient	Original IDLH	Revised IDLH	
1-Ethyl-6-fluoro-1,4-dihydro-4- oxo-7-(1-piperazinyl)-1,8- naphthyridine-3-carboxylic acid	Not Available	Not Available	
Occupational Exposure Banding	3		
Ingredient	Occupational Exposure Band Rating Occupational Exposure Band Limit		
1-Ethyl-6-fluoro-1,4-dihydro-4- oxo-7-(1-piperazinyl)-1,8- naphthyridine-3-carboxylic acid	E ≤ 0.01 mg/m ³		
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposure band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.		

8.2. Exposure controls

	Engineering controls are used to remove a hazard or place can be highly effective in protecting workers and will typical The basic types of engineering controls are: Process controls which involve changing the way a job acti Enclosure and/or isolation of emission source which keeps strategically 'adds' and 'removes' air in the work environme design of a ventilation system must match the particular pro Employers may need to use multiple types of controls to pr • Local exhaust ventilation is required where solids are h certain proportion will be powdered by mutual friction. • If in spite of local exhaust an adverse concentration of Such protection might consist of: (a): particle dust respirators, if necessary, combined with ar (b): filter respirators with absorption cartridge or canister of (c): fresh-air hoods or masks. Air contaminants generated in the workplace possess varyi circulating air required to effectively remove the contaminant	ly be independent of worker interact vity or process is done to reduce the a selected hazard 'physically' away nt. Ventilation can remove or dilute is bocess and chemical or contaminant event employee overexposure. andled as powders or crystals; even the substance in air could occur, res a absorption cartridge; the right type; ng 'escape' velocities which, in turn	tions to provide this h e risk. from the worker and an air contaminant if d in use. n when particulates an spiratory protection sh	igh level of protection. ventilation that designed properly. The re relatively large, a rould be considered.
	Type of Contaminant:			Air Speed:
8.2.1. Appropriate engineering controls	direct spray, spray painting in shallow booths, drum filling, generation into zone of rapid air motion)	conveyer loading, crusher dusts, ga	as discharge (active	1-2.5 m/s (200-500 f/min.)
	grinding, abrasive blasting, tumbling, high speed wheel ge of very high rapid air motion).	enerated dusts (released at high initi	ial velocity into zone	2.5-10 m/s (500-2000 f/min.)
	Within each range the appropriate value depends on:			
	Lower end of the range	Upper end of the range		
	1: Room air currents minimal or favourable to capture	1: Disturbing room air currents		
	2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity		
	3: Intermittent, low production.	3: High production, heavy use		
	4: Large hood or large air mass in motion	4: Small hood-local control only	1	
Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity gr decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction p adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for ex- a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical multiplied by factors of 10 or more when extraction systems are installed or used.				
8.2.2. Individual protection measures, such as personal protective equipment				
Eye and face protection	 Safety glasses with side shields. Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent] Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59]. 			
Skin protection	See Hand protection below			
Hands/feet protection	The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.			

 ohenical resistance of glove material, glove bickness and - dxxirtiy Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/AZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/ASZ 2161.1 0 or national equivalent) is recommended. When only bief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/ASZ 2161.1 0 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in AS/MF 7-379.6 BM or in - Good when breakthrough time > 480 min - Good when breakthrough time > 480 min - Fair when breakthrough time > 20 min - Boro when greades For greant applications, gloves with a thickness typically greater than 0.35 mm, are recommended. I should be emphased that gloves thoreas in other cospanity a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Note: Depending on the activity being conducted, doves of varing doves of varing the organizations. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these gloves are nonly likely tip being conducted, doves of varing doves of varing thores may be required where a high degree dor gaminate data. For example: - Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. wher		Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: · frequency and duration of contact,
• deteriny. Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent). • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to ES 74, AS/N2S 2161.1 or national equivalent) is recommended. • When only brief contact is expected, a glowe with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to ES N374, AS/N2S 2161.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-68 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • For when glowe material digrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove bickness is not necessarily agood predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exat composition of the glove material. Therefore, glove selection should also be based on consideration of the take requirements and knowledge of breakthrough times. Glove tickness may also vary depending on the glove material cas when ded. Therefore, glove selection and would normally be just for single use applications, then disposed of. • Thistor gloves (low 10 mm or neon) may be required where there is a mechanic		chemical resistance of glove material,
Select gives tested to a relevant standard (e.g. Europe EN 374, US F732 161 1.0 r antional equivalent). • When protoged or frequently repeated contact may occur, a give with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161 1.0 1 or national equivalent) is recommended. • When only build contact is expected, a give with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN25 2161 1.0 1 or national equivalent) is recommended. • Other and we polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • A defined in ASTM F739-96 in any application, gloves are rated as: • Contaminated gloves should be replaced. • A defined in ASTM F739-96 in any application, gloves are rated as: • Condition breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • For general applications, gloves with a dependent on the exact composition of the glove metal. • For general applications, gloves be taken into account to ensure selection of the glove mathetic gloves • Gove thickness may be taken into account to ensure selection of the glove mathetic gloves are not present and y gloves of varying thickness may be required where a high degree of manual dextret five endered. • To be the gloves (bot 7 mm or res) may be required where a high degree of manual dextret five endered of rese		5
• When prolonged on frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 220 minutes according to EX374, ASN25 2161:10.1 or national equivalent) is recommended. • When only birle contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EX374, ASN25 2161:10.1 or national equivalent) is recommended. • Containnated gloves should be replaced. As defined in ASTM F739-96 in any application, gloves are rated as: • Containnated gloves should be replaced. As defined in ASTM F739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Foor when gloves whit a thickness typically greater than 0.35 mm, are recommended. • Thank of the emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove wills a the endered on the exact composition of the glove material egrades • Glove thickness may also xary depending on the active digives and the glove material egrades • For general egrications, gloves with a thickness typically greater than 0.35 mm, are recommended. • It is though the preduction of the stark requirements and knowledge of breakthrough times. • For general egrications, thereaktrough times is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation difficiency of the glove will always be taken into account to ensure selection of the most approprinte glove of the task		
• When only brief contact is expected, a glove with a protection class of 30 ingher (breakthrough time greater than 60 minutes according to EN 374, AS/N25 2161 101 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • Scode glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • Scode when breakthrough time > 20 min • Fair When breakthrough time > 20 min • Fair When breakthrough time > 20 min • Fair When breakthrough time > 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove multade the equation of the glove material degrades Clove thickness may also vary depending on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection the most appropriate glove for the task. Note: Expending on the activity being contauted, gloves of varying thickness may also chype and the glove model. Therefore, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinker		When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than
 Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min For when glove material degrades For other alapplication, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove minufacture, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinker gloves glove that on any be required where there is a mechanical (as well as a chemical) risk evel where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Glove structure potential Glove thickness and present. Picychoroprene. Nither othersen. polychioroprene. Nithire rubber.		When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to
 Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min For when glove material degrades Poor when glove material degrades For yment applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily ag good predictor of glove resistance to a specific chemical, as the permeation of the glove ymethal. Perevention officiency of the glove will be dependent on the exact composition of the glove will be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the emanufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thincer gloves (down to 0.1 mor or less) may be required where a high degree of manual deterty is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thincer gloves (down to 0.1 mor or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. bityli rubber. bityli rubber. bityli ru		· Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term
As defined in As ^T M F-739-96 in any application, gloves are rated as: - Excellent when breakthrough time > 20 min - Excellent when breakthrough time > 20 min - Good when breakthrough time > 20 min - Por when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for single use applications, then disposed of. - Thicker gloves (up to 0.1 mm or less) may be required where a high degrae of manual destrity is needed. However, these gloves are only likely to give should always be taken into account to ensure selection of the rosing use applications, then disposed of. - Thicker gloves (up to 0.3 mm or more) may be required where a high degrae of manual destrity is needed. However, these gloves sure only be sense that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. - polychinoprene. - initir oubber.		
• Excellent when breakthrough time > 400 min • Good when breakthrough time < 20 min • Poor when glove material degrades • Poor when glove material degrades • Poor when glove material degrades • Bood when breakthrough time < 20 min • Poor when glove material degrades • Poor when glove material degrades • Bood when breakthrough time < 20 min • Poor when glove material degrades • Good when breakthrough time < 20 min • Poor when glove material degrades • Good when breakthrough time < 20 min • Poor when glove material tegrades • Good when breakthrough time < 20 min • Poor when glove material tegrades • Good when breakthrough time < 20 min • Bood when breakthrough time < 400 min be xathrough times • Glove sticker show and tegrades • Thicker gloves glove show tho 2 min nor tegrades • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncure potential		
• Good when breakthrough time < 20 min • Fair when breakthrough time < 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consisted that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consistents and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove moder. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted. gloves of varying thickness may be required there a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thinker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to gives bot duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are not protection advoid normally be just for single use applications, then disposed of. • Thicker gloves use on the activity bend duration protection adjust for single use applications, the disposed of. • Thicker gloves use are not present. <th></th> <th></th>		
 Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextertly is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where a nechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on chean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moistivers is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychiloroprene. hittle rubber. buyly rubber. buyly rubber. buyly rubber. buyly rubber. <li< th=""><th></th><th></th></li<>		
• Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ansure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these gloves are only likely to glive short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical)) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles are not present. • polychorprene. • fluorcoautchouc. • polychorprene. • fluor		
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. • polychioroprene. • polychioroprene		
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove soft any ing thickness may be required the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give shout duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. boly (hubber: bitly (hub		
be based on consideration of the task requirements and knowledge of breakthrough times. Give thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. fluorcoautchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below		It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the
technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual deketrity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. polychloroprene. nitrile rubber. polychloroprene. nitrile rubber. gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • hitrile rubber: • butyl rubber: • butyl rubber: • fluorocaoutchouc. • polychloroprene. • fluorocaoutchouc. • polychloroprene. • butyl rubber: • Doveralls. • PV.C apron. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream.		
only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. b polychloroprene. h nitrile rubber. b butyl rubber. b coveralls.		Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:
or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrile rubber. • hitrile rubber. • butyl rubber. • filtorocaoutchouc. • polychloroprene. • filtorocaoutchouc. • polycinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • Overalls. • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream.		only likely to give short duration protection and would normally be just for single use applications, then disposed of.
moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • butyl rubber. • butyl rubber. • fluorocaoutchouc. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. 		
Image: Polychloroprene. Image: Nitrile rubber. Image: Image: Nitrile rubber. Image: Nitrile rubber. Image: Image: Image: Nitrile rubber. Image: Nitrile rubber. Image:		
Image: Protection Image: Protection below Body protection See Other protection below Image: Protection Image: Protection below Image: Prote		
Image: butyl rubber. Image: fluorocaoutchouc. Image: fluorocaoutc		
Image: Polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Image: Body protection See Other protection below Image: Polycing protection Image: Polycing protection		▶ butyl rubber.
Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below Other protection • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		▶ fluorocaoutchouc.
Body protection See Other protection below Other protection • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream. • Skin cleansing cream.		▶ polyvinyl chloride.
Other protection Overalls. P.V.C apron. Barrier cream. Skin cleansing cream. 		Gloves should be examined for wear and/ or degradation constantly.
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 	Body protection	See Other protection below
Other protection • Barrier cream. • Skin cleansing cream.		► Overalls.
Other protection • Barrier cream. • Skin cleansing cream.		▶ P.V.C apron.
	Other protection	
► Eye wash unit.		
		► Eye wash unit.

Respiratory protection

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

· Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

8.2.3. Environmental exposure controls

See section 12

SECTION 9 Physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	225-229	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available
Nanoform Solubility	Not Available	Nanoform Particle Characteristics	Not Available
Particle Size	Not Available		

9.2. Other information

Not Available

SECTION 10 Stability and reactivity

10.1.Reactivity	See section 7.2
10.2. Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
10.3. Possibility of hazardous reactions	See section 7.2
10.4. Conditions to avoid	See section 7.2
10.5. Incompatible materials	See section 7.2
10.6. Hazardous decomposition products	See section 5.3

SECTION 11 Toxicological information

11.1. Information on hazard classes as defined in Regulation (EC) No 1272/2008

Inhaled	The material can cause respiratory irritation in some persons. The body's response to such irritation can cause further lung damage. Persons with impaired respiratory function, airway diseases and conditions such as emphysema or chronic bronchitis, may incur further disability if excessive concentrations of particulate are inhaled. If prior damage to the circulatory or nervous systems has occurred or if kidney damage has been sustained, proper screenings should be conducted on individuals who may be exposed to further risk if handling and use of the material result in excessive exposures.
Ingestion	The material has NOT been classified by EC Directives or other classification systems as 'harmful by ingestion'. This is because of the lack of corroborating animal or human evidence.
Skin Contact	This material can cause inflammation of the skin on contact in some persons. The material may accentuate any pre-existing dermatitis condition Skin contact is not thought to have harmful health effects (as classified under EC Directives); the material may still produce health damage following entry through wounds, lesions or abrasions. Open cuts, abraded or irritated skin should not be exposed to this material Entry into the blood-stream, through, for example, cuts, abrasions or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected.
Eye	This material can cause eye irritation and damage in some persons.

Long-term exposure to respiratory irritants may result in airways disease, involving difficulty breathing and related whole-body problems. Chronic Substance accumulation, in the human body, may occur and may cause some concern following repeated or long-term occupational exposure 1-Ethyl-6-fluoro-1,4-dihydro-TOXICITY IRRITATION 4-oxo-7-(1-piperazinyl)-1,8naphthyridine-3-carboxylic Not Available Oral (Mouse) LD50; >4000 mg/kg^[2] acid Legend: 1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances Asthma-like symptoms may continue for months or even years after exposure to the material ends. This may be due to a non-allergic condition known as reactive airways dysfunction syndrome (RADS) which can occur after exposure to high levels of highly irritating compound. Main criteria for diagnosing RADS include the absence of previous airways disease in a non-atopic individual, with sudden onset 1-Ethyl-6-fluoro-1,4-dihydroof persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. Other criteria for diagnosis of RADS 4-oxo-7-(1-piperazinyl)-1,8include a reversible airflow pattern on lung function tests, moderate to severe bronchial hyperreactivity on methacholine challenge testing, naphthyridine-3-carboxylic and the lack of minimal lymphocytic inflammation, without eosinophilia. RADS (or asthma) following an irritating inhalation is an infrequent acid disorder with rates related to the concentration of and duration of exposure to the irritating substance. On the other hand, industrial bronchitis is a disorder that occurs as a result of exposure due to high concentrations of irritating substance (often particles) and is completely reversible after exposure ceases. The disorder is characterized by difficulty breathing, cough and mucus production. × × Acute Toxicity Carcinogenicity Skin Irritation/Corrosion -Reproductivity × Serious Eye -STOT - Single Exposure ~ Damage/Irritation **Respiratory or Skin** X × STOT - Repeated Exposure sensitisation × × Mutagenicity Aspiration Hazard 🗙 – Data either not available or does not fill the criteria for classification Legend: Data available to make classification

11.2 Information on other hazards

11.2.1. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

11.2.2. Other information

See Section 11.1

SECTION 12 Ecological information

12.1. Toxicity

1-Ethyl-6-fluoro-1,4-dihydro-					
4-oxo-7-(1-piperazinyl)-1,8-	Endpoint	Test Duration (hr)	Species	Value	Source
naphthyridine-3-carboxylic acid	Not Available	Not Available	Not Available	Not Available	Not Available
aciu					
Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity 4. US EPA,				
-	Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI				
	(Japan) - Bioconcentration Data 8. Vendor Data				

DO NOT discharge into sewer or waterways.

12.2. Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air	
	No Data available for all ingredients	No Data available for all ingredients	

12.3. Bioaccumulative potential

Ingredient	Bioaccumulation
	No Data available for all ingredients

12.4. Mobility in soil

Ingredient	Mobility	
	No Data available for all ingredients	

12.5. Results of PBT and vPvB assessment

	Р	В	т
Relevant available data	Not Available	Not Available	Not Available
PBT	×	×	×
vPvB	×	×	×

Page 9 of 12

No

No

1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid

PBT Criteria fulfilled?

vPvB

12.6. Endocrine disrupting properties

No evidence of endocrine disrupting properties were found in the current literature.

12.7. Other adverse effects

No evidence of ozone depleting properties were found in the current literature.

SECTION 13 Disposal considerations

13.1. Waste treatment methods		
Product / Packaging disposal	 Recycle wherever possible or consult manufacturer for recycling options. Consult State Land Waste Management Authority for disposal. Bury residue in an authorised landfill. Recycle containers if possible, or dispose of in an authorised landfill. 	
Waste treatment options	Not Available	
Sewage disposal options	Not Available	

SECTION 14 Transport information

Labels Required

Marine Pollutant	NO
HAZCHEM	Not Applicable

Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number or ID number	Not Applicable		
14.2. UN proper shipping name	Not Applicable		
14.3. Transport hazard class(es)		Not Applicable Not Applicable	
14.4. Packing group	Not Applicable		
14.5. Environmental hazard	Not Applicable		
14.6. Special precautions for user	Hazard identification (K Classification code Hazard Label Special provisions Limited quantity Tunnel Restriction Code	Not Applicable Not Applicable Not Applicable Not Applicable	

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable			
14.2. UN proper shipping name	Not Applicable			
440 - 44 - 4	ICAO/IATA Class	Not Applicable		
14.3. Transport hazard class(es)	ICAO / IATA Subsidiary Hazard	Not Applicable		
	ERG Code	Not Applicable		
14.4. Packing group	Not Applicable			
14.5. Environmental hazard	Not Applicable			
	Special provisions		Not Applicable	
	Cargo Only Packing Instructions		Not Applicable	
	Cargo Only Maximum Qty / Pack		Not Applicable	
14.6. Special precautions for user	Passenger and Cargo Packing Instructions		Not Applicable	
	Passenger and Cargo Maximum Qty / Pack		Not Applicable	
	Passenger and Cargo Limited Qu	antity Packing Instructions	Not Applicable	
	Passenger and Cargo Limited Maximum Qty / Pack		Not Applicable	

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable		
14.2. UN proper shipping name	Not Applicable		
14.3. Transport hazard class(es)	IMDG ClassNot ApplicableIMDG Subsidiary HazardNot Applicable		
14.4. Packing group	Not Applicable		
14.5 Environmental hazard	Not Applicable		
14.6. Special precautions for user	EMS Number Special provisions Limited Quantities	Not Applicable Not Applicable Not Applicable	

Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

14.1. UN number	Not Applicable	
14.2. UN proper shipping name	Not Applicable	
14.3. Transport hazard class(es)	Not Applicable Not Applicable	
14.4. Packing group	Not Applicable	
14.5. Environmental hazard	Not Applicable	
14.6. Special precautions for user	Classification code	Not Applicable
	Special provisions	Not Applicable
	Limited quantity	Not Applicable
	Equipment required	Not Applicable
	Fire cones number	Not Applicable

14.7. Maritime transport in bulk according to IMO instruments

14.7.1. Transport in bulk according to Annex II of MARPOL and the IBC code Not Applicable

14.7.2. Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
1-Ethyl-6-fluoro-1,4-dihydro-4- oxo-7-(1-piperazinyl)-1,8- naphthyridine-3-carboxylic acid	Not Available

14.7.3. Transport in bulk in accordance with the IGC Code

Product name	Ship Type
1-Ethyl-6-fluoro-1,4-dihydro-4- oxo-7-(1-piperazinyl)-1,8- naphthyridine-3-carboxylic acid	Not Available

SECTION 15 Regulatory information

15.1. Safety, health and environmental regulations / legislation specific for the substance or mixture

1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid is found on the following regulatory lists Not Applicable

Additional Regulatory Information

Not Applicable

This safety data sheet is in compliance with the following EU legislation and its adaptations - as far as applicable - : Directives 98/24/EC, - 92/85/EEC, - 94/33/EC, - 2008/98/EC, - 2010/75/EU; Commission Regulation (EU) 2020/878; Regulation (EC) No 1272/2008 as updated through ATPs.

Information according to 2012/18/EU (Seveso III):

Seveso Category Not Available

15.2. Chemical safety assessment

For further information please look at the Chemical Safety Assessment and Exposure Scenarios prepared by your Supply Chain if available.

National Inventory Status

National Inventory	Status	
Australia - AIIC / Australia Non- Industrial Use	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Canada - DSL	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Canada - NDSL	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
China - IECSC	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Europe - EINEC / ELINCS / NLP	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Japan - ENCS	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Korea - KECI	Yes	
New Zealand - NZIoC	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Philippines - PICCS	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
USA - TSCA	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Taiwan - TCSI	Yes	
Mexico - INSQ	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Vietnam - NCI	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Russia - FBEPH	No (1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-(1-piperazinyl)-1,8-naphthyridine-3-carboxylic acid)	
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.	

SECTION 16 Other information

Revision Date	18/06/2024
Initial Date	19/06/2024

Full text Risk and Hazard codes

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

- EN 374 Protective gloves against chemicals and micro-organisms
- EN 13832 Footwear protecting against chemicals
- EN 133 Respiratory protective devices

Definitions and abbreviations

- PC TWA: Permissible Concentration-Time Weighted Average
- PC STEL: Permissible Concentration-Short Term Exposure Limit
- IARC: International Agency for Research on Cancer
- ACGIH: American Conference of Governmental Industrial Hygienists
- STEL: Short Term Exposure Limit
- TEEL: Temporary Emergency Exposure Limit。
- IDLH: Immediately Dangerous to Life or Health Concentrations
- ES: Exposure Standard
- OSF: Odour Safety Factor
- NOAEL: No Observed Adverse Effect Level
- LOAEL: Lowest Observed Adverse Effect Level
- TLV: Threshold Limit Value
- LOD: Limit Of Detection
- OTV: Odour Threshold Value
- BCF: BioConcentration Factors
- BEI: Biological Exposure IndexDNEL: Derived No-Effect Level
- PNEC: Predicted no-effect concentration
- AlIC: Australian Inventory of Industrial Chemicals
- DSL: Domestic Substances List
- NDSL: Non-Domestic Substances List
- IECSC: Inventory of Existing Chemical Substance in China
- EINECS: European INventory of Existing Commercial chemical Substances
- ELINCS: European List of Notified Chemical Substances
- NLP: No-Longer Polymers
- ENCS: Existing and New Chemical Substances Inventory
- KECI: Korea Existing Chemicals Inventory
- NZIoC: New Zealand Inventory of Chemicals
- PICCS: Philippine Inventory of Chemicals and Chemical Substances
- TSCA: Toxic Substances Control Act
- TCSI: Taiwan Chemical Substance Inventory
 INSQ: Inventario Nacional de Sustancias Químicas
- NCI: National Chemical Inventory
- FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Skin Corrosion/Irritation Category 2, H315	Expert judgement
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement
Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H335	Expert judgement

Powered by AuthorITe, from Chemwatch.