

Apollo Scientific

Part Number: **PC5973** Version No: **1.2** Safety Data Sheet Chemwatch Hazard Alert Code: 2

Issue Date: **26/05/2023** Print Date: **26/05/2023** S.GHS.GB-NIR.EN

SECTION 1 Identification of the substance / mixture and of the company / undertaking

Product Identifier

Product name	,5-Bis(trifluoromethyl)phenylacetic acid		
Chemical Name	2,5-Bis(trifluoromethyl)phenylacetic acid		
Synonyms	Not Available		
Other means of identification	Not Available		
CAS number	302912-02-3*		

Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
--------------------------	---------------

Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd	
Address	Whitefield Road, Bredbury SK62QR United Kingdom	Whitefield Road Not Available SK6 2QR United Kingdom (NI)	
Telephone	01614060505 +44(0) 161 406 0505		
Fax	0161 406 0506	Not Available	
Website	http://www.apolloscientific.co.uk/	apolloscientific.co.uk	
Email	I sales@apolloscientific.co.uk sales@apolloscientific.co.uk		

Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

SECTION 2 Hazards identification

Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments ^[1]	H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2
Legend:	1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

Label elements

Hazard pictogram(s)	
Signal word	Warning

Hazard statement(s)

H335	May cause respiratory irritation.	
H315	Causes skin irritation.	
H319	Causes serious eye irritation.	

Precautionary statement(s) Prevention

P271	Use only outdoors or in a well-ventilated area.	
P261	Avoid breathing dust/fumes.	
P280	Wear protective gloves, protective clothing, eye protection and face protection.	
P264 Wash all exposed external body areas thoroughly after handling.		

Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.			
P312	Call a POISON CENTER/doctor/physician/first aider/if you feel unwell.			
P337+P313	If eye irritation persists: Get medical advice/attention.			
P302+P352	IF ON SKIN: Wash with plenty of water.			
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.			
P332+P313	If skin irritation occurs: Get medical advice/attention.			
P362+P364	Take off contaminated clothing and wash it before reuse.			

Precautionary statement(s) Storage

P405	Store locked up.	
P403+P233	Store in a well-ventilated place. Keep container tightly closed.	

Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

SECTION 3 Composition / information on ingredients

Substances

CAS No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
Not Available	100	2.5-Bis(trifluoromethyl)phenylacetic acid	Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, Skin Corrosion/Irritation Category 2, Serious Eye Damage/Eye Irritation Category 2; H335, H315, H319 ^[1]	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; * EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

Mixtures

See section above for composition of Substances

SECTION 4 First aid measures

Description of first aid measures

Eye Contact

If this product comes in contact with the eyes:

	 Wash out immediately with fresh running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	 If skin or hair contact occurs: Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 Immediately give a glass of water. First aid is not generally required. If in doubt, contact a Poisons Information Centre or a doctor.

Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.
----------------------	-------------

Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves in the event of a fire. Prevent, by any means available, spillage from entering drains or water courses. Use fire fighting procedures suitable for surrounding area. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 Non combustible. Not considered a significant fire risk, however containers may burn. May emit corrosive fumes.

SECTION 6 Accidental release measures

Personal precautions, protective equipment and emergency procedures

See section 8

Environmental precautions

See section 12

Methods and material for containment and cleaning up

Minor Spills	 Clean up all spills immediately. Avoid breathing dust and contact with skin and eyes. Wear protective clothing, gloves, safety glasses and dust respirator. Use dry clean up procedures and avoid generating dust. Sweep up, shovel up or Vacuum up (consider explosion-proof machines designed to be grounded during storage and use). Place spilled material in clean, dry, sealable, labelled container. 	
Major Spills	Moderate hazard. CAUTION: Advise personnel in area.	

 Alert Emergency Services and tell them location and nature of hazard. Control personal contact by wearing protective clothing.
Prevent, by any means available, spillage from entering drains or water courses.
Recover product wherever possible.
IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.
ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.
If contamination of drains or waterways occurs, advise Emergency Services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

Precautions for safe handling

Safe handling	 Avoid all personal contact, including inhalation. Wear protective clothing when risk of exposure occurs. Use in a well-ventilated area. Prevent concentration in hollows and sumps. DO NOT enter confined spaces until atmosphere has been checked. DO NOT allow material to contact humans, exposed food or food utensils. Avoid contact with incompatible materials. When handling, DO NOT eat, drink or smoke. Keep containers securely sealed when not in use. Avoid physical damage to containers. Always wash hands with soap and water after handling. Work clothes should be laundered separately. Launder contaminated clothing before re-use. Use good occupational work practice. Observe manufacturer's storage and handling recommendations contained within this SDS. Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.
Other information	 Store in original containers. Keep containers securely sealed. Store in a cool, dry area protected from environmental extremes. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS. For major quantities: Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams). Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.

Conditions for safe storage, including any incompatibilities

Suitable container	 Lined metal can, lined metal pail/ can. Plastic pail. Polyliner drum. Packing as recommended by manufacturer. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	None known

SECTION 8 Exposure controls / personal protection

Control parameters

Occupational Exposure Limits (OEL)

INGREDIENT DATA

Not Available

Emergency Limits

Ingredient	TEEL-1	TEEL-2	TEEL-3
2,5-Bis(trifluoromethyl)phenylacetic acid	Not Available	Not Available	Not Available

ngredient	Original IDLH	Revised IDLH
2,5-Bis(trifluoromethyl)phenylacetic acid	Not Available	Not Available
xposure controls		
Eng	nineering controls are used to remove a hazard or place a barrier	r between the worker and the hazard. Well-designed

Process controls which involve changing the way a job activity or process is done to reduce the risk.

Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation that strategically "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure.

- Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction.
- If in spite of local exhaust an adverse concentration of the substance in air could occur, respiratory protection should be considered.

Such protection might consist of:

- (a): particle dust respirators, if necessary, combined with an absorption cartridge:
- (b): filter respirators with absorption cartridge or canister of the right type;
- (c): fresh-air hoods or masks.

Air contaminants generated in the workplace possess varving "escape" velocities which, in turn, determine the "capture velocities" of fresh circulating air required to effectively remove the contaminant.

Appropriate engineering	Type of Contaminant:	Air Speed:
controls	direct spray, spray painting in shallow booths, drum filling, conveyer loading, crusher dusts, gas discharge (active generation into zone of rapid air motion)	1-2.5 m/s (200-500 f/min.)
	grinding, abrasive blasting, tumbling, high speed wheel generated dusts (released at high initial velocity into zone of very high rapid air motion).	2.5-10 m/s (500-2000 f/min.)

Within each range the appropriate value depends on:

Lower end of the range	Upper end of the range
1: Room air currents minimal or favourable to capture	1: Disturbing room air currents
2: Contaminants of low toxicity or of nuisance value only.	2: Contaminants of high toxicity
3: Intermittent, low production.	3: High production, heavy use
4: Large hood or large air mass in motion	4: Small hood-local control only

Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used

Individual protection measures, such as personal protective equipment

Eye and face protection



Safety glasses with side shields.

Chemical goggles

Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent]

Skin protection See Hand protection below

The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.

Hands/feet protection

The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be

Personal hygiene is a key element of effective hand care. Gloves must only be worm on channels. After using gloves, hands soluble works of and dried throughly, Application of a non-perfunder dinsitiaries in accommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: channels and dried throughly the glove type is dependent on usage. Important factors in the selection of gloves include: channels of trequency and durability of glove type is dependent on usage. Important factors in the selection of gloves include: channels of trequency and durability of glove trep is the selection of gloves include: channels according to EN 374. ASINZ 52161.101 or national equivalent). When only brief context is sexpected, a glove with a protection class of 5 or higher (breasthrough time greater than 200 minutes according to EN 374. ASINZ 5161.101 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for log-first when breakthrough time > 20 min Glove material glove that breakthrough time > 20 min Poor when figore anaettid glove diverse should be replaced. Clove thickness at your all a school diverse breakthrough time > 20 min Poor when figore anaettid glove that ask requirements and knowledge of treakthrough time. Breakthrough time > 20 min Poor when glove material. Breakthrough time > 20 min Poor when figore anaettid diverse types are less affected by any application of diverse material. Breakthrough time > 20 min Breakthrough time > 20 min		observed when making a final choice.
Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • represense and duration of notation. • demination esistence of gloves instandard (e.g. Europe EN 374, US F739, ASN25 2161.1 or national equivalent). • When protonged of frequently repeated contact may accur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10 or national equivalent). • When only bind contact is expected. a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN25 2161.10 or national equivalent). • When only bind contact is expected. according to EN 374, ASN25 2161.10 or national equivalent) is recommended. • Contaminated gloves should be replaced. Ac defined in ASTM F7399.96 in any application, gloves are rated as: • Excellent when breakthrough time - 20 min • Socid when breakthrough time - 20 min • For oreneal applications, gloves with a thickness typically greater than 0.35 mm, are recommended. Is should be emphasised that glove thickness is not necessarily a good predictor of glove model. Therefore, the manufacturer, the glove splot and the glove plot on the active typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove model. Therefore, the manufacturer, the glove thickness is not necessarily a good predictor of glove model. Therefore, the manufacturer, the glove thickness is not necessarily a glove treplated tasis. School and a should always be taken into a		Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands
 - frequency and duration of contact. - demoit nestance of gives material, - gives thickness and - distrify Selicit gives tested to a relevant standard (e.g. Europe EN 374, US F739, A5/NZS 2161.1 or national equivalent). - When prolonged of mutales according to EN 374, AS/NZS 2161.1.0 or national equivalent). - When prolonged of mutales according to EN 374, AS/NZS 2161.1.0 or national equivalent) is recommended. - When only bried contact is expected, a gives with a protection class of 3 or higher (breakthrough time greater than 40 minutes according to EN 374, AS/NZS 2161.1.0 or national equivalent) is recommended. - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. - Contaminated gloves should be replaced. As defined in ASTM F739.06 minutes - Good when breakthrough time > 480 min - Fair when breakthrough time > 400 min - Fair when breakthrough time > 20 min - Fair when breakthrough time > 20 min - Fair when breakthrough time > 400 min - Fair when breakthrough time > 400 min - Good when breakthrough time > 400 min - Fair when breakthrough time > 400 min - Good when breakthrough time > 400 min - Boor when gloves no consideration of the task cauciments and howiedge of topicer statual. Therefore, give selection should also be based on consideration of the task cauciments and howiedge of topicer statual. Therefore, give selection on the dust account to ensure selection of the mask. For example: - Thinner gloves (down to 0.1 mm or less) may be r		should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.
 - chemical resistance of give material, - give thickness and - desterity Select gives tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZ5 2161.1 or national equivalent), - When prolonged of requently repeated contact may occur, a give with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZ5 2161.10.1 or national equivalent) is recommended. - Contaminated gives should be replaced. - Contaminated gives should be replaced. - Contaminated gives should be replaced. - Contaminated gives and the replaced. - Contaminated gives material, gives with a thickness typically greater than 0.35 mm, are recommended. - Fair them breakthrough time > 20 min - Fair them breakthrough time > 20 min - Foor when gives material greates - Foor when gives material on the gives material, equivernest and the work of give restance to a specific chemical, as the permeation efficiency of the gives will be dependent on the exact composition of the gives material. Therefore, gives estection of the adves may applications, gives with a thickness typically greater than 0.35 mm, are recommended. - Thickness technical data should always to taken into account when considering gives for budy the give material. Therefore, gives estection of the adves the taken into account exact composition of the give waterial and therefore the give material. - Thickness gives will be dependent on the exact composition of the give material. Therefore, gives estection of the advess the taken into account evolution protection against undissolved, divy solids, where a break theoring there tavakes a demicial risk i.e. where there is a barcanion prutue		Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include:
 glove thickness and glove thickness and destretity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.10 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 80 minutes according to EN 374, AS/NZS 2110.10 or national equivalent) is recommended. When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 80 minutes according to EN 374, AS/NZS 2110.10 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min For general applications, gloves with a biokness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetion efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always to taken into account on escue selection at the most appropriate glove of take. Note: Depending on the activity being conducted, gloves of varying thickness may as a chemical, as the gloves model. Glove rolenal data as the required where here is a mechanical (as well as a chemical) is i.e. where there is abreation or plove transition or plove material. Therefore, glove selection of the ack complex of manufacturers is needed. Note: Depending on the activity being conducted, gloves of varying thickness may also complexenter is an eclavation; is ex		frequency and duration of contact,
 åxerinjv åxerinjv Select gjöves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N2S 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a gjöve with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N2S 2161.1.0.1 or national equivalent) is recommended. Some gjöve ophmer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F739-96 in any application, gloves are rated as: Excellent when breakthrough time > 420 min Good when breakthrough time > 420 min Fair when breakthrough time > 420 min Foor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be based on consideration of the taken into account when considering gloves should be taken into account when considering the set 480 min Good when breakthrough time > 20 min Foor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be based on consideration of the take requirements and knowledge of breakthrough time, set 480 minutes according to the glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be based on consideration of the take requirements and knowledge of breakthrough time set 480 minutes according to the set 480 minutes		· chemical resistance of glove material,
Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AXR25 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASR25 2161.10.1 or national equivalent) is recommended. • When only bief contact is expected. a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASR25 2161.10.1 or national equivalent). • Gortaminated gloves should be replaced. • A defined in ASTM F73-96 bit in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • For yeneral glove with a dividences typically greater than 0.35 mm, are recommended. It is should be emphasised that glove with a dipotness typically greater than 0.35 mm, are recommended. It is should be emphasised that glove with a dipotness typically greater than 0.35 mm, are recommended. It is should be emphasised that glove with a dipotness typically greater than 0.35 mm, are recommended. It is should be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove material. Therefore, the manufacturer, the glove type and the glove model. Therefore, the manufacturer, the glove type and the glove model. Therefore, the manufacturer storhical data should always be taken into account to ensure selection of the most appropriate glove for thatesk. Note: Depending on the activity being conducted		· glove thickness and
• When prolonged or frequently repeated contact may occur, a glowe with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended. • When only birle contact is expected, a glowe with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASN/25 2161.10.1 or national equivalent) is recommended. • Some glowe ophimer types are less affected by movement and this should be taken into account when considering glowes for long-term use. • Contaminated glowes should be replaced. As defined in ASTM 739-96 in any application, glowes are rated as: • Excellent when breakthrough time > 420 min • Good when breakthrough time > 20 min • Pair when breakthrough time > 20 min • Pair when breakthrough time > 20 min • Brow making degrades For general applications, glowes with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glowe thickness is not necessarily a good predictor of glowe resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material devices the should be required by the specific device the should be treacher the should be replaced. Rischould be replaced. Rischould be replaced. Rischould also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the activit		· dexterity
greater than 240 minutes according to EN 374, ASIN25 2161.10.1 or national equivalent) is recommended. • When only bried contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASIN25 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove with a dive thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufactures technical data should always be should a bord always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thickor gloves (up to 3 mm or more) may be required where a high degree of manual destretions, the disposed of. • Thickor gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a breacino no cloud normally be jus		Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).
• When only brief contact is expected, a glove with a protection class of 30 higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 21611.0.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for lengterm use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Good when breakthrough time > 20 min • Poor when glove material gloves is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove mit be dependent on the exact composition of the glove model. Therefore, the manulactures technical data should always be taken into account or ensult devertify is needed. However, these gloves gloves don't being on the glove wing on the glove muterial. Therefore, the manulacture stending on the active diprive diverse high degree of manual devertify is needed. However, these gloves gloves gloves don't use in ordection and would normally be just for single use applications, the other diverse high degree of manual devertify is needed. However, these gloves gloves gloves don't lengt when the other a high degree of manual devertify is needed. However, these gloves gloves on the other divertify being conducted, gloves of way of general data. Note: Degree/filt casks. For example: • Thicker gloves (up to 3 mm or more) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abraisin or puncture potential Gloves since and polymers are suitable as glove materials for protection against undissolved, dry solids, where a braisive particles are no		· When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time
according to EN 374, AS/NZS 2161.0.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Sociell in ASTIM F-739-80 in any application, gloves are rated as: • Cover thickness may also vary depending on the clove application, there as proprise gloves for teaks. • As defined in the task requirements and knowledge of breakthrough times. • Glove thickness may also vary depending on the acount to ensure selection of the most approprise gloves for teaks. Note:		greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time < 20 min • Good when breakthrough time < 20 min • Good when breakthrough time < 20 min • Poor when glove material degrades • For openeral applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required there a high degree of manual doctarily is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 m or more) may be required where a high degree of manual doctarily is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 m or more) may be required where a high degree of manual doctarily is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 m or more) may b		· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
Image:		according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
• Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time < 20 min • Fair when breakthrough time < 20 min • For yeneral applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the porse type of the stak. Note: Depending on the ask menulacturer, the glove bype on the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the spote type of the task. Note: Depending on the ask manufacturer, the gloves duot to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is advariant on runcture patient and would depend on manufacturers technical data should always be taken into account to any single use applications, then disposed of. • Thicker gloves (up to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is advariant protection against undissolved, dry solids, where abarsive particles are not present. • polychloroprene. • hittig tubber. • polychloroprene. • hittig tubber. • polychloroprene. • hittig tubber. • polychloroprene. • polychloroprene. • hittig tubber. • polychloroprene. • polychloroprene. • polychloroprene. • polychloroprene. • polychloro		· Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for
As defined in ASTM F-739-96 in any application, gloves are rated as: 		long-term use.
• Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • Pair when breakthrough time > 20 min • Pair when breakthrough time > 20 min • Por when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It is hould be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times, algove selection should also be based on consideration of the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of - Thicker gloves (glove to 10 mm or ness) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves more on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dy solids, where abraive particles are not present. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. Polychioroprene. 		Contaminated gloves should be replaced.
 Good when breakthrough time > 20 min Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. bityl rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber.		As defined in ASTM F-739-96 in any application, gloves are rated as:
 Fair when breakthrough time < 20 min Poor when glove material degrades Progeneral applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task trequirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may becevities as the gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychiloroprene. huitile rubber. butyl rubber. butyl		Excellent when breakthrough time > 480 min
 Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the eativity being conducted, gloves of varying thickness may be required thore a high degree of manual destript is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where a tapic dependent and their protection against undissolved, dry solids, where abrasive particles are not present. Thicker gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroopene. third rubber. butyr lubber. butyr		· Good when breakthrough time > 20 min
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove maturaturer, the glove gove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, there there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. bo		· Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraison or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfured moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraise particles are not present. 		Poor when glove material degrades
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn o clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychiloroprene. • initrile rubber. • butyl fulbored. Gloves should he examined for wear and/ or degradation constantly.Body protectionSee Other protection belowChem protectionSee ream. • Skin cleansing cream. • Skin cleansing cream.		
should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. by loychloroprene. hittile rubber. butyl rubber. 		
Glove thickness may also vary depending on the glove manufacturer, the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber.		
Imanufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. butyl nubber. butyl nubber. 		
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: 		
 Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. Polychloroprene. Initrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below Other protection Shin cleansing cream. Skin cleansing cream. 		
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. * polychloroprene. * nitrile rubber. * bolychloroprene. * polychloroprene. * nitrile rubber. * bolychloroprene. * fluorocaoutchouc. * polychloroprene. * fluorocaoutchouc. * polychloroprene. * bolychloroprene. * fluorocaoutchouc.		
• Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrile rubber. • butyl rubber. • fluorocaoutchouc. • polychloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. > polychloroprene. > nitrile rubber. > butyl rubber. > butyl rubber. > butyl rubber. > fluorocaoutchouc. > polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. See Other protection below Other protection > Overalls. > P.V.C apron. > Barrier cream. > Skin cleansing cream. > Skin cleansing cream.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrile rubber. • butyl rubber. • butyl rubber. • fluorocaoutchouc. • polychloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. > polychloroprene. > nitrile rubber. > butyl rubber. > butyl rubber. > polychloroprene. > polychloroprene. > nitrile rubber. > butyl rubber. > butyl rubber. > polychloroprene.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. See Other protection below Other protection Barrier cream. Skin cleansing cream. Skin cleansing cream. 		
where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polycyinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below Other protection Barrier cream. Skin cleansing cream. 		
i polychloroprene. nitrile rubber. butyl rubber. butyl rubber. fluorocaoutchouc. polycyinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below Other protection P.V.C apron. Barrier cream. Skin cleansing cream. Skin cleansing cream. 		
• nitrile rubber. • butyl rubber. • fluorocaoutchouc. • polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		
Image:		
Image:		▶ butyl rubber.
Gloves should be examined for wear and/ or degradation constantly. Body protection See Other protection below Other protection P.V.C apron. Barrier cream. Skin cleansing cream.		•
Body protection See Other protection below Other protection • Overalls. • P.V.C apron. • Barrier cream. • Skin cleansing cream.		polyvinyl chloride.
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		Gloves should be examined for wear and/ or degradation constantly.
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 	Body protection	See Other protection below
Other protection P.V.C apron. Barrier cream. Skin cleansing cream. 		
Other protection Barrier cream. Skin cleansing cream. 		
► Skin cleansing cream.	Other	·
	Other protection	
r ⊑ye wash unit.		
		Cye wash unit.

Respiratory protection

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to

personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

 \cdot Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

SECTION 9 Physical and chemical properties

Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	95-98	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

SECTION 10 Stability and reactivity

Reactivity	See section 7
Chemical stability	Product is considered stable and hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

SECTION 11 Toxicological information

Information on toxicological effects

Inhaled

The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control

	measures be used in an occupational setting.
Ingestion	The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.
Skin Contact	The material is not thought to produce adverse health effects or skin irritation following contact (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.
Eye	This material can cause eye irritation and damage in some persons.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

Legend:

1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

Acute Toxicity	×	Carcinogenicity	×
Skin Irritation/Corrosion	¥	Reproductivity	×
Serious Eye Damage/Irritation	~	STOT - Single Exposure	*
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×

```
    Data available to make classification
```

SECTION 12 Ecological information

Toxicity

Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity
	4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) -
	Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
	No Data available for all ingredients	No Data available for all ingredients

Bioaccumulative potential

Ingredient	Bioaccumulation
	No Data available for all ingredients

Mobility in soil

Ingredient	Mobility
	No Data available for all ingredients

SECTION 13 Disposal considerations

Waste treatment methods	/aste treatment methods	
Product / Packaging disposal	 Recycle wherever possible or consult manufacturer for recycling options. Consult State Land Waste Management Authority for disposal. Bury residue in an authorised landfill. Recycle containers if possible, or dispose of in an authorised landfill. 	

SECTION 14 Transport information

Labels Required

Marine Pollutant NO

Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
2,5-Bis(trifluoromethyl)phenylacetic acid	Not Available

Transport in bulk in accordance with the IGC Code

Product name	Ship Type
2,5-Bis(trifluoromethyl)phenylacetic acid	Not Available

SECTION 15 Regulatory information

Safety, health and environmental regulations / legislation specific for the substance or mixture

National Inventory Status

National Inventory	Status
Australia - AIIC / Australia Non-Industrial Use	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Canada - DSL	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Canada - NDSL	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
China - IECSC	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Europe - EINEC / ELINCS / NLP	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Japan - ENCS	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Korea - KECI	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
New Zealand - NZIoC	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Philippines - PICCS	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
USA - TSCA	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Taiwan - TCSI	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Mexico - INSQ	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Vietnam - NCI	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Russia - FBEPH	No (2,5-Bis(trifluoromethyl)phenylacetic acid)
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.

SECTION 16 Other information

Revision Date	26/05/2023
Initial Date	26/05/2023

SDS Version Summary

Version Date of Update	Sections Updated
------------------------	------------------

Version	Date of Update	Sections Updated
0.2	26/05/2023	Hazards identification - Classification, Composition / information on ingredients - Ingredients, Identification of the substance / mixture and of the company / undertaking - Supplier Information, Identification of the substance / mixture and of the company / undertaking - Synonyms

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available

engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

Definitions and abbreviations

 ${\sf PC-TWA}: {\sf Permissible \ Concentration-Time \ Weighted \ Average}$

PC-STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit。

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H335	Expert judgement
Skin Corrosion/Irritation Category 2, H315	Expert judgement
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement

Powered by AuthorITe, from Chemwatch.