

# 3-(Benzyloxy)-4-fluorobenzeneboronic acid Apollo Scientific

Part Number: **PC7572** Version No: **3.3** Safety Data Sheet Chemwatch Hazard Alert Code: 2

Issue Date: **29/06/2023** Print Date: **29/06/2023** S.GHS.GB-NIR.EN

# SECTION 1 Identification of the substance / mixture and of the company / undertaking

### **Product Identifier**

Product name	3-(Benzyloxy)-4-fluorobenzeneboronic acid	
Chemical Name	benzyloxy-4-fluorophenylboronic acid	
Synonyms	Not Available	
Other means of identification	Not Available	
CAS number	957034-74-1*	

### Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Not Available
Relevant identified uses	Not Available

### Details of the manufacturer or supplier of the safety data sheet

Registered company name	Apollo Scientific	Apollo Scientific Itd	
Address	Vhitefield Road, Bredbury SK62QR United Kingdom Whitefield Road, Bredbury SK6 2QR United Kingdom		
Telephone	01614060505 +44(0) 161 406 0505		
Fax	x 0161 406 0506 Not Available		
Website	http://www.apolloscientific.co.uk/ apolloscientific.co.uk		
Email	nail sales@apolloscientific.co.uk sales@apolloscientific.co.uk		

# Emergency telephone number

Association / Organisation	Not Available
Emergency telephone numbers	Not Available
Other emergency telephone numbers	Not Available

### **SECTION 2 Hazards identification**

### Classification of the substance or mixture

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments <sup>[1]</sup>

H312 - Acute Toxicity (Dermal) Category 4, H332 - Acute Toxicity (Inhalation) Category 4, H335 - Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H302 - Acute Toxicity (Oral) Category 4, H315 - Skin Corrosion/Irritation Category 2, H319 - Serious Eye Damage/Eye Irritation Category 2

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI

# Label elements

Hazard pictogram(s)	
Signal word	Warning

### Hazard statement(s)

H312	Harmful in contact with skin.	
H332	Harmful if inhaled.	
H335	May cause respiratory irritation.	
H302	Harmful if swallowed.	
H315	Causes skin irritation.	
H319	Causes serious eye irritation.	

# Precautionary statement(s) Prevention

P271 Use only outdoors or in a well-ventilated area.	
P261 Avoid breathing dust/fumes.	
P264	Wash all exposed external body areas thoroughly after handling.
P270	Do not eat, drink or smoke when using this product.
P280	Wear protective gloves, protective clothing, eye protection and face protection.

### Precautionary statement(s) Response

P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P337+P313	If eye irritation persists: Get medical advice/attention.	
P301+P312	IF SWALLOWED: Call a POISON CENTER/doctor/physician/first aider if you feel unwell.	
P302+P352	IF ON SKIN: Wash with plenty of water.	
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.	
P330	Rinse mouth.	
P332+P313	If skin irritation occurs: Get medical advice/attention.	
P362+P364	Take off contaminated clothing and wash it before reuse.	

# Precautionary statement(s) Storage

P405	Store locked up.	
P403+P233	Store in a well-ventilated place. Keep container tightly closed.	

# Precautionary statement(s) Disposal

P501

Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

# **SECTION 3 Composition / information on ingredients**

### Substances

CAS No	%[weight]	Name	Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	SCL / M-Factor
957034-74-1*	100	<u>3-(Benzyloxy)-</u> <u>4-fluorobenzeneboronic</u> <u>acid</u>	Acute Toxicity (Dermal) Category 4, Acute Toxicity (Inhalation) Category 4, Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, Acute Toxicity (Oral) Category 4, Skin Corrosion/Irritation Category 2, Serious Eye Damage/Eye Irritation Category 2; H312, H332, H335, H302, H315, H319 <sup>[1]</sup>	Not Available

Legend: 1. Classified by Chemwatch; 2. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 3. Classification drawn from C&L; \* EU IOELVs available; [e] Substance identified as having endocrine disrupting properties

See section above for composition of Substances

# **SECTION 4 First aid measures**

# Description of first aid measures If this product comes in contact with the eyes: Wash out immediately with fresh running water. • Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally Eve Contact lifting the upper and lower lids. ▶ Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel. If skin contact occurs: Immediately remove all contaminated clothing, including footwear. Skin Contact Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation. If fumes or combustion products are inhaled remove from contaminated area. Lav patient down. Keep warm and rested. Prostheses such as false teeth, which may block airway, should be removed, where possible, prior to initiating first aid procedures. Inhalation Apply artificial respiration if not breathing, preferably with a demand valve resuscitator, bag-valve mask device, or pocket mask as trained. Perform CPR if necessary. Transport to hospital, or doctor. IF SWALLOWED, REFER FOR MEDICAL ATTENTION, WHERE POSSIBLE, WITHOUT DELAY. ▶ For advice, contact a Poisons Information Centre or a doctor. Urgent hospital treatment is likely to be needed. In the mean time, qualified first-aid personnel should treat the patient following observation and employing supportive measures as indicated by the patient's condition. • If the services of a medical officer or medical doctor are readily available, the patient should be placed in his/her care and a copy of the SDS should be provided. Further action will be the responsibility of the medical specialist. If medical attention is not available on the worksite or surroundings send the patient to a hospital together with a copy of the Ingestion SDS. Where medical attention is not immediately available or where the patient is more than 15 minutes from a hospital or unless instructed otherwise: • INDUCE vomiting with fingers down the back of the throat, ONLY IF CONSCIOUS. Lean patient forward or place on left side (head-down position, if possible) to maintain open airway and prevent aspiration. NOTE: Wear a protective glove when inducing vomiting by mechanical means.

### Indication of any immediate medical attention and special treatment needed

As in all cases of suspected poisoning, follow the ABCDEs of emergency medicine (airway, breathing, circulation, disability, exposure), then the ABCDEs of toxicology (antidotes, basics, change absorption, change distribution, change elimination). For poisons (where specific treatment regime is absent):

------

### BASIC TREATMENT

- Establish a patent airway with suction where necessary.
- Watch for signs of respiratory insufficiency and assist ventilation as necessary.
- Administer oxygen by non-rebreather mask at 10 to 15 L/min.
- Monitor and treat, where necessary, for pulmonary oedema.
- Monitor and treat, where necessary, for shock.
- Anticipate seizures.
- DO NOT use emetics. Where ingestion is suspected rinse mouth and give up to 200 ml water (5 ml/kg recommended) for dilution where patient is able to swallow, has a strong gag reflex and does not drool.

#### ADVANCED TREATMENT

- Positive-pressure ventilation using a bag-valve mask might be of use.
- Monitor and treat, where necessary, for arrhythmias.
- Start an IV D5W TKO. If signs of hypovolaemia are present use lactated Ringers solution. Fluid overload might create complications.
- Drug therapy should be considered for pulmonary oedema.
- + Hypotension with signs of hypovolaemia requires the cautious administration of fluids. Fluid overload might create complications.
- Treat seizures with diazepam.
- Proparacaine hydrochloride should be used to assist eye irrigation.

<sup>+</sup> Consider orotracheal or nasotracheal intubation for airway control in unconscious patient or where respiratory arrest has occurred.

BRONSTEIN, A.C. and CURRANCE, P.L. EMERGENCY CARE FOR HAZARDOUS MATERIALS EXPOSURE: 2nd Ed. 1994

### **SECTION 5 Firefighting measures**

### Extinguishing media

There is no restriction on the type of extinguisher which may be used.

Use extinguishing media suitable for surrounding area.

### Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.
----------------------	-------------

### Advice for firefighters

Fire Fighting	<ul> <li>Alert Fire Brigade and tell them location and nature of hazard.</li> <li>Wear breathing apparatus plus protective gloves in the event of a fire.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Use fire fighting procedures suitable for surrounding area.</li> <li>DO NOT approach containers suspected to be hot.</li> <li>Cool fire exposed containers with water spray from a protected location.</li> <li>If safe to do so, remove containers from path of fire.</li> <li>Equipment should be thoroughly decontaminated after use.</li> </ul>
Fire/Explosion Hazard	<ul> <li>Non combustible.</li> <li>Not considered a significant fire risk, however containers may burn.</li> <li>May emit poisonous fumes.</li> <li>May emit corrosive fumes.</li> </ul>

### **SECTION 6 Accidental release measures**

### Personal precautions, protective equipment and emergency procedures

See section 8

### **Environmental precautions**

See section 12

# Methods and material for containment and cleaning up

Minor Spills	<ul> <li>Remove all ignition sources.</li> <li>Clean up all spills immediately.</li> <li>Avoid contact with skin and eyes.</li> <li>Control personal contact with the substance, by using protective equipment.</li> <li>Use dry clean up procedures and avoid generating dust.</li> <li>Place in a suitable, labelled container for waste disposal.</li> </ul>
Major Spills	<ul> <li>Moderate hazard.</li> <li>CAUTION: Advise personnel in area.</li> <li>Alert Emergency Services and tell them location and nature of hazard.</li> <li>Control personal contact by wearing protective clothing.</li> <li>Prevent, by any means available, spillage from entering drains or water courses.</li> <li>Recover product wherever possible.</li> <li>IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. IF WET: Vacuum/shovel up and place in labelled containers for disposal.</li> <li>ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.</li> <li>If contamination of drains or waterways occurs, advise Emergency Services.</li> </ul>

Personal Protective Equipment advice is contained in Section 8 of the SDS.

# **SECTION 7 Handling and storage**

# Precautions for safe handling

Safe handling	<ul> <li>Avoid all personal contact, including inhalation.</li> <li>Wear protective clothing when risk of exposure occurs.</li> <li>Use in a well-ventilated area.</li> </ul>
---------------	---

	Prevent concentration in hollows and sumps.
	DO NOT enter confined spaces until atmosphere has been checked.
	DO NOT allow material to contact humans, exposed food or food utensils.
	Avoid contact with incompatible materials.
	When handling, DO NOT eat, drink or smoke.
	Keep containers securely sealed when not in use.
	Avoid physical damage to containers.
	Always wash hands with soap and water after handling.
	Work clothes should be laundered separately. Launder contaminated clothing before re-use.
	Use good occupational work practice.
	Observe manufacturer's storage and handling recommendations contained within this SDS.
	Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are
	maintained.
	Store in original containers.
	Keep containers securely sealed.
	Store in a cool, dry area protected from environmental extremes.
	Store away from incompatible materials and foodstuff containers.
	Protect containers against physical damage and check regularly for leaks.
Other information	Observe manufacturer's storage and handling recommendations contained within this SDS.
	For major quantities:
	Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including
	stormwater, ground water, lakes and streams}.
	Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.

# Conditions for safe storage, including any incompatibilities

Suitable container	<ul> <li>Polyethylene or polypropylene container.</li> <li>Check all containers are clearly labelled and free from leaks.</li> </ul>
Storage incompatibility	None known

# **SECTION 8 Exposure controls / personal protection**

# **Control parameters**

### Occupational Exposure Limits (OEL)

# INGREDIENT DATA

Not Available

### Emergency Limits

Ingredient	TEEL-1	TEEL-2		TEEL-3
3-(Benzyloxy)- 4-fluorobenzeneboronic acid	Not Available	Not Available		Not Available
Ingredient	Original IDLH		Revised IDLH	
3-(Benzyloxy)- 4-fluorobenzeneboronic acid	Not Available		Not Available	

Occupational Exposure Banding		
Ingredient	Occupational Exposure Band Rating	Occupational Exposure Band Limit
3-(Benzyloxy)- 4-fluorobenzeneboronic acid	E	≤ 0.01 mg/m³
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposure band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.	

# Exposure controls

Appropriate engineering controls	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation

cal exhaust ventilation usually required. If risk of overexplain adequate protection. Supplied-air type respirator management of the protection in warehouse or closed storage adequate ventilation in warehouse or closed storage cape" velocities which, in turn, determine the "capture ventaminant. Appe of Contaminant: Appe of Contaminant of a pouring operations, intermittent on Apple theory shows that air velocity falls rapidly with distant the appropriate of distance from the erraction point should be adjusted, accordingly, after referraction fan, for example, should be a minimum of 1-2	ay be required in special circumstant hay be required in some situations. ge area. Air contaminants generate relocities" of fresh circulating air red (in still air). tainer filling, low speed conveyer tr at low velocity into zone of active of , conveyer loading, crusher dusts, of enerated dusts (released at high in Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only ince away from the opening of a sire extraction point (in simple cases). T	nces. Correct fi ed in the workpl quired to effecti ransfers, generation) gas discharge itial velocity	t is essential to lace possess varying vely remove the Air Speed: 0.25-0.5 m/s (50-100 f/min.) 0.5-1 m/s (100-200 f/min.) 1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
Alvent, vapours, degreasing etc., evaporating from tank is erosols, fumes from pouring operations, intermittent com elding, spray drift, plating acid fumes, pickling (released rect spray, spray painting in shallow booths, drum filling, ctive generation into zone of rapid air motion) inding, abrasive blasting, tumbling, high speed wheel ge to zone of very high rapid air motion). hin each range the appropriate value depends on: ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with distance raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	tainer filling, low speed conveyer tr at low velocity into zone of active of , conveyer loading, crusher dusts, e enerated dusts (released at high in Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only nnce away from the opening of a sir extraction point (in simple cases). T	generation) gas discharge iitial velocity mple extraction	0.25-0.5 m/s (50-100 f/min.) 0.5-1 m/s (100-200 f/min.) 1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
Alvent, vapours, degreasing etc., evaporating from tank is erosols, fumes from pouring operations, intermittent com elding, spray drift, plating acid fumes, pickling (released rect spray, spray painting in shallow booths, drum filling, ctive generation into zone of rapid air motion) inding, abrasive blasting, tumbling, high speed wheel ge to zone of very high rapid air motion). hin each range the appropriate value depends on: ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with distance raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	tainer filling, low speed conveyer tr at low velocity into zone of active of , conveyer loading, crusher dusts, e enerated dusts (released at high in Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only nnce away from the opening of a sir extraction point (in simple cases). T	generation) gas discharge iitial velocity mple extraction	0.25-0.5 m/s (50-100 f/min.) 0.5-1 m/s (100-200 f/min.) 1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
elding, spray drift, plating acid fumes, pickling (released rect spray, spray painting in shallow booths, drum filling, ctive generation into zone of rapid air motion) inding, abrasive blasting, tumbling, high speed wheel ge to zone of very high rapid air motion). hin each range the appropriate value depends on: ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion hiple theory shows that air velocity falls rapidly with distance raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	at low velocity into zone of active of , conveyer loading, crusher dusts, e enerated dusts (released at high in Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only ince away from the opening of a sire extraction point (in simple cases). T	generation) gas discharge iitial velocity mple extraction	0.5-1 m/s (100-200 f/min.) 1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
rect spray, spray painting in shallow booths, drum filling, ctive generation into zone of rapid air motion) inding, abrasive blasting, tumbling, high speed wheel ge to zone of very high rapid air motion). hin each range the appropriate value depends on: ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion hiple theory shows that air velocity falls rapidly with distance raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	<ul> <li>conveyer loading, crusher dusts, enerated dusts (released at high in</li> <li>Upper end of the range</li> <li>1: Disturbing room air currents</li> <li>2: Contaminants of high toxicity</li> <li>3: High production, heavy use</li> <li>4: Small hood-local control only</li> <li>ince away from the opening of a sire</li> <li>extraction point (in simple cases). T</li> </ul>	gas discharge iitial velocity	1-2.5 m/s (200-500 f/min.) 2.5-10 m/s (500-2000 f/min.)
inding, abrasive blasting, tumbling, high speed wheel ge to zone of very high rapid air motion). hin each range the appropriate value depends on: ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with distance raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	Upper end of the range 1: Disturbing room air currents 2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only ince away from the opening of a sir extraction point (in simple cases). T	mple extraction	2.5-10 m/s (500-2000 f/min.)
ower end of the range Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with dista nerally decreases with the square of distance from the e raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	<ol> <li>Disturbing room air currents</li> <li>Contaminants of high toxicity</li> <li>High production, heavy use</li> <li>Small hood-local control only</li> <li>ance away from the opening of a sire</li> <li>extraction point (in simple cases). T</li> </ol>	-	
Room air currents minimal or favourable to capture Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with distanerally decreases with the square of distance from the eraction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	<ol> <li>Disturbing room air currents</li> <li>Contaminants of high toxicity</li> <li>High production, heavy use</li> <li>Small hood-local control only</li> <li>ance away from the opening of a sire</li> <li>extraction point (in simple cases). T</li> </ol>	-	
Contaminants of low toxicity or of nuisance value only. Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with dista nerally decreases with the square of distance from the e raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	2: Contaminants of high toxicity 3: High production, heavy use 4: Small hood-local control only ince away from the opening of a sir extraction point (in simple cases). T	-	
Intermittent, low production. Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with distanterally decreases with the square of distance from the erraction point should be adjusted, accordingly, after referraction fan, for example, should be a minimum of 1-2 m	3: High production, heavy use 4: Small hood-local control only ince away from the opening of a sir extraction point (in simple cases). T	-	
Large hood or large air mass in motion nple theory shows that air velocity falls rapidly with dista nerally decreases with the square of distance from the e raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	4: Small hood-local control only ince away from the opening of a sir extraction point (in simple cases). T	-	
nple theory shows that air velocity falls rapidly with distance nerally decreases with the square of distance from the e raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	nce away from the opening of a sir extraction point (in simple cases). T	-	
nerally decreases with the square of distance from the e raction point should be adjusted, accordingly, after refer raction fan, for example, should be a minimum of 1-2 m	extraction point (in simple cases). T	-	
ters distant from the extraction point. Other mechanical paratus, make it essential that theoretical air velocities a talled or used.	considerations, producing perform	solvents generation ance deficits w	ated in a tank 2 ithin the extraction
<ul> <li>Safety glasses with side shields.</li> <li>Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent]</li> <li>Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59].</li> </ul>			
See Hand protection below			
nufacturer to manufacturer. Where the chemical is a pre- not be calculated in advance and has therefore to be of e exact break through time for substances has to be obt served when making a final choice. rsonal hygiene is a key element of effective hand care. O build be washed and dried thoroughly. Application of a no- tability and durability of glove type is dependent on usage	eparation of several substances, th shecked prior to the application. ained from the manufacturer of the Gloves must only be worn on clean on-perfumed moisturiser is recomm	e resistance of e protective glov n hands. After u nended.	the glove material ves and has to be using gloves, hands
	Chemical goggles. [AS/NZS 1337.1, EN166 or national Contact lenses may pose a special hazard; soft contact document, describing the wearing of lenses or restriction include a review of lens absorption and adsorption for the Medical and first-aid personnel should be trained in the event of chemical exposure, begin eye irrigation immediate be removed at the first signs of eye redness or irritation have washed hands thoroughly. [CDC NIOSH Current e Hand protection below e selection of suitable gloves does not only depend on the nufacturer to manufacturer. Where the chemical is a pre- not be calculated in advance and has therefore to be of exact break through time for substances has to be obterved when making a final choice. sonal hygiene is a key element of effective hand care. ( uld be washed and dried thoroughly. Application of a new context station of a new should be the station of a new context station of a new should be the station of a new context station of a new should be the station of a new context station of a new should be the station of a new should be the station of a new should be accurated the station of a new should be station of a new should be the station of a new should be there should be the station of a new should be the station of	Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent] Contact lenses may pose a special hazard; soft contact lenses may absorb and concentr document, describing the wearing of lenses or restrictions on use, should be created for e- include a review of lens absorption and adsorption for the class of chemicals in use and a Medical and first-aid personnel should be trained in their removal and suitable equipment event of chemical exposure, begin eye irrigation immediately and remove contact lens as be removed at the first signs of eye redness or irritation - lens should be removed in a cle have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59]. Hand protection below eselection of suitable gloves does not only depend on the material, but also on further ma nufacturer to manufacturer. Where the chemical is a preparation of several substances, th not be calculated in advance and has therefore to be checked prior to the application. exact break through time for substances has to be obtained from the manufacturer of the erved when making a final choice. sonal hygiene is a key element of effective hand care. Gloves must only be worn on clear uld be washed and dried thoroughly. Application of a non-perfumed moisturiser is recom- tability and durability of glove type is dependent on usage. Important factors in the selection	Chemical goggles. [AS/NZS 1337.1, EN166 or national equivalent] Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A v document, describing the wearing of lenses or restrictions on use, should be created for each workplace include a review of lens absorption and adsorption for the class of chemicals in use and an account of in Medical and first-aid personnel should be trained in their removal and suitable equipment should be reace event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practi- be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59]. Hand protection below eselection of suitable gloves does not only depend on the material, but also on further marks of quality w nufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of not be calculated in advance and has therefore to be checked prior to the application. exact break through time for substances has to be obtained from the manufacturer of the protective glove erved when making a final choice. sonal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After u uld be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. tability and durability of glove type is dependent on usage. Important factors in the selection of gloves inco

dexterity

Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.

according to EU 37, AS/N2S 2101.10.1 or national equivalent) is recommended.         - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use.         - Contaminate gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:         - Excellent when breakthrough time > 480 min         - Good when breakthrough time > 20 min         - Fair when breakthrough time > 20 min         - Por own glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It is should be emphasized that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Clove thickness may also vary depending on the gloves of varying thickness may be required for specific tasks. For example:         - Thinner gloves (down to 0.1 mm or iless) may be required where a high degree of manual destript is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         - Thicker gloves gloves in the rollowing polymers are suitable as glove materials for protection advect be reaktive.         Body protection       See Other protection below         - Thicker gloves should be examined for wear and/ or degradation constantly.         Experience indicates that the following polymers are suitable a		• When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes
Iong-term use.       Contaminated gloves should be replaced.         As defined in ASTM F-739-96 in any application, gloves are rated as:       Excellent when breakthrough time > 480 min         Good when breakthrough time > 20 min       For yomen glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.       It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.       It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.       It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         Should be explosited that glove thickness typically greater than 0.35 mm, are recommended.       It should be emphasised that glove thickness typically greater than 0.35 mm, are recommended.         Should be explosited that glove thickness typically greater than 0.35 mm, are recommended.       It should be explosed to consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinker gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a breasion or puncture potential</li> <ul> <li>Gloves must only be worn on clean hands. After us</li></ul></ul>		according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.
<ul> <li>Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as:         <ul> <li>Excellent when breakthrough time &gt; 40 min</li> <li>Good when breakthrough time &gt; 20 min</li> <li>Fair when breakthrough time &gt; 20 min</li> <li>For when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessary agood predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most apprintel glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required dors provide there a high degree of manual dexterity is needed. However, these gloves are only likely to give shot duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasino particles are not present.</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• buyly rubber.</li> <li>• fluorocaoutchouc.</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• buyly rubber.</li> <li>• fluorocaoutchouc.</li> <li>• polychloroprene.</li> <li>• hittile rubber:</li> <li>• buylyrubber.</li> <li>• fluorocaoutchouc.</li> <li>• polychl</li></ul></li></ul>		
As defined in ASTM F-739-96 in any application, gloves are rated as:         Excellent when breakthrough time > 400 min         Glove theo hor breakthrough time > 20 min         Fair when breakthrough time < 20 min         Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily agood predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove mauterial. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         Thinner gloves (down to 0.1 mm or less) may be required where here is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves are only likely to give shot duration protection and would normally be used protection against undissolved, dry solids, where abrasive particles are not present.         * polychloroprene.       * polychloroprene.         * hintle rubber.       * polychloroprene.         * hintle rubber		5
• Excellent when breakthrough time > 480 min         • Good when breakthrough time > 20 min         • Fair when breakthrough time > 20 min         • Por when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasized that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the glove type draving thickness may be required for specific tasks. For example:         • Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.       • hitlift rubber.         • budy thober.       • budy rubber.         • budy rubber.       • budy rubber. <th></th> <th></th>		
• Good when breakthrough time > 20 min         • Fair when breakthrough time < 20 min         • Poor when glove material degrades         For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.         It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove and the oglove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required of respecific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thickre gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abraision or puncture potential</li> <li>Glove smust only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>hitrile rubber.</li> <li>butyl rubber.</li> <li>floroca</li></ul>		
<ul> <li>Fair when breakthrough time &lt; 20 min</li> <li>Poor when glove material degrades</li> <li>For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thickreg gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barsaion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraisive particles are not present.</li> <li> bityl rubber.</li> <li> bityl r</li></ul>		
Poor when glove material degradesFor general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual desterity is needed. However, these sloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential 		-
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where a there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. > polychioroprene. > hittile intubber. Hourocaoutchouc. > polychioroprene. Hittile intubber.Model portectionSee Other protection belowSee Other protection belowOteralls. P.V.C apron.		· Fair when breakthrough time < 20 min
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times.         Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinker gloves (up to 3 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • huttper. • butyl tubber.         • hutyl routocauchouc.       • polychloroprene.         • nitrile rubber.       • butyl rubber.         • butyl rubber.       • butyl rubber.         • butyl rubber.       • butyl rubber.         • butyl rubber.		Poor when glove material degrades
permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these  gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul><li>Thinker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there          is abrasion or puncture potential</li><li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a          non-perfumed moisturiser is recommended.</li><li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids,          where abrasive particles are not present.</li><li>         bolychloroprene.</li><li>         intitle tubber.</li><li>         bolychloroprene.</li><li>         intitle tubber.</li><li>         bolychloroprene.</li><li>         intitle nubber.</li><li>         bolychloroprene.</li><li>         intitle nubber.</li><li>         bolychloroprene.</li><li>         intitle nubber.</li><li>         bolychloroprene.</li><li>         intitle nubber.</li><li>         bolychloroprene.</li><li>         bolychloroprene.</li><li>         bolychloroprene.</li><li>         bolychloroprene.</li><li>         bolychlo</li></ul></li></ul>		For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended.
should also be based on consideration of the task requirements and knowledge of breakthrough times.       Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:         • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • hitrile rubber.         • butyl rubber.		It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul><li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these  gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.  <ul><li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there  is abrasion or puncture potential  Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a              non-perfumed moisturiser is recommended.</li></ul></li><li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids,      where abrasive particles are not present.  <ul><li>polychloroprene.</li><li>hitriie rubber.</li><li>butyl rubber.</li><li>fluorocaoutchouc.</li><li>polychloroprene.</li><li>fluorocaoutchouc.</li><li>polychloroprene.</li><li>fluorocaoutchouc.</li><li>polychloroprene.</li><li>fluorocaoutchouc.</li><li>polyching cher for wear and/ or degradation constantly.</li></ul>Body protectionSee Other protection belowOveralls.<li>P.V.C apron.</li></li></ul>		permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection
manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: - Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. - Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. boltyl rubber. butyl rubor. butyl rubber. butyl rubb		should also be based on consideration of the task requirements and knowledge of breakthrough times.
Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: <ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.</li> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychily chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> <li>Body protection         <ul> <li>See Other protection below</li> <li>Overalls.</li> <li>P.V.C apron.</li> </ul> </li>		Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the
<ul> <li>Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         <ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential</li> <li>Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.</li> <li>Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polychloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> </li> <li>Body protection         <ul> <li>See Other protection below</li> <li>Overalls.</li> <li>P.V.C apron.</li> </ul> </li> </ul>		manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task.
gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.         Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential         Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • initrile rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • bolychloroprene.         • polycinloroprene.         • notyl rubber.         • butyl rubber.		Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example:
<ul> <li>Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.</li> <li>polychloroprene.</li> <li>nitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride. Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection See Other protection below <ul> <li>Overalls.</li> <li>P.V.C apron.</li> </ul>		• Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.		gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of.
is abrasion or puncture potential       Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • butyl rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. 		
non-perfumed moisturiser is recommended.         Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.		
Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.       • polychloroprene.         • polychloroprene.       • nitrile rubber.         • butyl rubber.       • butyl rubber.         • fluorocaoutchouc.       • polychloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • Overalls.         • P.V.C apron.       • Overalls.		
where abrasive particles are not present.         • polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.		·
• polychloroprene.         • nitrile rubber.         • butyl rubber.         • fluorocaoutchouc.         • polyvinyl chloride.         Gloves should be examined for wear and/ or degradation constantly.         Body protection         See Other protection below         • Overalls.         • P.V.C apron.		
<ul> <li>hitrile rubber.</li> <li>butyl rubber.</li> <li>fluorocaoutchouc.</li> <li>polyvinyl chloride.</li> <li>Gloves should be examined for wear and/ or degradation constantly.</li> </ul> Body protection See Other protection below I Overalls. <ul> <li>P.V.C apron.</li> </ul>		
• butyl rubber.       • fluorocaoutchouc.         • polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         • Overalls.       • Overalls.         • P.V.C apron.       • Overalls.		
Image: Protection below       * Overalls.         * Overalls.       * P.V.C apron.		
Image: Polyvinyl chloride.       Gloves should be examined for wear and/ or degradation constantly.         Image: Polycinyl chloride.       See Other protection below         Image: Polycinyl chloride.       Image: Polycinyl chloride.         Image: Polycinyl c		
Gloves should be examined for wear and/ or degradation constantly.         Body protection       See Other protection below         Image: Comparison of the protection below          • Overalls.         • P.V.C apron.		
Body protection     See Other protection below       Image: Description of the protection below <ul> <li>• Overalls.</li> <li>• P.V.C apron.</li> </ul> <ul> <li>• P.V.C apron.</li> </ul> <ul> <li>• Overalls.</li> <li>• P.V.C apron.</li> </ul> <ul> <li>• Overalls.</li> <li>• P.V.C apron.</li> </ul> <ul> <li>• P.V.C apron.</li> </ul> <ul> <li>• P.V.C apron.</li> <li>• P.V.C apron.</li> <li>• P.V.C apron.</li> <li>• P.V.C apron.</li> </ul> <ul> <li>• P.V.C apron.</li> <li>• P.V.C apron.</li> <li>• • • • • • • • • • • • • • • • • • •</li></ul>		
<ul> <li>Overalls.</li> <li>P.V.C apron.</li> </ul>		
► P.V.C apron.	Body protection	See Other protection below
► P.V.C apron.		► Overalls.
	Other protection	·
Skin cleansing cream.	p	
► Eve wash unit.		

### **Respiratory protection**

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*	-	PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

\* - Negative pressure demand \*\* - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

• Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

 $\cdot$  Try to avoid creating dust conditions.

Issue Date: 29/06/2023 Print Date: 29/06/2023

# 3-(Benzyloxy)-4-fluorobenzeneboronic acid

# **SECTION 9** Physical and chemical properties

# Information on basic physical and chemical properties

Appearance	Not Available		
Physical state	Solid	Relative density (Water = 1)	Not Available
Odour	Not Available	Partition coefficient n-octanol / water	Not Available
Odour threshold	Not Available	Auto-ignition temperature (°C)	Not Available
pH (as supplied)	Not Available	Decomposition temperature (°C)	Not Available
Melting point / freezing point (°C)	Not Available	Viscosity (cSt)	Not Available
Initial boiling point and boiling range (°C)	Not Available	Molecular weight (g/mol)	Not Available
Flash point (°C)	Not Available	Taste	Not Available
Evaporation rate	Not Available	Explosive properties	Not Available
Flammability	Not Available	Oxidising properties	Not Available
Upper Explosive Limit (%)	Not Available	Surface Tension (dyn/cm or mN/m)	Not Applicable
Lower Explosive Limit (%)	Not Available	Volatile Component (%vol)	Not Available
Vapour pressure (kPa)	Not Available	Gas group	Not Available
Solubility in water	Not Available	pH as a solution (1%)	Not Available
Vapour density (Air = 1)	Not Available	VOC g/L	Not Available

# **SECTION 10 Stability and reactivity**

Reactivity	See section 7
Chemical stability	<ul> <li>Unstable in the presence of incompatible materials.</li> <li>Product is considered stable.</li> <li>Hazardous polymerisation will not occur.</li> </ul>
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

# **SECTION 11 Toxicological information**

# Information on toxicological effects

Inhaled	Inhalation of dusts, generated by the material, during the course of normal handling, may be harmful. The material is not thought to produce respiratory irritation (as classified by EC Directives using animal models). Nevertheless inhalation of dusts, or fumes, especially for prolonged periods, may produce respiratory discomfort and occasionally, distress.
Ingestion	Accidental ingestion of the material may be harmful; animal experiments indicate that ingestion of less than 150 gram may be fatal or may produce serious damage to the health of the individual.
Skin Contact	Skin contact with the material may be harmful; systemic effects may result following absorption. The material is not thought to be a skin irritant (as classified by EC Directives using animal models). Abrasive damage however, may result from prolonged exposures. Open cuts, abraded or irritated skin should not be exposed to this material

	Entry into the blood-stream, through, for example, cuts, abrasions or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected.
Eye	This material can cause eye irritation and damage in some persons.
Chronic	Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified by EC Directives using animal models); nevertheless exposure by all routes should be minimised as a matter of course.

 Legend:
 1. Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS.

 Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances

Data available to make classification

Acute Toxicity	✓	Carcinogenicity	×
Skin Irritation/Corrosion	¥	Reproductivity	×
Serious Eye Damage/Irritation	×	STOT - Single Exposure	*
Respiratory or Skin sensitisation	×	STOT - Repeated Exposure	×
Mutagenicity	×	Aspiration Hazard	×
Legend: X – Data either not available or does not fill the criteria for classification			

# **SECTION 12 Ecological information**

### Toxicity

Legend:	Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity	
	4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data	

### DO NOT discharge into sewer or waterways.

# Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
	No Data available for all ingredients	No Data available for all ingredients

# **Bioaccumulative potential**

Ingredient	Bioaccumulation		
	No Data available for all ingredients		

# Mobility in soil

Ingredient	Mobility		
	No Data available for all ingredients		

# **SECTION 13 Disposal considerations**

Waste treatment methods			
Product / Packaging disposal	<ul> <li>Containers may still present a chemical hazard/ danger when empty.</li> <li>Return to supplier for reuse/ recycling if possible.</li> <li>Otherwise: <ul> <li>If container can not be cleaned sufficiently well to ensure that residuals do not remain or if the container cannot be used to store the same product, then puncture containers, to prevent re-use, and bury at an authorised landfill.</li> <li>Where possible retain label warnings and SDS and observe all notices pertaining to the product.</li> <li>Recycle wherever possible or consult manufacturer for recycling options.</li> <li>Consult State Land Waste Management Authority for disposal.</li> <li>Bury residue in an authorised landfill.</li> </ul> </li> </ul>		
	Recycle containers if possible, or dispose of in an authorised landfill.		

# **SECTION 14 Transport information**

### Labels Required

Marine Pollutant NO

# Land transport (ADR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

#### Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Inland waterways transport (ADN): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

### Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

#### Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
3-(Benzyloxy)- 4-fluorobenzeneboronic acid	Not Available

#### Transport in bulk in accordance with the IGC Code

Product name	Ship Type
3-(Benzyloxy)- 4-fluorobenzeneboronic acid	Not Available

### **SECTION 15 Regulatory information**

### Safety, health and environmental regulations / legislation specific for the substance or mixture

### 3-(Benzyloxy)-4-fluorobenzeneboronic acid is found on the following regulatory lists

Not Applicable

### **National Inventory Status**

National Inventory	Status		
Australia - AIIC / Australia Non-Industrial Use	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Canada - DSL	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Canada - NDSL	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
China - IECSC	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Europe - EINEC / ELINCS / NLP	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Japan - ENCS	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Korea - KECI	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
New Zealand - NZIoC	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Philippines - PICCS	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
USA - TSCA	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Taiwan - TCSI	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Mexico - INSQ	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Vietnam - NCI	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Russia - FBEPH	No (3-(Benzyloxy)-4-fluorobenzeneboronic acid)		
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.		

### **SECTION 16 Other information**

Initial Date 30/06/2023

### **SDS Version Summary**

Version	Date of Update	Sections Updated
2.3	29/06/2023	Hazards identification - Classification, Korean MSDS Number, Identification of the substance / mixture and of the company / undertaking - Supplier Information

### Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

For detailed advice on Personal Protective Equipment, refer to the following EU CEN Standards:

EN 166 Personal eye-protection

EN 340 Protective clothing

EN 374 Protective gloves against chemicals and micro-organisms

EN 13832 Footwear protecting against chemicals

EN 133 Respiratory protective devices

### **Definitions and abbreviations**

PC - TWA: Permissible Concentration-Time Weighted Average

PC - STEL: Permissible Concentration-Short Term Exposure Limit

IARC: International Agency for Research on Cancer

ACGIH: American Conference of Governmental Industrial Hygienists

STEL: Short Term Exposure Limit

TEEL: Temporary Emergency Exposure Limit.

IDLH: Immediately Dangerous to Life or Health Concentrations

ES: Exposure Standard

OSF: Odour Safety Factor

NOAEL :No Observed Adverse Effect Level

LOAEL: Lowest Observed Adverse Effect Level

TLV: Threshold Limit Value

LOD: Limit Of Detection

OTV: Odour Threshold Value

BCF: BioConcentration Factors

BEI: Biological Exposure Index

AIIC: Australian Inventory of Industrial Chemicals

DSL: Domestic Substances List

NDSL: Non-Domestic Substances List

IECSC: Inventory of Existing Chemical Substance in China

EINECS: European INventory of Existing Commercial chemical Substances

ELINCS: European List of Notified Chemical Substances

NLP: No-Longer Polymers

ENCS: Existing and New Chemical Substances Inventory

KECI: Korea Existing Chemicals Inventory

NZIoC: New Zealand Inventory of Chemicals

PICCS: Philippine Inventory of Chemicals and Chemical Substances

TSCA: Toxic Substances Control Act

TCSI: Taiwan Chemical Substance Inventory

INSQ: Inventario Nacional de Sustancias Químicas

NCI: National Chemical Inventory

FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

#### Classification and procedure used to derive the classification for mixtures according to Regulation (EC) 1272/2008 [CLP]

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Acute Toxicity (Dermal) Category 4, H312	On basis of test data
Acute Toxicity (Inhalation) Category 4, H332	On basis of test data

Classification according to regulation (EC) No 1272/2008 [CLP] and amendments	Classification Procedure
Specific Target Organ Toxicity - Single Exposure (Respiratory Tract Irritation) Category 3, H335	Expert judgement
Acute Toxicity (Oral) Category 4, H302	On basis of test data
Skin Corrosion/Irritation Category 2, H315	Expert judgement
Serious Eye Damage/Eye Irritation Category 2, H319	Expert judgement

Powered by AuthorITe, from Chemwatch.